Standard Specification for Uranium Metal Enriched to More than 15 % and Less Than 20 % 235 U1

This standard is issued under the fixed designation C 1462; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This specification covers nuclear grade uranium metal that has either been processed through an enrichment plant, or has been produced by the blending of highly enriched uranium with other uranium, to obtain uranium of any ²³⁵U concentration below 20 % (and greater than 15 %) and that is intended for research reactor fuel fabrication. The scope of this specification includes specifications for enriched uranium metal derived from commercial natural uranium, recovered uranium, or highly enriched uranium. Commercial natural uranium, recovered uranium and highly enriched uranium are defined in Section 3. The objectives of this specification are to define the impurity and uranium isotope limits for commercial grade enriched uranium metal.
- 1.2 This specification is intended to provide the nuclear industry with a standard for enriched uranium metal which is to be used in the production of research reactor fuel. In addition to this specification, the parties concerned may agree to other appropriate conditions.
- 1.3 The scope of this specification does not comprehensively cover all provisions for preventing criticality accidents or requirements for health and safety or for shipping. Observance of this standard does not relieve the user of the obligation to conform to all applicable international, federal, state, and local regulations for processing, shipping, or any other way of using uranium metal (see, for example, C 996 regarding references).

2. Referenced Documents

- 2.1 ASTM Standards:
- C 696 Test Methods for Chemical, Mass Spectrometric, and Spectrochemical Analysis of Nuclear-Grade Uranium Dioxide Powers and Pellets²
- C 799 Test Methods for Chemical, Mass Spectrometric, Spectrochemical, Nuclear, and Radiochemical Analysis of Nuclear-Grade Uranyl Nitrate Solutions²
- C 859 Terminology Relating to Nuclear Materials²
- C 996 Specification for Uranium Hexafluoride Enriched to less than 5 % $^{235} U^2$

- C 1233 Practice for Determining the Equivalent Boron Content of Nuclear Material²
- C 1295 Test Method for Gamma Energy Emission from Fission Products in Uranium Hexafluoride and Uranium Solutions²
- C 1347 Practice for Preparation and Dissolution of Uranium Materials for Analysis²
- 2.2 ANSI Standard
- ANSI-ASME NQA-1 Quality Assurance Program Requirements for Nuclear Facility Applications³
- 2.3 U.S. Government Documents
- Code of Federal Regulations, Title 10, Part 50, (Appendix B)⁴

3. Terminology

- 3.1 *Definitions of Terms Specific to This Standard*—Terms shall be defined in accordance with Terminology C 859, except for the following:
- 3.1.1 commercial grade enriched uranium metal—uranium metal derived from commercial natural uranium, recovered uranium, or uranium obtained from the blending of highly enriched uranium with commercial natural uranium, recovered uranium, or depleted uranium.
- 3.1.2 commercial natural uranium—any form of natural unirradiated uranium (containing 0.711 + 0.004 g 235 U per 100 g U).
- 3.1.3 *depleted uranium*—any form of unirradiated uranium with a ²³⁵U content less than commercial natural uranium.
- 3.1.4 *highly enriched uranium*—any form of uranium having a ²³⁵U content equal to or in excess of 20 %.
- 3.1.5 recovered uranium—any form of uranium that has been exposed in a neutron irradiation facility and either has been subsequently chemically separated from the fission products and transuranic isotopes so generated, or may be used as is, due to low irradiation levels.
- 3.1.5.1 *Discussion*—The requirements for recovered uranium are intended to be typical of reprocessed spent fuel from research reactors that have achieved burn-up levels of up to 50 % of the originally contained fissile material or may have been utilized in critical facilities. It is recognized that different

¹ This specification is under the jurisdiction of ASTM Committee C-26 on Nuclear fuel Cycle and is the direct responsibility of Subcommittee C26.02 on Fuel and Fertile Material Specifications.

Current edition approved Apr. 10, 2000. Published May 2000.

² Annual Book of ASTM Standards, Vol 12.01.

 $^{^3}$ Available from the American National Standards Institute, 11 W. 42nd St, 13th Floor, New York, NY 10036.

⁴ Available from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.



limits would be necessary to accommodate different fuel histories.

3.1.6 For enriched uranium metal transactions, "buyer" usually represents the research reactor operator or the fuel fabricator, and "seller" usually represents the supplier of the enriched uranium metal.

4. Health Physics Requirements

4.1 For commercial grade enriched uranium metal, the gamma activity from fission products shall not exceed 600 Bq/gU. The measurements are to be made by Test Method C 1295 or equivalent. See Note 1.

Note 1—Depending upon the requirements of the fabricator utilizing enriched uranium metal, gamma activity from fission products as high as 6,000 Bq/gU may be acceptable, due to the utilization of reprocessed enriched uranium in producing the enriched uranium metal.

4.2 For commercial grade enriched uranium metal, the total alpha activity from transuranium elements shall be less than 250 Bq/gU.

5. Chemical, Physical, and Isotopic Requirements

- 5.1 Physical Requirements:
- 5.1.1 The uranium content of commercial grade enriched uranium metal shall be greater than or equal to 99.85 weight percent.
- 5.1.2 The product shall be supplied as spherical, cubical, cylindrical or broken pieces, with dimensions of not more than 40 mm or less than 10 mm. The mass of individual pieces shall be between 130 and 300 g.
- 5.1.3 The individual pieces of product shall be free of loose or excessive oxides or contaminants. A tightly adhering oxide film is allowable.
- 5.1.4 The following impurity elements shall not exceed these values:

Element		μg/gU	Element	μg	/gU
Aluminum	ΑI	150	Magnesium	Mg	50
Boron	В	1	Manganese	Mn	50
Beryllium	Be	10	Molybdenum	Mo	100
Carbon	С	800	Nickel	Ni	100
Calcium	Ca	100	Phosphorus	Р	100
Cadmium	Cd	1	Silicon	Si	250
Chromium	Cr	50	Sodium	Na	25
Cobalt	Co	10	Tin	Sn	100
Copper	Cu	50	Vanadium	V	30
Iron	Fe	250	Tungsten	W	100
Lead	Pb	10	Zirconium	Zr	250
Lithium	Li	10			
Rare Earths (Dy, Eu, Gd, Sm)					3.0

The sum of the impurity elements shall not exceed 1500 $\mu g/gU$.

5.1.5 Equivalent Boron Content—For research reactor use, the total equivalent boron content (EBC) shall not exceed 4.0

µg/gU. The list of elements to be considered for the EBC calculation shall be agreed upon between the buyer and the seller. The method of performing the calculation and the EBC Factors shall be as indicated in Practice C 1233. For fast reactor use, the above limitation on total EBC does not apply.

- 5.2 Isotopic Requirements:
- 5.2.1 The following limits for commercial grade enriched uranium metal shall not be exceeded:

²³² U	0.002 μg/gU
²³⁴ U	0.01 g/gU
²³⁶ U	0.04 g/gU

5.2.2 Uranium isotopic concentrations shall be determined and reported for 232 U, 234 U, 235 U, and 236 U. The allowable variation for 235 U shall be \pm 0.20 weight percent absolute from the nominal 235 U assay.

6. Sampling

- 6.1 A representative sample of sufficient size to perform tests prescribed shall be taken from each lot. The size of a lot shall be as agreed upon between seller and buyer and shall be from a single melt. Typically, a lot shall not be greater than 10 kg.
- 6.2 All samples shall be clearly identified including the seller's lot number.
- 6.3 All containers used for a lot shall be positively identified as containing material from a particular lot.
- 6.4 ASTM standard practice for preparation of uranium materials (Practice C 1347), or demonstrated equivalent shall be used as mutually agreed upon between the buyer and seller.

7. Test Methods for Chemical and Isotopic Analysis

7.1 ASTM test methods for chemical and isotopic analysis (Test Methods C 696 or C 799), or demonstrated equivalent, shall be used as mutually agreed upon between the buyer and seller

8. Packaging, Handling, and Shipping

8.1 Procedures for packaging, handling, and shipping commercial grade enriched uranium metal are as agreed between buyer and seller and shall be in accordance with applicable national or international procedures.

9. Quality Assurance

9.1 Quality assurance requirements shall be agreed upon between the buyer and the seller when specified in the purchase order. Code of Federal Regulations, Title 10, Part 50 (Appendix B) and NQA-1 are referenced as guides.

10. Keywords

10.1 medium enriched uranium; nuclear fuel; research reactor fuel; uranium metal

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.





This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).