



# Standard Specification for Solvent Release Sealants<sup>1</sup>

This standard is issued under the fixed designation C 1311; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification describes the properties of a one-component solvent release sealant for use in building construction. These sealants are generally formulated to withstand a maximum joint movement of 7.5 % in extension and 7.5 % in compression of the nominal joint width.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The committee with jurisdiction of this specification is not aware of any similar specification within ISO or any other organization.

## 2. Referenced Documents

### 2.1 ASTM Standards:

- C 661 Test Method for Indentation Hardness of Elastomeric-Type Sealants by Means of a Durometer<sup>2</sup>
- C 712 Test Method for Bubbling of One-Part, Elastomeric, Solvent-Release Type Sealants<sup>2</sup>
- C 717 Terminology of Building Seals and Sealants<sup>2</sup>
- C 1193 Guide for Use of Joint Sealants<sup>2</sup>
- C 1216 Test Method for Adhesion and Cohesion of One-Part Elastomeric Solvent Release Sealants<sup>2</sup>
- C 1257 Test Method for Accelerated Weathering of Solvent-Release-Type Sealants<sup>2</sup>
- D 2202 Test Method for Slump of Sealants<sup>2</sup>
- D 2203 Test Method for Staining from Sealants<sup>2</sup>
- D 2377 Test Method for Tack-Free Time of Caulking Compounds and Sealants<sup>2</sup>
- D 2452 Test Method for Extrudability of Oil- and Resin-Base Caulking Compounds<sup>2</sup>

## 3. Terminology

3.1 *Definitions*—Definitions of the following terms used in this specification are found in Terminology C 717: adhesive

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is under the direct responsibility of Subcommittee C24.10 on Specifications, Guides and Practices.

Current edition approved May 10, 2002. Published June 2002. Originally published as C 1311–95. Last previous edition C 1311–95.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.07.

failure (adhesion loss), caulk ( $\nu$ ), compound, durometer, hardness, joint, primer, seal, sealant, sealing material, and solvent release sealant.

## 4. Materials and Manufacture

4.1 The sealing compound shall be a solvent release material compounded to conform to the requirements prescribed in this specification.

4.2 All material and workmanship shall be in accordance with good commercial practice. The producer is permitted a wide latitude in choice of raw materials for making these products. Consequently, there is no implication that the compounds are equivalent in all physical properties.

4.3 The manufacturing process shall be such as will ensure a homogeneous mix, free of defects that would affect serviceability, and of a consistency suitable for immediate application.

## 5. General Requirements

5.1 *Standard Conditions*—Perform all of the tests in a laboratory controlled at  $23 \pm 2^\circ\text{C}$  ( $73 \pm 3.6^\circ\text{F}$ ) and  $50 \pm 10\%$  relative humidity. Condition sealant samples for at least 5 h at these conditions before any tests are performed.

5.2 The sealant in the original container shall be suitable for use for at least 12 months from the date of manufacture when stored at a temperature neither below  $5^\circ\text{C}$  ( $41.0^\circ\text{F}$ ) nor exceeding  $27^\circ\text{C}$  ( $80.6^\circ\text{F}$ ).

5.3 The color of the sealant shall be as agreed upon between the purchaser and the manufacturer.

5.4 The sealant shall be intended for use only on clean, dry surfaces. When a primer is recommended by a manufacturer for a specific substrate, all tests on that substrate shall include the primer. The proper use of primers (or surface conditioners) with the application of sealants is described in detail in Guide C 1193. This guide also describes proper methods for joint design, backup materials, surface preparation, tooling of sealant, and other important procedures in sealant application in buildings.

## 6. Significance and Use

6.1 This specification describes solvent release sealants for general caulking and sealing operations in building construction. However, it should be recognized by the user that not all

sealants meeting this specification are suitable for all applications and all substrates and that there is no implication that the sealants are equivalent in all physical properties.

6.2 Refer to Guide **C 1193** for information on the proper use of sealants meeting this specification.

## 7. Physical Requirements

7.1 The sealant shall conform to the physical requirements specified in **Table 1**.

## 8. Test Methods

8.1 *Indentation Hardness*—Refer to Test Method **C 661**.

8.2 *Bubbling*—Refer to Test Method **C 712**.

8.3 *Adhesion and Cohesion After Cyclic Movement*—Refer to Test Method **C 1216**.

8.4 *Accelerated Weathering*—Refer to Test Method **C 1257**.

8.5 *Slump*—Refer to Test Method **D 2202**.

8.6 *Staining*—Refer to Test Method **D 2203**.

8.7 *Tack-Free Time*—Refer to Test Method **D 2377**.

8.8 *Extrudability After Aging*—Refer to Test Method **D 2452**.

## 9. Packaging and Package Marking

9.1 Unless otherwise specified in the contract or order, the sealant shall be packaged in standard commercial containers constructed so as to ensure acceptance by common or other carrier for safe transportation to the point of delivery.

9.2 Shipping containers shall be marked with the name, grade, and quantity of the sealant contained therein, as defined by the contract or order under which shipments are made. The name of the supplier and the lot or batch shall also be shown.

## 10. Keywords

10.1 accelerated weathering; application life; bubbling; extrusion rate; sealant; sealing compound (sealing material); slump; solvent-release sealant; staining; tack free

**TABLE 1 Physical Requirements**

Property	Requirement	Test Method
Extrudability	9/s/mL, max	<b>D 2452</b>
Shore A hardness	50, max	<b>C 661</b>
Bubbling	25 %, max	<b>C 712</b>
Adhesive and cohesive loss	9 cm <sup>2</sup> (1.5 in. <sup>2</sup> ), max per substrate	<b>C 1216</b>
Slump	0.38 cm (0.15 in.), max	<b>D 2202</b>
Stain index	3, max	<b>D 2203</b>
Tack-free time	72 h, max	<b>D 2377</b>
Accelerated weathering		<b>C 1257</b>
Edge cracking	3, max	
Center cracking	3, max	
Adhesion loss	3, max	
Color Change	as agreed	

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*