

Standard Specification for Concrete Grid Paving Units¹

This standard is issued under the fixed designation C 1319; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the requirements for concrete grid paving units for vehicular trafficways, parking areas, soil stabilization, and revetments. Maximum dimensions are 24 long by 24 in. wide (610 by 610 mm), with a minimum nominal thickness of $3\frac{1}{8}$ in. (80 mm).

NOTE 1—When particular features are desired, such as weight classification, higher compressive strength, surface texture, finish, color, or other special features, such properties should be specified separately by the purchaser. However, local sellers should be consulted as to availability of units having the desired features.

1.2 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

- 2.1 ASTM Standards: ²
- C 33 Specification for Concrete Aggregates
- C 140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units
- C 150 Specification for Portland Cement
- C 331 Specification for Lightweight Aggregates for Concrete Masonry Units
- C 595 Specification for Blended Hydraulic Cements
- C 618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C 989 Specification for Ground Granulated Blast-Furnace Slag for Use in Concrete and Mortars
- C 1157 Performance Specification for Hydraulic Cement

C 1209 Terminology of Concrete Masonry Units and Related Units

C 1232 Terminology of Masonry

3. Terminology

3.1 Terminology defined in Terminology C 1209 and Terminology C 1232 shall apply for this specification.

4. Materials

4.1 *Cementitious Materials*—Materials shall conform to the following applicable ASTM specifications:

4.1.1 Portland Cements—Specification C 150.

4.1.2 *Modified Portland Cement*—Portland cement conforming to Specification C 150, modified as follows:

4.1.2.1 Calcium carbonate, with a minimum 85 % $CaCO_3$ content, shall be permitted to be interground with the cement, provided the requirements of Specification C 150 as modified are met: limitation on insoluble residue is 1.5 % and limitation on loss on ignition is 7 %.

4.1.3 Blended Hydraulic Cements—Specification C 595.

4.1.4 Hydraulic Cement—Specification C 1157.

4.1.5 Pozzolans—Specification C 618.

4.1.6 Blast Furnace Slag Cements—Specification C 989.

4.2 *Aggregates*—Aggregates shall conform to one of the following ASTM specifications, except that grading requirements shall not necessarily apply:

4.2.1 Normal Weight—Specification C 33.

4.2.2 *Lightweight*—Specification C 331.

4.3 Other Constituents—Air-entraining agents, coloring pigments, integral water repellents, and finely ground silica, shall be previously established as suitable for use in concrete grid paving units and shall conform to applicable ASTM standards, or they shall be shown by test or experience satisfactory to the specifier and not to be detrimental to the durability of the concrete grid paving unit or any material customarily used in grid paving construction.

5. Physical Requirements

5.1 At the time of delivery to the work site, the units shall conform to the physical requirements prescribed in Table 1.

5.2 *Durability*—Durability shall be demonstrated by proven field performance satisfactory to the specifier that the grid paver units have adequate durability for the intended use.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.03 on Concrete Masonry Units and Related Units.

Current edition approved Dec. 1, 2006. Published December 2006. Originally approved in 1995. Last previous edition approved in 2001 as C 1319 – 01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

🕼 C 1319 – 01 (2006)

TABLE 1	Physical	Requirements
---------	----------	--------------

Compressive Strength Net Area, min. psi (MPa)		Water Absorption, max lb/ft ³ (kg/m ³)	Net Area, min.,%	Web Width	
				in. (mm)	in. (mm)
Avg. of 3	Individual	Avg. of 3 units		Min. ^A	Avg. ^B
5000 (35)	4500 (31)	10 (160)	50	1.00 (25)	1.25 (32)

^A Measured at the thinnest point.

^B Average of measurements along the height of the web.

5.2.1 *Proven Field Performance*—Satisfactory field performance is demonstrated when units similar in composition and made with the same manufacturing process as those to be supplied to the purchaser, maintain the physical requirements specified in Table 1 after three years of use. The units used as the basis for proven field performance shall have been exposed to the same general type of environment, temperature range, and traffic volume as is expected for the units supplied to the purchaser.

6. Permissible Variations in Dimensions

6.1 Length or width of units shall not differ by more than $\pm \frac{1}{8}$ in. (± 3.2 mm) from approved samples. Heights of units shall not differ by more than $\pm \frac{1}{8}$ in. (± 3.2 mm) from the specified standard dimensions. Tests shall be performed as required in 7.2.

7. Sampling and Testing

7.1 The purchaser or his authorized representative shall be accorded proper facilities to inspect and sample the units at the place of manufacture from lots ready for delivery.

7.2 Sample and test units in accordance with Test Methods C 140, except that the coupon method for determining compressive strength shall not be used.

8. Visual Inspection

8.1 Units shall be free of defects that interfere with the proper placing of the unit or impair the strength or permanence of the construction.

9. Compliance

9.1 If a sample fails to conform to the specified requirements, the manufacturer shall be permitted to remove units from the shipment. A new sample shall be selected by the purchaser from remaining units from the shipment with a similar configuration and dimension and tested at the expense of the manufacturer. If the second sample meets the specified requirements, the remaining portion of the shipment represented by the sample meets the specified requirements. If the second sample fails to meet the specified requirements, the remaining portion of the shipment represented by the sample meets the specified requirements, the remaining portion of the shipment represented by the sample fails to meet the specified requirements.

NOTE 2—Unless otherwise specified in the purchase order, the costs of tests is typically borne as follows: (I) if the results of the tests show that the units do not conform to the requirements of this specification the cost is typically borne by the seller; (2) if the results of the tests show that the units conform to the specification requirements, the cost is typically borne by the purchaser.

10. Keywords

10.1 concrete grid paving units; revetments; soil stabilization; vehicular trafficways

SUMMARY OF CHANGES

Committee C15 has identified the location of selected changes to this standard since C 1319–99 was published in the 2001 Annual Book of ASTM Standards, Vol 04.05.

(1) In Section 4 on Materials, Specification C 1157 was moved from Paragraph 4.1.3 to its own paragraph and identified as

hydraulic cement rather than blended cement.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).