



Standard Specification for Cellular Melamine Thermal and Sound-Absorbing Insulation¹

This standard is issued under the fixed designation C 1410; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the type, physical properties, and dimensions of open-cell melamine foam intended for use as thermal and sound-absorbing insulation for temperatures from -40 to $+350^{\circ}\text{F}$ (-40 to $+177^{\circ}\text{C}$) in industrial environments.

1.2 Some uses of thermal insulation materials covered by this specification are governed by building codes that address fire performance.

1.3 The use of an appropriate vapor retarder is required on cold surface applications where water vapor condense and cause a decrease in thermal performance. Refer to Practice C 755 for selection of vapor retarders. Facings shall be agreed upon between the purchaser and the manufacturer or supplier.

1.4 The values stated in inch-pounds are to be regarded as the standard. The SI units given in parentheses are provided for information only and are approximate.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- C 168 Terminology Relating to Thermal Insulating Materials
- C 177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- C 335 Test Method for Steady-State Heat Transfer Properties of Horizontal Pipe Insulation
- C 356 Test Method for Lineal Shrinkage of Preformed

High-Temperature Thermal Insulation Subjected to Soaking Heat

- C 390 Practice for Sampling and Acceptance of Preformed Thermal Insulation Lots
 - C 423 Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method
 - C 518 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
 - C 585 Practice for Inner and Outer Diameters of Rigid Thermal Insulation for Nominal Sizes of Pipe and Tubing (NPS Systems)
 - C 755 Practice for Selection of Vapor Retarders for Thermal Insulation
 - C 1045 Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions
 - C 1104/C 1104M Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation
 - C 1363 Test Method for the Thermal Performance of Building Assemblies by Means of a Hot Box Apparatus
 - D 2863 Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastic (Oxygen Index)
 - D 3574 Test Methods for Flexible Cellular Materials—Slab, Bonded, and Molded Urethane Foams
 - E 84 Test Method for Surface Burning Characteristics of Building Materials
 - E 176 Terminology of Fire Standards
 - E 662 Test Method for Specific Optical Density of Smoke Generated by Solid Materials
 - E 795 Practices for Mounting Test Specimens During Sound Absorption Tests
 - E 800 Guide for Measurement of Gases Present or Generated During Fires
 - E 2231 Practice for Specimen Preparation and Mounting of Pipe and Duct Insulation Materials to Assess Surface Burning Characteristics
- ### 2.2 Boeing Standards:
- Boeing Specification Support Standard 72396³

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.22 on Organic and Nonhomogeneous Inorganic Thermal Insulation.

Current edition approved May 1, 2005. Published May 2005. Originally approved in 1998. Last previous edition approved in 1998 as C 1014-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The Boeing Company, Boeing Technology Services, Seattle, WA.

TABLE 1 Common Dimensions

	Type I	Type II
Width, in. (mm)	12 to 50 (305 to 1270)	N/A
Length, in. (mm)	48 to 100 (1219 to 2540)	36 or 48 (914 or 1219)
Thickness, in. (mm)	¼ to 20 (6.4 to 508)	½ to 5 (12.7 to 127)

2.3 International Maritime Organization:

Resolution MSC.41(64) Interim Standard for Measuring Smoke and Toxic Products of Combustion Interim Standard for Measuring Smoke and Toxic Products of Combustion⁴

3. Terminology

3.1 *Definitions*—Terms used in this specification are defined in Terminology **C 168** and also in Terminology **E 176** as appropriate

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *melamine foam*—a low-density, semirigid, open-cell foam made from a melamine-formaldehyde or aldehyde polymer.

4. Classification

4.1 Melamine thermal insulation are furnished in the following types and grades:

4.1.1 Type I—Flat slab:

4.1.1.1 *Grade 1*—Regular (core foam with no facing).

4.1.1.2 *Grade 2*—Faced foam.

4.1.2 Type II—Pipe and tubing insulation:

4.1.2.1 *Grade 1*—Regular (core foam with no facing).

4.1.2.2 *Grade 2*—Faced foam.

4.1.3 Type III—Special shapes.

4.1.4 Special Facings.

5. Ordering Information

5.1 Purchase orders for melamine thermal insulation shall specify any or all of the following:

5.1.1 Title, number, and year of this specification.

5.1.2 Type and grade designation (see **4.1**).

5.1.3 Length, width and thickness required (see **Table 1**).

5.1.4 Tolerance, if other than specified (see **Table 2**).

5.1.5 Quantity of material.

5.1.6 Special packaging or marking, when required.

5.1.7 Special requirements for inspection and for testing.

5.1.8 Thermal conductivity at mean temperature of flat stock.

5.1.9 Manufacturers name, address, and telephone number.

5.1.10 Jacket facing type.

6. Materials and Manufacture

6.1 Typically a pentane blowing agent is used to foam a melamine-aldehyde precondensate. The result is an open-cell melamine foam.

⁴ International Maritime Organization, 4 Albert Embankment, London, United Kingdom.

TABLE 2 Insulation Tolerances

Type	Type I	Type II
Width, in. (mm)	±¼ (6.4)	N/A
Length, in. (mm)	±¼ (6.4)	±½ (3.2) –0
Thickness, in. (mm)	±⅛ (3.2) or 2 % whichever is smaller	±⅛ (3.2) –0 or 2 % whichever is smaller

6.2 Facing materials incorporated into the design of pipe insulation or flat slab shall be agreed upon between the purchaser and the manufacturer or seller. Typical materials are as follows:

6.2.1 *Aluminum Foil*—Aluminum foil laminated to a supporting membrane.

6.2.2 *Aluminized Mylar*—Aluminized mylar film laminated to a supporting membrane.

6.2.3 *Polyvinylchloride*—Polyvinylchloride either plain or reinforced with polyester.

6.2.4 *Polyvinylfluoride*—Polyvinylfluoride reinforced with fiberglass and rubber.

7. Physical Properties

7.1 Melamine thermal insulation shall conform to the physical requirements in **Table 3**, which shall constitute acceptance or rejection values for this specification when tested by test methods specified in Section **14**.

NOTE 1—Data in **Table 3** is for unfaced products; facings affect the properties listed.

NOTE 2—Melamine foams are hydrophilic and will absorb large quantities of water or moisture. Any system exposed to water, moisture, high humidity or that is used on cold installations must be protected by a vapor retarder or moisture retarder system.

7.2 The sound-absorption results for unfaced melamine foam shall conform to the performance requirements in **Table 4** of this specification.

7.3 Do not use values stated in **Tables 3 and 4** as design values. It is the buyer's responsibility to specify design requirements and obtain supporting documentation from the material supplier.

8. Inspection Requirements

8.1 The physical requirements for density and thermal conductivity at 75°F mean temperature (unless otherwise agreed upon between the purchaser and the supplier) as listed in **Table 3** are defined as inspection requirements (refer to Practice **C 390**).

8.2 All dimensional requirements, as described in **Tables 1 and 2**, are defined as inspection requirements.

8.3 All workmanship and appearance requirements, as described in Section **11**, are defined as inspection requirements.

9. Qualification Requirements

9.1 All physical requirements listed in **Tables 3 and 4** that are not considered inspection requirements are defined as qualification requirements (refer to Practice **C 390**).

9.2 For the purpose of initial material qualification, compliance with qualification requirements for each type of insulation shall be in accordance with Practice **C 390**.

TABLE 3 Physical Properties

Property	Requirement
Oxygen index, minimum % oxygen	33
Specific optical smoke density, max, Dm:	
Flaming mode	86
Non-flaming mode	40
Surface burning characteristics, max:	
Flame spread index smoke development at 1-in. thickness	25/50
Density, lb/ft ³ (kg/m ³)	0.70 ± 0.10 (11.2 ± 1.6)
Tensile strength, min, lb/in. ² (kPa)	14 (96.52)
Percent elongation, max	30
Indentation force deflection, min, lb 50 in. ² (kg/323 cm ²)	
Compression at 25 %	80 (36.3)
Compression at 65 %	160 (72.6)
Thermal conductivity, max, Btu in./h ft ² °F (W/mK)	
at -40°F mean	0.26 (0.038)
at 75°F mean	0.30 (0.044)
at 300°F mean	0.50 (0.073)
Water vapor sorption by weight, max, % (by volume, max, %)	25 (0.30)
High-temperature linear shrinkage at 350°F, max, %	5
Smoke toxicity, max ppm	
Carbon monoxide	3500
Hydrogen Chloride	500
Hydrogen fluoride	50
Nitrous Oxide	100
Sulfur Dioxide	100
Hydrogen cyanide	150

TABLE 4 Unfaced Sound-Absorption Coefficients Versus Frequency

Frequency, Hz	125	250	500	1000	2000	4000
Minimum coefficient at 2-in. (50-mm) thickness	0.15	0.32	0.77	0.95	0.94	0.92

9.3 Other properties, such as odor or corrosion, agreed upon between the purchaser and the manufacturer or supplier shall be considered to comply with this specification.

10. Dimensions and Permissible Variations

10.1 *Type I, Flat Sheet*—Sheets shall be rectangular sections and shall be true to form and dimensions, the corners square and the sides and edges parallel. Typical sizes are shown in **Table 1**. Other sizes as agreed upon between the purchaser and the manufacturer or supplier shall be considered to comply with this specification.

10.2 *Type II, Pipe and Tubing Insulation*—Pipe insulation shall be fabricated in sizes to conform to Practice **C 585** or as agreed upon between the manufacturer and the user.

10.3 *Type III, Special Shapes*—Dimensions of special shapes shall be as decided upon between the manufacturer and the user.

10.4 *Dimensional Tolerances*—The insulation shall not differ from the manufacturer’s standard dimensions by more than the tolerances listed in **Table 2**.

11. Workmanship and Appearance

11.1 Since several requirements for this material are not easily defined by a numerical value but affect the workmanship of the finished job, the insulation shall be free of visual defects that adversely affect the service quality. For example, blow-holes and tears when occurring to an excessive degree shall be judged to adversely affect the service quality of the material.

12. Sampling

12.1 Unless otherwise specified in the purchase order or contract, sampling shall be in accordance with Practice **C 390**.

13. Test Methods

13.1 *Apparent Thermal Conductivity*—Determine the thermal conductivity versus temperature relationship for the material using Test Methods **C 177, C 335, C 518** or **C 1363** as appropriate for the sample in conjunction with Practice **C 1045**. For data analysis. For most specimens, Test Methods **C 177** and **C 518**, are preferred. Test Method **C 177** Shall be used as the referee in case of disputes.

13.2 *Sound Absorption Coefficients*—Test in accordance with Test Method **C 423** using Type A mounting defined in Practices **E 795**. This specification addresses the foam alone; coatings and facings affect the properties listed.

13.3 *Oxygen Index*—Test in accordance with Test Method **D 2863**.

13.4 *Density*—Test in accordance with Test Methods **D 3574**, Test Method A.

13.5 *Tensile Strength*—Test in accordance with Test Methods **D 3574**, Test Method E.

13.6 *Compressibility*—Test in accordance with Test Methods **D 3574**, Test Method C.

13.7 *Elongation*—Test in accordance with Test Methods **D 3574**, Test Method E

13.8 *Surface Burning Characteristics:*

13.8.1 *For Grade 1 Materials*—Test 1-in. thick core foam sample in accordance with Test Method **E 84** and Practice **E 2231 mounting procedure**.

13.8.2 For thickness other than 1-in. the manufacture or the supplier shall test in the actual thickness used for surface burning characteristics and other fire properties. the thickness and the results shall be reported.

13.8.3 *For Grade 2 Materials*—Test 1-in. thick core foam and specified facer sample in accordance with Test Method **E 84** and Practice **E 2231 mounting procedure**. See **13.8.2**.

13.9 *Specific Optical Smoke Density:*

13.9.1 *For Grade 1 Materials*—Test 1-in. thick sample in accordance with Test Method **E 662**. See **13.8.2**.

13.9.2 *For Grade 2 Materials*—Test 1-in. thick core foam and specified facer sample in accordance with Test Method **E 662**. See **13.8.2**.

13.10 *High-Temperature Shrinkage*—Test in accordance with Test Method **C 356** at 350°F. Use the provisions for linear shrinkage-length only with a specimen size of 300 × 75mm (12 × 3in.)

13.11 *Indentation Force Deflection*—Test in accordance with Test Methods **D 3574**, Test Method B.

13.12 *Water Vapor Sorption*—Test in accordance with Test Method **C 1104**.

13.13 *Smoke Toxicity*—Test for gases listed in **Table 3** in accordance with the following methods: **Boeing Specification Support Standard 7239; with toxic gasses evaluated in accordance with IMO Resolution MCS.41(64)**.

13.13.1 *For Grade 1 Materials*—Test 1-in. thick core foam specimen. See **13.8.2**.

13.13.2 *For Grade 2 Materials*—Test 1—in. thick core foam and specified facer specimen. See 13.8.2.

14. Inspection

Unless otherwise specified in the purchase order or contract, Practice C 390 shall be used for the basis of inspection requirements and qualification requirements.

15. Rejection and Rehearing

15.1 Material that fails to conform to the requirements of this specification are subject to rejection. Rejection shall be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the tests, the producer or the supplier shall have the right to request a rehearing.

15.2 At the agreement of the buyer and the seller, the seller shall have the right to reinspect a rejected shipment and resubmit same after removal of the non-conforming portion.

16. Certification

16.1 Unless otherwise specified in the purchase order or contract, Practice C 390 shall be the basis for the certification. When specified in the purchase order or contract, a report of the test results shall be furnished.

17. Packaging and Package Marking

17.1 *Packaging*—Unless otherwise agreed upon and specified between the purchaser and the manufacturer or supplier, the insulation shall be packaged by the manufacturer's standard commercial practice.

17.2 *Marking*—Unless otherwise specified, each container shall be plainly marked with this specification number, type and grade (see 4.1), and the following:

17.2.1 *Sheet (Type I)*—The name of the manufacturer, address, telephone number, size, and quantity of the material in the container.

17.2.2 *Pipe and Tubing Insulation (Type II)*—The name of the manufacturer, address, telephone number, pipe size, quantity, and nominal thickness of the material in the container.

17.2.3 *Special Shapes (Type III)*—The name of the manufacturer, address, telephone number, shape, and quantity of the material in the container.

17.2.4 *Facing Materials*—The type of facing material and adhesive.

18. Keywords

18.1 acoustical insulation; formaldehyde and aldehyde; melamine; melamine formaldehyde; pipe insulation; thermal conductivity; thermal insulation

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).