



Standard Classification of Insulating Firebrick¹

This standard is issued under the fixed designation C 155; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This classification covers heat insulating material known as insulating firebrick. This material is suitable for lining certain kinds of industrial furnaces.

NOTE 1—Insulating materials for use below 1000°F (538°C) are covered² by ASTM Committee C-16 on Thermal Insulation.

2. Referenced Documents

2.1 *ASTM Standards:*²

C 134 Test Methods for Size, Dimensional Measurements, and Bulk Density of Refractory Brick and Insulating Firebrick

C 210 Test Method for Reheat Change of Insulating Firebrick

3. Significance and Use

3.1 This classification establishes an orderly grouping of insulating firebrick to provide group identifications for use by those producing or purchasing these materials. The group identification number is not meant to specifically designate the maximum service temperature although the number times 100 does approximate the temperature (in degrees Fahrenheit) to be used to check the reheat change and can be used as a guide for relative temperature stability. The bulk density limits the weight per unit volume for any group as sold, but is not meant to be used for detailed engineering calculations.

4. Basis of Classification

4.1 The classification of insulating firebrick in accordance with **Table 1** is based on bulk density (weight per cubic foot)

TABLE 1 Grouping of Insulating Firebrick

Group No.	Reheat Change, Not More Than 2 % When Tested at °F (°C)	Bulk Density Not Greater Than lb/ft ³ (g/cm ³)
16	1550 (845)	34 (0.54)
20	1950 (1065)	40 (0.64)
23	2250 (1230)	48 (0.77)
26	2550 (1400)	54 (0.86)
28	2750 (1510)	60 (0.96)
30	2950 (1620)	68 (1.09)
32	3150 (1730)	95 (1.52)
33	3250 (1790)	95 (1.52)

and the behavior in the reheat change test conducted at the specified temperature.

5. Test Methods

5.1 The properties enumerated in this classification shall be determined in accordance with the following ASTM test methods:

5.1.1 *Bulk Density*—Test Methods **C 134**.

5.1.2 *Reheat Change*—Test Method **C 210**. For the purpose of this classification, the percentage of reheat change shall be obtained from only the 9-in. (228-mm) dimension of the test brick.

6. Retests

6.1 Because of variables resulting from sampling and the lack of satisfactory reproducibility in tests conducted by different laboratories, the material may be resampled and retested when requested by either the manufacturer or the purchaser. This may apply in instances when the first test results do not conform to the requirements prescribed in this classification. The final results to be used shall be the average of at least two sets of results, each of which has been obtained by following in detail the specified testing procedures.

7. Keywords

7.1 bulk density; insulating firebrick; refractories; reheat change

¹ This classification is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.92 on The Joseph E. Kopanda Subcommittee for Editorial, Terminology and Classification.

Current edition approved March 1, 2007. Published April 2007. Originally approved in 1940. Last previous edition approved in 2002 as C 155 – 97 (2002).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



C 155 – 97 (2007)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).