



Standard Test Method for Determining the Potential Alkali-Silica Reactivity of Combinations of Cementitious Materials and Aggregate (Accelerated Mortar-Bar Method)¹

This standard is issued under the fixed designation C 1567; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method permits detection within 16 days of the potential for deleterious alkali-silica reaction of combinations of cementitious materials and aggregate in mortar bars. The cementitious materials are composed of various proportions of hydraulic cement, pozzolans and ground granulated blast-furnace slag.

1.2 The test results are only valid for the specific combinations of pozzolan, slag, and reactive aggregates tested.

1.3 This test is not suitable for evaluating the potential for deleterious reaction of combinations of hydraulic cement and aggregate (that is, in the absence of pozzolans or ground granulated blast-furnace slag).

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. A specific precautionary statement is given in the section on Reagents.*

2. Referenced Documents

2.1 ASTM Standards:²

C 109/C 109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

C 125 Terminology Relating to Concrete and Concrete Aggregates

C 127 Test Method for Density, Relative Density (Specific Gravity), and Absorption of Coarse Aggregate

C 128 Test Method for Density, Relative Density (Specific Gravity), and Absorption of Fine Aggregate

C 150 Specification for Portland Cement

C 151 Test Method for Autoclave Expansion of Hydraulic Cement

C 305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

C 490 Practice for Use of Apparatus for the Determination of Length Change of Hardened Cement Paste, Mortar, and Concrete

C 494/C 494M Specification for Chemical Admixtures for Concrete

C 511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes

C 618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete

C 670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

C 989 Specification for Ground Granulated Blast-Furnace Slag for Use in Concrete and Mortars

C 1240 Specification for Silica Fume Used in Cementitious Mixtures

C 1260 Test Method for Potential Alkali Reactivity of Aggregates (Mortar-Bar Method)

C 1293 Test Method for Determination of Length Change of Concrete Due to Alkali-Silica Reaction

C 1437 Test Method for Flow of Hydraulic Cement Mortar

D 1193 Specification for Reagent Water

E 11 Specification for Wire Cloth and Sieves for Testing Purposes

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms relating to concrete or aggregates, see Terminology **C 125**.

3.2 *relative density (OD)*, *n*—as defined in Test Methods **C 127** or **C 128**, for coarse and fine aggregates, respectively.

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.26 on Chemical Reactions.

Current edition approved Dec. 1, 2008. Published January 2009. Originally approved in 2004. Last previous edition approved in 2007 as C 1567 – 07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

4. Significance and Use

4.1 This test method provides a means for evaluating the ability of pozzolans and ground granulated blast-furnace slag to control deleterious internal expansion due to alkali-silica reaction when used with an aggregate intended for use in concrete. It is based on the Accelerated Test Method developed at the National Building Research Institute (NBRI) in the Republic of South Africa (1-4).³

4.2 Results obtained using this test method may overestimate the reactivity of some types of aggregates if used in service with the same pozzolans or slag and hydraulic cement of low alkali content.

4.3 Different levels of pozzolan and ground granulated blast-furnace slag may require testing to determine the amount required to reduce expansion to an acceptable level. Pozzolans and ground granulated blast-furnace slag may be tested separately or in combination.

4.4 It is recommended to test the same aggregate and hydraulic cement (without pozzolans and slag) using Test Method C 1260.

4.5 This test method may underestimate the expansion of cementitious systems containing pozzolans with an alkali content > 4.0 % sodium oxide equivalent (7-9). It is recommended that such materials be tested using Test Method C 1293.

5. Apparatus

5.1 The apparatus shall conform to Practice C 490, except as follows:

5.2 *Sieves*—Square hole, woven-wire cloth sieves, shall conform to Specification E 11.

5.3 *Mixer, Paddle, and Mixing Bowl*—Mixer, paddle, and mixing bowl shall conform to the requirements of Practice C 305, except that the clearance between the lower end of the paddle and the bottom of the bowl shall be 5.1 ± 0.3 mm.

5.4 *Tamper and Trowel*—The tamper and trowel shall conform to Test Method C 109/C 109M.

5.5 *Containers*—The containers shall be of such a nature that the bars can be totally immersed in either the water or 1N sodium hydroxide (NaOH) solution. The containers shall be made of material that can withstand prolonged exposure to 80 °C and must be resistant to a 1N NaOH solution (see Note 1). The containers must be so constructed that when used for storing specimens, the loss or gain of moisture is prevented by tight-fitting covers, by sealing, or both (see Note 2). The bars in the solution must be placed and supported so that the solution has access to the entire surface of each bar; therefore, ensure that the specimens do not touch the sides of the container or each other. The specimens, if stood upright in the solution, shall not be supported by the metal gage stud.

NOTE 1—The NaOH solution corrodes glass or metal containers.

NOTE 2—Some microwave-proof food storage containers made of polypropylene or high-density polyethylene have been found to be acceptable.

³ The boldface numbers in parentheses refer to a list of references at the end of the text.

5.6 *Oven, or Water Bath*—A convection oven or water bath with temperature control maintaining 80.0 ± 2.0 °C.

6. Reagents

6.1 *Sodium Hydroxide (NaOH)*—USP or technical grade may be used, provided the Na^+ and OH^- concentrations are shown by chemical analysis to lie between 0.99N and 1.01N.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type IV of Specification D 1193.

6.3 *Sodium Hydroxide Solution*—Each litre of solution shall contain 40.0 g of NaOH dissolved in 900 mL of water, and shall be diluted with additional distilled or deionized water to obtain 1.0 L of solution. The volume proportion of sodium hydroxide solution to mortar bars in a storage container shall be 4 ± 0.5 volumes of solution to 1 volume of mortar bars. The volume of a mortar bar may be taken as 184 mL. Include sufficient test solution to ensure complete immersion of the mortar bars.

6.3.1 *Warning*—Before using NaOH, review: (1) the safety precautions for using NaOH; (2) first aid for burns; and (3) the emergency response to spills, as described in the manufacturer's Material Safety Data Sheet or other reliable safety literature. NaOH can cause very severe burns and injury to unprotected skin and eyes. Suitable personal protective equipment must always be used. These include full-face shields, rubber aprons, and gloves impervious to NaOH. Gloves must be checked periodically for pinholes.

7. Conditioning

7.1 Maintain the temperature of the molding room and dry materials at not less than 20 °C and not more than 27.5 °C. The temperature of the mixing water, and of the moist closet or moist room, shall not vary from 23 °C by more than 2 °C.

7.2 Maintain the relative humidity of the molding room at not less than 50 %. The moist closet or room shall conform to Specification C 511.

7.3 Maintain the storage oven or water bath in which the specimens are stored at a temperature of 80.0 ± 2.0 °C.

8. Sampling and Preparation of Test Specimens

8.1 *Selection of Aggregate*—Process materials proposed for use as fine aggregate in concrete as described in 8.2 with a minimum of crushing. Process materials proposed for use as coarse aggregate in concrete by crushing to produce as nearly as practical a graded product from which a sample can be obtained. Grade the sample as prescribed in Table 1. The sample shall represent the composition of the coarse aggregate as proposed for use.

TABLE 1 Grading Requirements

Sieve Size		Mass, %
Passing	Retained on	
4.75 mm (No. 4)	2.36 mm (No. 8)	10
2.36 mm (No. 8)	1.18 mm (No. 16)	25
1.18 mm (No. 16)	600 μm (No. 30)	25
600 μm (No. 30)	300 μm (No. 50)	25
300 μm (No. 50)	150 μm (No. 100)	15

8.1.1 When a given quarried material is proposed for use both as coarse and as fine aggregate, test only a selection of the fine aggregate, unless there is reason to expect that the coarse aggregate has a different composition than the fine aggregate. If such a difference is expected and if the differences might significantly affect expansion due to reaction with the alkalis in cement or from the environment of service, test the coarse aggregate in a manner similar to that employed in testing the fine aggregate.

8.2 *Preparation of Aggregate*—Grade aggregates to provide a sample meeting the requirements given in **Table 1**. Crush aggregates in which sufficient quantities of the sizes specified in **Table 1** do not exist until the required material has been produced. In the case of aggregates containing insufficient amounts of one or more of the larger sizes listed in **Table 1**, and if no larger material is available for crushing, the first size in which sufficient material is available shall contain the cumulative percentage of material down to that size as determined from the grading specified in **Table 1**. When such procedures are required, make a special note thereof in the test report. After the aggregate has been separated into the various sieve sizes, wash each size with a water spray over the sieve to remove adhering dust and fine particles from the aggregate. Dry the portions retained on the various sieves and, unless used immediately, store each such portion individually in a clean container provided with a tight-fitting cover.

8.3 *Selection and Preparation of Cement:*

8.3.1 *Hydraulic Cement*—Use a hydraulic cement meeting the requirements of Specification **C 150 (Note 3)**. In addition, the autoclave expansion in Test Method **C 151** shall be less than 0.20 %.

NOTE 3—The alkali content of the cement has been found to have negligible (3) or minor (6) effects on expansion in this test.

8.3.2 *Preparation of Cement*—Pass cement for use in this test through an 850-μm (No. 20) sieve to remove lumps before use.

8.4 *Selection of pozzolan or ground granulated blast-furnace slag*—Use one, or a combination, of the following:

8.4.1 Fly ash or natural pozzolan meeting the requirements of Specification **C 618**.

8.4.2 Silica fume meeting the requirements of Specification **C 1240**.

8.4.3 Ground granulated blast furnace slag meeting the requirements of Specification **C 989**.

8.5 *Preparation of Test Specimens:*

8.5.1 *Number of Specimens*—Make at least three test specimens for each cementitious materials-aggregate combination.

8.5.2 *Preparation of Molds*—Prepare the specimen molds in accordance with the requirements of Practice **C 490** except, the interior surfaces of the molds shall be covered with a release agent (see **Note 4**). A release agent is acceptable if it serves as a parting agent without affecting the time of setting of the cement and without leaving any residue that will inhibit the penetration of water into the specimen.

NOTE 4—TFE-fluorocarbon tape complies with the requirements for a mold release agent.

8.5.3 *Proportioning of Mortar*—Proportion the dry materials for the test mortar using 1 part of cementitious materials (hydraulic cement plus pozzolan or ground granulated blast-furnace slag) to 2.25 parts of graded aggregate by mass for aggregates with a relative density (OD) at or above 2.45. For aggregates with a relative density (OD) below 2.45, determine the aggregate proportion as follows:

$$\text{Aggregate Proportion} = 2.25 \times \frac{D}{2.65}$$

where:

D = relative density (OD) of test aggregate.

8.5.3.1 For aggregates with a relative density (OD) equal to or greater than 2.45, the quantities of dry materials to be mixed at one time in the batch of mortar for making three specimens shall be 440 g of cementitious material and 990 g of aggregate made up by recombining the portions retained on the various sieves in the grading prescribed in **Table 1**. Use a water-cement ratio equal to 0.47 by mass (see **Note 5**).

8.5.3.2 For aggregates with a relative density (OD) less than 2.45, the quantities of dry materials to be mixed at one time in the batch of mortar for making three specimens shall be 440 g of cementitious material and mass of aggregate shall be 440 g multiplied by the aggregate proportion determined in **8.5.3**. This aggregate mass shall be made up by recombining the portions retained on the various sieves in the grading prescribed in **Table 1**. Use a water-cementitious material ratio equal to 0.47 by mass (see **Note 5**).

NOTE 5—Ruggedness tests indicated that mortar bar expansions were less variable at a fixed water-cement ratio than when gauged to a constant flow (3).

8.5.3.3 If silica fume or metakaolin are used, a high range water reducer (HRWR), meeting the requirements of Specification **C 494/C 494M** Type F, shall be used (if necessary) to provide adequate dispersion and workability of the mixture. The water-cementitious material ratio shall remain 0.47 by mass and the amount of HRWR shall be that to obtain a flow of ± 7.5 percentage points of a control mortar without silica fume or metakaolin as determined in accordance with Test Method **C 1437** using 10 drops of the flow table. If liquid HRWR is used, the water present in the liquid must be included in the calculation of the water-cementitious material ratio.

8.5.4 *Mixing of Mortar*—Mix the mortar in accordance with the requirements of Practice **C 305**.

8.5.5 *Molding of Test Specimens*—Mold test specimens within a total elapsed time of not more than 2 min and 15 s after completion of the original mixing of the mortar batch. Fill the molds with two approximately equal layers, each layer being compacted with the tamper. Work the mortar into the corners, around the gage studs, and along the surfaces of the mold with the tamper until a homogeneous specimen is obtained. After the top layer has been compacted, cut off the mortar flush with the top of the mold and smooth the surface with a few strokes of the trowel.

9. Procedure

9.1 *Initial Storage and Reading*—Place each mold in the moist cabinet or room immediately after molds have been

filled. The specimens shall remain in the molds for 24 ± 2 h. Remove the specimens from the molds and, while they are being protected from loss of moisture, properly identify and make an initial comparator reading. Make and record the initial and all subsequent readings to the nearest 0.002 mm. Place the specimens made with each aggregate sample in a storage container with sufficient tap water to totally immerse them. Seal and place the containers in an oven or water bath at 80.0 ± 2.0 °C for a period of $24 \text{ h} \pm 2 \text{ h}$.

9.2 Zero Readings—Remove the containers from the oven or water bath one at a time. Remove other containers only after the bars in the first container have been measured and returned to the oven or water bath. The time elapsed between removal and return of the specimens to the oven or water bath shall not exceed 10 min. Remove the bars one at a time from the water and dry their surface with a towel paying particular attention to the two metal gage studs. Take the zero reading (see **Note 6**) of each bar immediately after drying, and read as soon as the bar is in position. Complete the process of drying and reading within 15 ± 5 s of removing the specimen from the water. After taking comparator readings, leave the specimen on a towel until comparator readings have been taken on the remainder of the bars. Place all specimens made with each unique cementitious materials-aggregate combination in a separate container with sufficient 1N NaOH, at 80.0 ± 2.0 °C for the specimens to be totally immersed. Seal the container and return it to the oven or water bath.

NOTE 6—The reference bar should be read prior to each set of specimens since the heat from the mortar bars may cause the length of the comparator to change.

9.3 Subsequent Storage and Measurement—Make subsequent comparator readings of the specimens periodically, with at least three intermediate readings, for 14 days after the zero reading, at approximately the same time each day. If readings are continued beyond the 14-day period, take at least one reading per week. The procedure is identical to that described in the **9.2**, except that the specimens are returned to their own container after measurement.

10. Calculation

10.1 Calculate the difference between the zero comparator reading of the specimen and the reading at each period to the nearest 0.001 % of the effective gage length and record as the expansion of the specimen for that period. Report the average expansion of the three specimens of a given cementitious materials-aggregate combination to the nearest 0.01 % as the expansion for the combination for a given period.

11. Report

11.1 Report the following information:

11.1.1 Type and source of aggregate,

11.1.2 Type and source of hydraulic cement,

11.1.3 Type, source, and proportions of pozzolan

11.1.4 Grade, source, and proportions of ground granulated blast-furnace slag

11.1.5 Autoclave expansion and alkali content of cement as percent potassium oxide (K_2O), sodium oxide (Na_2O), and calculated sodium oxide (Na_2O) equivalent ($\text{Na}_2\text{O}_{\text{eq}} = \% \text{Na}_2\text{O} + 0.658 \times \% \text{K}_2\text{O}$),

11.1.6 Average length change in percent at each reading of the specimens,

11.1.7 Any relevant information concerning the preparation of aggregates, including the grading of the aggregate when it differs from that given in **8.2**,

11.1.8 Any significant features revealed by examination of the specimens during and after test,

11.1.9 Amount of mixing water expressed as a mass fraction of the total cementitious material,

11.1.10 A graph of the length change data from the time of the zero reading to the end of the 16 day period.

12. Precision and Bias

12.1 The following precision statements are taken from Test Method **C 1260**, and are based on tests without pozzolans or ground slag.

12.2 Within-Laboratory Precision—It has been found that the average within-laboratory coefficient of variation for materials with an average expansion greater than 0.1 % at 14 days is 2.94 % (**5**) (**Note 7**). Therefore, the results of two properly conducted tests within the same laboratory on specimens of a sample of aggregate should not differ by more than 8.3 % (**Note 7**) of the mean expansion.

12.3 Multi-Laboratory Precision—It has been found that the average multilaboratory coefficient of variation for materials with an average expansion greater than 0.1 % at 14 days is 15.2 % (**5**) (**Note 7**). Therefore, the results of two properly conducted tests in different laboratories on specimens of a sample of aggregate should not differ by more than 43 % (**Note 7**) of the mean expansion.

NOTE 7—These numbers represent, respectively, the (1s %) and (d2s %) limits as described in Practice **C 670**.

12.4 Bias—Since there is no accepted reference material for determining the bias of this test method, no statement on bias is being developed.

13. Keywords

13.1 aggregate; alkali-silica reactivity; length change; mortar; pozzolans, slag, sodium hydroxide

APPENDIX

(Nonmandatory Information)

X1. INTERPRETATION OF TEST RESULTS

X1.1 There is good agreement in the published literature (2, 10-12) for the following expansion limits:

X1.1.1 Combinations of cement, pozzolan, or ground granulated blast-furnace slag, and aggregate that expand less than 0.10 % at 16 days after casting are likely to produce acceptable expansions when tested in concrete (that is, Test Method C 1293) and to have a low risk of deleterious expansion when used in concrete under field conditions.

X1.1.2 Combinations of cement, pozzolan, or ground granulated blast-furnace slag, and aggregate that expand more

than 0.10 % at 16 days after casting are indicative of potentially deleterious expansion. However, the potential for deleterious reaction should be confirmed by testing the same combination of materials in concrete (that is, Test Method C 1293). The expansion may be reduced by retesting the material combination using the pozzolan or ground granulated blast-furnace slag at a higher replacement level.

REFERENCES

- (1) Oberholster, R. E., and Davies, G., "An Accelerated Method for Testing the Potential Alkali Reactivity of Siliceous Aggregates." *Cement and Concrete Research*, Vol 16, 1986, pp. 181-189.
- (2) Davies, G., and Oberholster, R. E., "Use of the NBRI Accelerated Test to Evaluate the Effectiveness of Mineral Admixtures in Preventing the Alkali-Silica Reaction," *Cement and Concrete Research*, Vol 17, 1987, pp. 97-107.
- (3) Davies, G., and Oberholster, R. E., "An Interlaboratory Test Programme on the NBRI Accelerated Test to Determine the Alkali-Reactivity of Aggregates," National Building Research Institute, CSIRO, Special Report BOU 92-1987, Pretoria, RSA, 1987, 16 pp.
- (4) Oberholster, R. E., "Alkali Reactivity of Siliceous Rock Aggregates: Diagnosis of the Reaction, Testing of Cement and Aggregate and Prescription of Preventative Measures," *Alkali in Concrete, Research and Practice*, Copenhagen, 1983, Danish Concrete Association, pp. 419-433.
- (5) Rogers, C.A., "Multi-laboratory Study of the Accelerated Mortar Bar Test (ASTM Test Method C 1260) for Alkali-Silica Reaction," *Cement, Concrete, and Aggregates*, Vol 21, 1999, pp. 185-194.
- (6) Hooton, R. D., "Interlaboratory Study of the NBRI Rapid Test Method and CSA Standardization Status," *Report EM-92*, Ontario Ministry of Transport, March 1990, pp. 225-240.
- (7) Shehata, M.H. and Thomas, M.D.A. "The Effects of Fly Ash Composition on the Expansion of Concrete Due to Alkali-Silica Reaction." *Cement and Concrete Research*, Vol. 30, July 2000, pp. 1063-1072.
- (8) Mehland, I. and Dahl, P.A. "Recycling glass cullet as concrete aggregates: applicability and durability." *Proceedings of the International Symposium: Recycling and Reuse of Glass Cullet*, (Ed. R. Dhir et al), Dundee, Scotland, 2001, pp. 167-177.
- (9) Baxter, S. "Recycled glass in concrete: the good news and the bad news." *Beneficial Use of Recycled Materials in Transportation Applications*, (Ed. T. Eighmy), Virginia, 2001, pp. 747-756.
- (10) Berra, M., Mangialardi, T. and Paolini, A. E. "Application of the NaOH bath test method for assessing the effectiveness of mineral admixtures against reaction of alkali with artificial siliceous aggregate." *Cement & Concrete Composites*, Vol. 16, 1994, pp. 207-218.
- (11) Bérubé, M.-A., Duchesne, J., and Chouinard, D. "Why the accelerated mortar bar method ASTM C 1260 is reliable for evaluating the effectiveness of supplementary cementing materials in suppressing expansion due to alkali-silica reactivity." *Cement, Concrete, and Aggregates*, Vol. 17, No. 1, 1995, pp. 26 - 34.
- (12) Thomas, M.D.A. and Innis, F.A. "Use of the accelerated mortar bar test for evaluating the efficacy of mineral admixtures for controlling expansion due to alkali-silica reaction." *Cement, Concrete, and Aggregates*, Vol. 21 (2), 1999, pp. 157-164.

SUMMARY OF CHANGES

Committee C09 has identified the location of selected changes to this test method since the last issue, C 1567 – 07, that may impact the use of this test method. (Approved December 1, 2008)

(1) Revised 8.5.3.3.

Committee C09 has identified the location of selected changes to this test method since the last issue, C 1567 – 04, that may impact the use of this test method. (Approved July 15, 2007)

(1) Revised 9.2.

(2) Revised Section 3.

(3) Revised 8.5.3, added new 8.5.3.1 and 8.5.3.2, and moved some of the text from 8.5.3 into new 8.5.3.3.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).