



# Standard Specification for Elastomeric Seals for Joining Concrete Structures<sup>1</sup>

This standard is issued under the fixed designation C 1619; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers the physical property requirements of elastomeric seals (gaskets) used to seal the joints of precast concrete structures conforming to Specifications **C 14**, **C 14M**, **C 118**, **C 118M**, **C 361**, **C 361M**, **C 443**, **C 443M**, **C 505**, or **C 505M** used in gravity and low head pressure applications.

1.2 Requirements are given for natural or synthetic rubber gaskets, or a combination of both.

1.3 Values stated in imperial units are to be regarded as the standard.

1.4 The following precautionary caveat pertains only to the test method portion, Section 8, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- C 14** Specification for Concrete Sewer, Storm Drain, and Culvert Pipe
- C 14M** Specification for Concrete Sewer, Storm Drain, and Culvert Pipe [Metric]
- C 118** Specification for Concrete Pipe for Irrigation or Drainage
- C 118M** Specification for Concrete Pipe for Irrigation or Drainage [Metric]
- C 361** Specification for Reinforced Concrete Low-Head Pressure Pipe
- C 361M** Specification for Reinforced Concrete Low-Head Pressure Pipe [Metric]
- C 443** Specification for Joints for Concrete Pipe and Manholes, Using Rubber Gaskets

- C 443M** Specification for Joints for Concrete Pipe and Manholes, Using Rubber Gaskets [Metric]
- C 497** Test Method for Concrete Pipe, Manhole Sections, or Tile
- C 497M** Test Method for Concrete Pipe, Manhole Sections, or Tile [Metric]
- C 505** Specification for Nonreinforced Concrete Irrigation Pipe with Rubber Gasket Joints
- C 505M** Specification for Nonreinforced Concrete Irrigation Pipe with Rubber Gasket Joints [Metric]
- C 822** Terminology Relating to Concrete Pipe and Related Products
- D 395** Test Methods for Rubber Property—Compression Set
- D 412** Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension
- D 471** Test Method for Rubber Property—Effect of Liquids
- D 573** Test Method for Rubber—Deterioration in an Air Oven
- D 1149** Test Method for Rubber Deterioration—Surface ozone cracking in a Chamber
- D 1566** Terminology Relating to Rubber
- D 2240** Test Method for Rubber Property—Durometer Hardness
- D 2527** Specification for Rubber Seals—Splice Strength

## 3. Terminology

3.1 *Definitions*—For definitions of terms relating to concrete pipe, see Terminology **C 822**. For definitions relating to rubber or elastomers, see Terminology **D 1566**.

## 4. Classification

4.1 In order to provide for the various types of seals and requirements, multiple classifications have been established.

4.1.1 Class A is generally intended to cover seals in low head pressure piping applications not exceeding 125 ft (375 kPa) where premium physical properties are required.

4.1.2 Class B is generally intended for Class A and Class E applications that also require special oil resistant performance.

4.1.3 Class C is generally intended to cover seals in applications not exceeding 30 ft (9.14 m) of hydrostatic head.

4.1.4 Class D is generally intended for Class C applications that also require special oil resistant performance.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.08 on Joints for Precast Concrete Structures.

Current edition approved May 15, 2005. Published June 2005.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Physical Property Requirements for Elastomeric Seals**

	Class A	Class B	Class C	Class D	Class E
Tensile, min, psi (MPa)	2300 (15.9)	1500 (10.3)	1200 (8-3)	1200 (8.3)	1800 (12.4)
Elongation at break, min, %	425	350	350	350	425
Specified Hardness, Shore A	40-60	40-60	40-60	40-60	40-60
Oven-Age Tensile reduction, max % of original	15	20	15	20	15
Oven-Age Elongation reduction, max % of original	20	40	20	40	20
Oven-Age hardness increase, max	—	15	—	15	—
Compression Set, max %	20	20	25	25	20
Water Absorption, max % weight increase	5	15	10	15	5
Ozone Resistance level, 50 pphm	No cracks	No cracks	No cracks	No cracks	No cracks
Liquid Immersion IRM 903 Oil. Max % volume change	—	80	—	80	—
Splice Strength Classification	Class 3	Class 2	Class 3	Class 2	Class 3

4.1.5 Class E is generally intended for gravity flow sewer pipe in applications not exceeding 30 ft (9.14 m) of hydrostatic head.

## 5. Composition and Manufacture

5.1 All gaskets shall be extruded or molded in such a manner that any cross-section will be dense, homogeneous, and free of porosity, blisters, pitting, or other imperfections. The gaskets shall be fabricated from an elastomeric material meeting the appropriate classification physical property requirements in Section 7. The base polymer shall be natural rubber, synthetic rubber, or a blend of both that is acceptable to the owner.

## 6. Dimensions and Tolerances

6.1 Specified Durometer Shore A hardness shall be within the range given in Section 7, Table 1, and actual gasket durometer shall conform to  $\pm 5$  points from the specified value.

6.2 Cross-sectional and circumferential dimensions and tolerances shall comply with the relevant standard specification that is referencing this standard.

6.3 When in its assembled position, the gasket shall not be stretched more than 30 % of its original circumference.

## 7. Physical Requirements

7.1 The sealing portion of the gaskets shall comply with the physical requirements listed in Table 1 when testing in accordance with Section 8.

7.2 Gasket swell has a bearing on joint performance. It is the responsibility of the manufacturer to set appropriate limits for swell and durometer change of the gasket material and “wash off” for the gasket lubricant. These limits shall then be verified by test methods described in Test Method C 497. Gasket lubricant shall not be altered, corrupted, or diluted from its original formulation as tested and certified prior to its use on the gasket for installation purposes.

7.3 Class B and Class D oil resistant gaskets shall contain not less than 50 % by volume, oil resistant polymer.

## 8. Test Methods

8.1 Laboratory tests to determine the physical properties of the gasket to be furnished under this specification shall be performed on the finished product as supplied or from test specimens taken from the finished product unless otherwise stated within this specification.

8.1.1 *Tensile Strength and Elongation*—See Test Methods D 412.

8.1.2 *Hardness*—See Test Method D 2240, with the exception of Section 5. The determination shall be taken directly on the gasket. The presser foot shall be applied on areas that are ¼ in. (6.4 mm) or greater in thickness. If ¼ in. (6.4 mm) or greater thickness is not available, thinner samples shall be plied up to obtain this thickness.

8.1.3 *Compression Set*—See Test Methods D 395 Method B. Test conditions to be 22 h at 70°C. Specimen shall not be prepared from laboratory cured slabs or by direct molding. Because testing is required on the finished product, specimens shall not be prohibited from deviating from the standard dimensions as per Test Methods D 395 section 5.6.

8.1.4 *Accelerated Aging*—See Test Method D 573. Test conditions to be 96 h at 70°C.

8.1.5 *Water Absorption*—See Test Method D 471. Use distilled water for the standard liquid test. When a 1 in. wide test sample cannot be obtained, use the greatest width obtainable. Test conditions shall be 48 h at 70°C. At test completion, immediately remove from water, blot the specimen dry, and determine specimen weight. Calculate the volume increase.

8.1.6 *Ozone Resistance*—Determine the resistance to ozone in accordance with Test Method D 1149.

8.1.6.1 Test specimens shall be constructed from a finished gasket cross-section and of type A.

8.1.6.2 Conduct test for 72 h in 50 PPHM concentration at 40°C (104  $\pm$  4°F) stressed at 20 % extension.

8.1.7 *Oil Immersion Testing*—See Test Method D 471. Determine resistance to oil by calculating % volume change after immersing product specimen in ASTM IRM 903 oil for 70 h at 100°C.

8.1.8 *Splice Strength Classification*—See Specification D 2527. No specimen for destructive test or no seal for nondestructive test shall show sign of damage at the splice.

## 9. Test Frequency

9.1 When specified in Table 1, verification of the physical properties for tensile, elongation, hardness, oven aging, and compression set shall be performed on the finished product for each run startup and at a minimum of every 20 000 lb (9072 kg) of rubber processed after a run setup. A run startup shall be defined as the beginning of the production run of a particular cross-section of gasket and/or after significantly changing the processing equipment set up parameters to recover from a substantial event.

9.2 When specified in **Table 1**, verification of the physical properties for water absorption, ozone resistance, and oil immersion shall be verified on an annual basis on a finished product sample of the elastomeric formulation of the gasket.

9.3 Formulation content of base polymer, polymer blends, or other materials shall be verified during the formulation development.

## 10. Certification

10.1 At the option of the purchaser, certified copies of test reports on the elastomer from which the shipment of gaskets was made shall be furnished by the gasket supplier.

## 11. Storage

11.1 The rubber gaskets shall be stored in a cool, clean, and shaded environment. The preferred temperature is 70°F (21°C) or lower.

## 12. Marking

12.1 The markings shall include at a minimum the gasket manufacturer's name or symbol, nominal pipe size, ASTM designation, classification, gasket cross-section (if other than circular), cut length or volume, and month and year of manufacture.

12.2 Additional markings and color designations shall be agreed upon by the pipe manufacturer and the gasket manufacturer.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*