



# Standard Specification for Mineral Fiber Thermal Insulating Cement<sup>1</sup>

This standard is issued under the fixed designation C 195; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification covers mineral fiber thermal insulating materials in the form of dry cement, which, when mixed with a suitable proportion of water, applied as a plastic mass, and dried in place, affords resistance to heat transmission on surfaces operating at temperatures between 250 and 1900°F (about 121 and 1038°C).

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following safety hazards caveat pertains only to the test methods section of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- C 136 Test Method for Sieve Analysis of Fine and Coarse Aggregates
- C 163 Practice for Mixing Thermal Insulating Cement Samples
- C 166 Test Method for Covering Capacity and Volume Change Upon Drying of Thermal Insulating Cement
- C 168 Terminology Relating to Thermal Insulation
- C 177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.20 on Homogeneous Inorganic Thermal Insulations.

Current edition approved Nov. 15, 2007. Published December 2007. Originally published as ES 10, 1942. Last previous edition approved in 2000 as C 195 – 00.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C 356 Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat

C 390 Practice for Sampling and Acceptance of Thermal Insulation Lots

C 411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation

C 518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus

C 1045 Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions

C 1058 Practice for Selecting Temperatures for Evaluating and Reporting Thermal Properties of Thermal Insulation

C 1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus

E 136 Test Method for Behavior of Materials in a Vertical Tube Furnace at 750°C

## 3. Terminology

3.1 *Definitions*—Terminology C 168 shall be considered as applying to the terms used in this specification.

## 4. Materials and Manufacture

4.1 Mineral fiber thermal insulating cement shall be composed of mineral fiber and inorganic fillers, with a suitable proportion of heat-resistant binder.

4.2 The mineral fiber shall consist of rock, slag, or glass processed from a molten state into fibrous form.

4.3 Asbestos shall not be used as an ingredient or component part of the product.

## 5. Other Requirements

5.1 The cement shall conform to the requirements given in Table 1. Conformance shall be based on results of tests on specimens prepared in accordance with 9.1.

5.2 *Maximum Use Temperature*—When tested in accordance with 10.5, the dried cement shall not warp, flame, or glow during hot surface exposure. No evidence of melting or fiber degradation shall be evident upon post-test inspection.

**TABLE 1 Physical Requirements**

Dry covering capacity, min, ft <sup>2</sup> , 1 in. in thickness per 100 lb of dry cement (m <sup>2</sup> , 1 cm in thickness per 100 kg of dry cement)	30 (15.6)
Volume change (shrinkage) upon drying, max, %	35 (35)
Linear shrinkage (length) after heat soaking at 1600°F (871°C) max, %	5 (5)
Apparent thermal conductivity, max, Btu-in./h-ft <sup>2</sup> -°F (W/m-K): <sup>A</sup>	
At mean temperature of 200°F (93°C)	0.70 (0.101)
At mean temperature of 500°F (260°C)	0.85 (0.123)
At mean temperature of 700°F (371°C)	0.95 (0.137)
At mean temperature of 900°F (482°C)	1.2 (0.173)

<sup>A</sup> The user is advised that some applications could require the knowledge of the thermal conductivity of the insulating cement at mean temperatures above those shown. Consult the manufacturer for data at mean temperatures exceeding those listed.

5.3 *Non-combustibility*—When tested in accordance with 10.6, the dried cement shall conform to the requirements of Test Method E 136.

## 6. Qualification Requirements

6.1 The following requirements are employed for purposes of initial material or product qualification:

- 6.1.1 Linear shrinkage, and
- 6.1.2 Dry adhesion to steel.

## 7. Sampling

7.1 The cement shall be sampled, for the purpose of tests, using one of the following procedures. Unless otherwise specified or agreed upon between the purchaser and the manufacturer or supplier, the cement shall be sampled using the manufacturer's standard procedure.

7.1.1 Use Criteria C 390. Each bag shall represent a unit.

7.1.1.1 In a single sampling plan by attributes the acceptability of a lot will be determined by the number of units of product in the sample that do not conform to the specifications. The acceptable quality level (AQL) and limiting quality level (LQL) of an acceptance sampling plan, expressed as percentages of the units nonconforming, are characteristics of the sampling plan and are not to be viewed as product specifications.

7.1.2 Use the average of the test data from the number of test specimens required by the appropriate test method to represent the average for the entire lot.

7.2 The specimen for test is to be taken from the middle of a bag, so as to be representative of material from the entire bag.

## 8. Number of Tests and Retests

8.1 If the average of the test data obtained using 7.1.2 fails to conform to the requirements of this specification, a second sample shall be taken from the lot. Average the results of the retest with the results of the original test to determine compliance with this specification.

## 9. Specimen Preparation

9.1 Mix cement with water and mold, cure, dry, and cut in accordance with Practice C 163, to produce the appropriate size and shape specimens for testing as specified below.

## 10. Test Methods

- 10.1 *Dry Covering Capacity*—Test Method C 166.
- 10.2 *Volume Change Upon Drying*—Test Method C 166.
- 10.3 *Linear Shrinkage*—Test Method C 356.

## 10.4 Apparent Thermal Conductivity

10.4.1 The thermal conductivity as a function of temperature for the representative specimens shall be determined with data obtained from a series of thermal tests utilizing test methods C 177, C 518, or C 1114 as appropriate for the material under study. Specimen shall be tested at a maximum thickness of 1½ in. (38 mm).

10.4.1.1 Test Method C 518 shall not be used at temperatures or resistances other than those in the range of the calibration.

10.4.1.2 Test Method C 1114 shall not be used at temperatures or resistance ranges other than those with comparable results to Test Method C 177.

10.4.2 The test method selected shall have proven correlation with Test Method C 177 over the temperature range of conditions used. In cases of dispute, Test Method C 177 shall be considered as the final authority for material having flat geometry.

10.4.3 Practice C 1058 shall be used to obtain recommended test temperature combinations for testing purposes.

10.4.4 As specified in Practice C 1045, the range of test conditions must include at least one test where the hot surface temperature is greater than, or equal to, the hot limit of the temperature range of desired data and at least one test where the cold surface temperature is less than, or equal to, the cold limit of the temperature range desired. Additional tests, at least two, shall be distributed somewhat evenly over the rest of the temperature range.

10.4.5 Conduct the final analysis of the thermal data in accordance with Practice C 1045 to generate a thermal conductivity versus temperature relationship for the specimen.

10.4.6 The final step of Practice C 1045 analysis is to calculate the thermal conductivity using the equations generated at a set of mean temperatures for comparison to the specification. **Warning**—While it is recommended that the specification data be presented as thermal conductivity versus temperature, several existing specifications may contain mean temperature data from tests conducted at specific hot and cold surface temperatures. In these cases, the thermal conductivity as a function of temperature from the Practice C 1045 analysis may provide different results. To insure that the data is compatible, a Practice C 680 analysis, using the thermal conductivity versus temperature relationship from Practice C 1045 and the specific hot and cold surface temperatures, is required to determine the effective thermal conductivity for comparison to the specification requirements.

10.5 *Maximum Use Temperature*—Test Method C 411, at the insulation's maximum use temperature and at the manufacturer's maximum recommended thickness at that temperature. The test surface shall be at the intended surface temperature when test begins. No special requirements for heat up shall be specified by the manufacturer.

10.6 *Non-combustibility*—Test Method E 136.

## 11. Inspection

11.1 The following requirements are employed for purposes of acceptance sampling of lots or shipments of qualified cement:

- 11.1.1 Dry covering capacity.

11.1.2 Volume change upon drying.

## 12. Rejection and Rehearing

12.1 Failure to conform to the requirements in this specification shall constitute cause for rejection. Rejection shall be reported to the manufacturer or supplier promptly and in writing.

12.2 In case of rejection, the manufacturer or supplier shall have the right to reinspect the rejected shipment and resubmit the lot after removal of that portion not conforming to the specified requirements.

## 13. Certification

13.1 When specified in the purchase order or contract, the purchaser shall be furnished certification that samples repre-

senting each lot have been either tested or inspected as directed in this specification and the requirements have been met. When specified in the purchase order or contract, a report of the test results shall be furnished.

## 14. Packaging

14.1 Unless otherwise specified or agreed upon by the purchaser and the manufacturer or supplier, the cement shall be packaged in the manufacturer's standard commercial containers.

## 15. Keywords

15.1 insulating cement; mineral fiber; thermal insulation

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*