



Standard Specification for Flat Asbestos-Cement Sheets¹

This standard is issued under the fixed designation C 220; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Asbestos warning editorially added in February 2005.

1. Scope

1.1 This specification covers asbestos-cement sheets in flat form designed for industrial, commercial, and general building purposes, of the following types:

1.1.1 *Flat Sheets, Type F (Flexible)*—An asbestos-cement flat sheet suitable for exterior and interior use, where a board having higher strength and density, smoother surface, greater flexibility, and lower moisture absorption is desired.

1.1.2 *Flat Sheets, Type U (Utility)*—An asbestos-cement flat sheet suitable for exterior and interior use, having sufficient strength for general utility and construction purposes, and where a board having maximum flexibility, highest density, smoother surface, and lower moisture absorption is not essential.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 **Warning**—Breathing of asbestos dust is hazardous. Asbestos and asbestos products present demonstrated health risks for users and for those with whom they come into contact. In addition to other precautions, when working with asbestos-cement products, minimize the dust that results. For information on the safe use of chrysotile asbestos, refer to “Safe Use of Chrysotile: A Manual on Preventive and Control Measures.”²

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

¹ This specification is under the jurisdiction of ASTM Committee C17 on Fiber-Reinforced Cement Products and is the direct responsibility of Subcommittee C17.03 on Asbestos Cement Sheet Products and Accessories.

Current edition approved June 1, 2004. Published July 2004. Originally approved in 1949. Last previous edition approved in 1999 as C 220 – 91 (1999).

² Available from The Asbestos Institute, http://www.chrysotile.com/en/sr_use/manual.htm.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

C 458 Test Method for Organic Fiber Content of Asbestos-Cement Products

C 459 Test Methods for Asbestos-Cement Flat Products

2.2 *Federal Standard:*

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)⁴

2.3 *Military Standard:*

MIL-STD-129 Marking for Shipment and Storage⁴

3. Materials and Manufacture

3.1 Flat asbestos-cement sheets shall be composed of a combination of asbestos fiber and portland cement or portland blast-furnace slag cement, with or without the addition of curing agents, water-repellent substances, mineral fillers, coatings, pigments, or mineral granules, formed under pressure and cured to meet the physical requirements of this specification. Sheets shall not contain more than 1 mass % organic fiber, as determined in accordance with Test Method C 458, Table 1 and Table 2.

4. Dimensions

4.1 Flat asbestos-cement sheets are normally supplied in the commercial dimensions given in Table 3.

5. Permissible Variations in Dimensions

5.1 *Thickness*—The average thickness of all flat sheets supplied under this specification shall be as prescribed in Table 4. The average thickness of any one sheet shall not differ from the average of all sheets by more than 10 %.

5.2 *Width and Length*—The permissible variation from the nominal width shall be $\pm 1/16$ in. (± 1.6 mm), and, from the nominal length, $\pm 1/8$ in. (± 3.2 mm), as measured after 48 h at 73°F (25°C) and 50 % relative humidity.

5.3 *Squareness*—The length of the diagonals shall not vary by more than $1/64$ in./ft (1.3 mm/m) of length of the sheet. Opposite sides of the sheet shall not vary in length by more than $1/64$ in./ft.

5.4 *Edge Straightness*—The sheet edges shall be straight within $1/64$ in./ft (1.3 mm/m) of length or width. Straightness shall be determined by stretching a string or wire along the

⁴ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

TABLE 1 Flexural Strength Requirements for Dried Specimens Loaded Simultaneously at Both One-Third Points of the Span

Type		Average Flexural Strength, nominal thickness, mm, (in.)					
		3 (1/8)	4.5 (3/16)	6 (1/4)	10 (3/8)	12 (1/2)	16 (5/8)
F	N (lbf)	140 (30)	330 (75)	589 (130)	1310 (300)	2330 (520)	3620 (810)
U	N (lbf)	... (...)	210 (50)	370 (80)	820 (180)	1470 (330)	2590 (580)

TABLE 2 Deflection Requirements for Dried Specimens Loaded Simultaneously at Both One-Third Points of the Span

Nominal Thickness		Average Deflection Under Maximum Load							
		Type F				Type U			
		Parallel to length		Parallel to width		Parallel to length		Parallel to width	
mm	(in.)	mm	(in.)	mm	(in.)	mm	(in.)	mm	(in.)
3	(1/8)	15.5	(0.06)	13	(0.5)
4.5	(3/16)	10	(0.4)	7	(0.25)	7	(0.25)	6	(0.24)
6	(1/4)	7	(0.3)	5	(0.2)	5	(0.2)	3	(0.12)
9	(3/8)	4.5	(0.18)	2.5	(0.1)	2.5	(0.1)	2.5	(0.1)
12	(1/2)	0.1	(0.004)	0.1	(0.004)	0.1	(0.004)
16	(5/8)

TABLE 3 Nominal Dimensions

Type	Nominal Thickness, in. (mm)	Nominal Width, in. (mm)	Nominal Length, in. (mm)
F	1/8, 3/16, 1/4, 3/8, 1/2, 5/8, (3.2, 4.8, 6.4, 9.5, 12.7, 15.9)	48 (1219)	48, 96, 120, 144 (1219, 2438, 3048, 3658)
U	3/16, 1/4, 3/8, 1/2, 5/8 (4.8, 6.4, 9.5, 12.7, 15.9)	48 (1219)	48, 96, 120, 144 (1219, 2438, 3048, 3658)

edge to be measured from one corner to the adjacent corner and measuring the greatest distance between the string or wire and the sheet edge.

6. Physical Requirements

6.1 *Flexural Strength*—The average breaking load in newtons (or pounds-force) of dried specimens loaded as simple beams on a span of 10 in. (254 mm) with the load applied equally and simultaneously at both one-third points of the span.

6.1.1 Flexural strength shall not be less than that shown in Table 1.

6.2 *Water Absorption*—The average water absorption shall not exceed the following mass percentages:

Type	Water Absorption, max, %
F	25
U	30

6.3 All measurements and tests necessary for determining the conformity of the asbestos-cement sheets with this specification shall be made in accordance with Test Methods C 459.

7. Workmanship, Finish, and Appearance

7.1 *Workmanship*—Sheets shall have a commercially smooth surface on one side and be free of major defects that will impair appearance, erection, use, or serviceability.

7.2 *Finish*—The surface of the sheet to be exposed shall be smooth, granular, or otherwise textured.

7.3 *Color*—The surface of the sheet shall be the natural color of the asbestos-cement product or may be colored by the

addition of mineral pigments, chemical impregnation, pigmented coatings, veneers, or embedded mineral granules.

7.4 *Efflorescence*—Efflorescence that sometimes may appear on flat asbestos-cement sheets is not a defect and should not result in a permanent change in color.

8. Rejection and Retesting

8.1 If the sample fails to conform to any one of the requirements of this specification, a second sample from the same lot shall be prepared and tested. The results of the retest shall be averaged with the results of the original test to determine compliance with this specification.

8.2 Failure to conform to any one of the requirements of this specification, upon retest as prescribed above, shall constitute grounds for rejection. In case of rejection, the seller shall have the right to reinspect the rejected shipment and resubmit the lot after removal of the portion of the shipment not conforming to the specified requirements, provided this is done within 20 days after receipt of notice of the specific cause for rejection.

9. Inspection

9.1 Inspection of material shall be made at the point of shipment. The inspector representing the purchaser shall have free access to the carriers being loaded for shipment to the purchaser. He shall be afforded all reasonable and available facilities at the point of shipment for sampling and inspection of the material, which shall be so conducted as not to interfere unnecessarily with the loading of the carriers.

10. Packaging and Shipping

10.1 *Commercial Quantities*—The commercial unit for marketing flat sheets is the square foot. Table 3 lists sizes generally available commercially.

10.2 *Commercial Packaging*—Flat sheets shall be so shipped as to ensure acceptance by common carrier. There is no standard package. The material is usually shipped in bulk, but may be crated when so specified by the purchaser.

10.3 *Storage*—Flat sheets should be piled on sufficient firm supports that will keep the sheets level and flat. The sheets shall

TABLE 4 Thickness Requirements

Nominal Thickness, in. (mm)	1/8 (3.2)	3/16 (4.8)	1/4 (6.4)	3/8 (9.5)	1/2 (12.7)	5/8 (15.9)
Average Thickness:						
min, in. (mm)	0.100 (2.54)	0.162 (4.11)	0.225 (5.72)	0.345 (8.76)	0.470 (11.94)	0.595 (15.11)
max, in. (mm)	0.150 (3.81)	0.212 (5.38)	0.275 (6.99)	0.405 (10.29)	0.530 (13.46)	0.655 (16.64)

be piled with the edges square and flush, and covered to provide protection from the weather until used.

11. Keywords

11.1 asbestos; asbestos-cement flat sheet; sheeting

SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall apply when material is supplied under this specification for U. S. Government Procurement.

S1. Packaging

S1.1 Unless otherwise specified in the contract, the material shall be packaged in accordance with the suppliers standard practice which will be acceptable to the carrier at lowest rates. Containers and packing shall comply with Uniform Freight Classification Rules⁵ or National Motor Freight Classification Rules.⁶ Marking for shipment of such material shall be in accordance with **Fed. Std. No. 123** for civil agencies and MIL-STD-129 for military agencies.

⁵ Available from The Uniform Classification Commission, Room 1106, 222 S. Riverside Plaza, Chicago, IL 60606.

⁶ Available from National Motor Freight Inc., 1616 P. St., N. W., Washington, DC 20036.

S2. Responsibility for Inspection

S2.1 Unless otherwise specified in the contract or purchase order, the manufacturer is responsible for the performance of all inspection and test requirements specified herein. Except as otherwise specified in the contract or order, the manufacturer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to assure that material conforms to prescribed requirements.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).