



Standard Test Method for Organic Fiber Content of Asbestos-Cement Products¹

This standard is issued under the fixed designation C 458; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the organic fiber content of asbestos-cement products.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 **Warning**—Breathing of asbestos dust is hazardous. Asbestos and asbestos products present demonstrated health risks for users and for those with whom they come into contact. In addition to other precautions, when working with asbestos-cement products, minimize the dust that results. For information on the safe use of chrysotile asbestos, refer to “Safe Use of Chrysotile: A Manual on Preventive and Control Measures.”²

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

C 114 Test Methods for Chemical Analysis of Hydraulic Cement

D 2946 Terminology for Asbestos and Asbestos-Cement Products

E 11 Specification for Wire Cloth and Sieves for Testing Purposes

E 50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

2.2 BNQ Standard:⁴

P2639-230 *Asbestos-Cement Sheets: Methods of Test and Control*

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *organic fiber content*—the percentage of organic matter expressed as the equivalent percentage of cellulose in a dried sample.

3.1.2 For additional definitions refer to Terminology D 2946.

4. Apparatus

4.1 *Sieve*—A 150- μm (No. 100) sieve, conforming to Specification E 11.

4.2 *Drying Oven*, ventilated, capable of being maintained at 100 to 105°C (212 to 220°F).

4.3 *Apparatus for Determination of Total Carbon by Direct Combustion*—Apparatus No. 1 of Practices E 50.

5. Reagent

5.1 *Hydrochloric Acid (1 + 17)*—Dilute 1 part by volume of concentrated hydrochloric acid (HCl, sp gr 1.19) with 17 parts of water.

6. Procedure

6.1 Grind a 100 ± 10 -g sample of the asbestos-cement to pass a 150- μm (No. 100) sieve. Avoid excessive, or high energy grinding that may cause partial thermal decomposition of organic matter. Dry 1 g of the ground sample to constant mass in a ventilated oven at a temperature of 212 or 220°F (100 to 104.4°C) and cool to room temperature in a desiccator. Determine the mass of the dried sample to the nearest 0.001 g. (**Warning**—See 1.3.)

6.2 Transfer the dried sample to a 100-cm³ beaker, add 50 cm³ of HCl (1 + 17), and digest on a steam bath for 20 min. After this treatment, filter the sample on a washed and ignited Gooch crucible pad and dry at a temperature of 100 to 105°C (212 to 220°F).

6.3 Transfer the sample and crucible pad to a combustion boat and burn in a current of oxygen in a combustion furnace. Absorb the resultant carbon dioxide (CO₂) by the procedure described in 9.3.3 and 9.3.4 of BNQ Methods P2639-230.

¹ This test method is under the jurisdiction of ASTM Committee C17 on Fiber-Reinforced Cement Products and is the direct responsibility of Subcommittee C17.03 on Asbestos-Cement Sheet Products and Accessories.

Current edition approved June 1, 2006. Published June 2006. Originally approved in 1960. Last previous edition approved in 2002 as C 458 – 98 (2002)¹.

² Available from The Asbestos Institute, http://www.chrysotile.com/en/sr_use/manual.htm.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from Bureau de Normalisation du Québec, Département de l'Industrie et du Commerce, 50 St-Joseph Street East, Québec, QC, Canada G1K 3A5.



Make a blank determination, following the same procedure and using the same amounts of all materials except the sample.

7. Calculation

7.1 Calculate the organic fiber content, in mass percent, as follows (Note 1):

Organic fiber (cellulose), % = [(A - B) x 0.614/C] x 100

where:

- A = mass of CO2, g,
B = correction for CO2 in blank, g,
C = mass of dry sample, g, and
0.614 = gravimetric factor (C6H10O5/6CO2) for converting CO2 absorbed to cellulose.

NOTE 1—Asbestos-cement products may include water-repellent substances that would produce CO2 in this test method for organic fiber. Such water-repellent substances are usually soluble in chloroform. In case of dispute, the chloroform-soluble organic substance shall be determined as described in Sections 69 to 72 of Test Methods C 114. A40.0-g sample of the ground, oven-dried material shall be used for this test method.

Water-repellent substances contain a higher percentage of carbon than cellulose. To correct for this, 1.8 times the percentage of chloroform-soluble organic substance, so determined, shall be subtracted from the calculated percentage of organic fiber (cellulose).

NOTE 2—This test method does not provide a correction for organic pigments, which would likewise produce CO2 in this test method for organic fiber.

8. Precision and Bias

8.1 Repeatability—The intra-laboratory single apparatus, operator and specimen repeatability of the mass of organic fiber content determined is as follows:

Table with 4 columns: Concentration, Mean, g, Standard Deviation, g, Relative Standard Deviation, %. Rows for Low and High concentrations.

8.2 Bias—Bias has not yet been established in accordance with the requirements of ASTM.

9. Keywords

9.1 asbestos; asbestos-cement; organic fiber

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).