



# Standard Specification for Asbestos-Cement Underdrain Pipe<sup>1</sup>

This standard is issued under the fixed designation C 508; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers asbestos-cement perforated and plain pipe intended for use in the conveyance of drainage water for the subsurface drainage of highways, airports, farms, foundations, and other similar drainage work.

1.2 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- C 150 Specification for Portland Cement
- C 458 Test Method for Organic Fiber Content of Asbestos-Cement Products
- C 500 Test Methods for Asbestos-Cement Pipe
- C 595 Specification for Blended Hydraulic Cements
- C 608 Method of Test for Brittle Ring Tensile Strength of Chemically Setting Silicate and Silica Chemical-Resistant Mortars
- C 618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use as a Mineral Admixture in Concrete

### D 2946 Terminology for Asbestos and Asbestos-Cement Products

#### 2.2 Federal Standard:

No. 123 Marking for Shipment Civil Agencies<sup>3</sup>

#### 2.3 Military Standard:

MIL-STD-129 Marking for Shipment and Storage<sup>3</sup>

#### 2.4 Other Standards:

Uniform Freight Classification Rules<sup>4</sup>

National Motor Freight Classification Rules<sup>5</sup>

## 3. Terminology

### 3.1 Definitions:

3.1.1 *coupling, n*—component made from a larger diameter pipe of the same type or class, or of Type II and a higher class, or produced otherwise to yield at least equal performance, for joining asbestos-cement pipe that when properly installed, forms a silt-tight joint, allows alignment corrections and slight changes in direction, and provides an assembled joint equivalent in serviceability and strength to the pipe sections.

3.1.2 *lot*—each 400 m (1300 ft) of pipe or less of a given type and size manufactured on each machine during a 24-h period.

3.2 Additional terminology is given in Terminology D 2946.

## 4. Sizes and Types

4.1 Asbestos-cement underdrain pipe furnished under this specification shall be known as “asbestos-cement underdrain pipe.” It shall be furnished in nominal inside diameters of 10, 15, 20, 25, and 30 cm (4, 6, 8, 10, and 12 in.). The types of pipe shall be known as Type I and Type II corresponding to the chemical requirements given in Section 9.

NOTE 1—To assist the purchaser in choosing the type of pipe most suitable for his use, guidelines for the definition of aggressiveness of water

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C17 on Fiber-Cement Products and is the direct responsibility of C17.03 on Asbestos-Cement Sheet Products and Accessories.

Current edition approved Nov. 1, 2004. Published January 2005. Originally approved in 1963. Last previous edition approved in 2000 as C 508–00.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>3</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

<sup>4</sup> Available from the Uniform Classification Commission, Room 1106, 222 S. Riverside Plaza, Chicago, IL 60606.

<sup>5</sup> Available from National Motor Freight Inc., 1616 P. St., N.W., Washington, DC 20036.

and of soil environments for selection of the proper type of asbestos-cement pipe are covered in the appropriate sections of Test Methods **C 500**.

## 5. Materials and Manufacture

5.1 Asbestos-cement underdrain pipe shall be composed of an intimate mixture of portland cement or portland blast-furnace slag cement described in Specification **C 150** or portland blast-furnace slag or pozzolan cements described in Specification **C 595** and asbestos fiber with or without fine silica or additives containing such silica meeting Specification **C 608** that is capable of reacting completely to yield calcium silicate reaction products upon autoclaving; and asbestos fiber. The mixture shall not contain more than 0.2 % of nondeleterious organic matter as determined by Test Method **C 458**. The material shall be of laminar construction, formed under pressure to a homogeneous structure, and cured to meet the physical and chemical requirements of this specification.

## 6. Crushing Strength

6.1 Crushing tests shall be conducted before shipment. Pipe of 30 cm (1 ft lengths) cut from unmachined portions of the pipe shall have the minimum crushing strength prescribed in **Table 1** when tested in accordance with the Procedure section of Test Methods **C 500**, except that when the perforated underdrain pipe is tested, the sample shall contain four circumferential rows of holes with the first row 4 cm (1.5 in.) from the end. The specimen shall be tested with the line of symmetry of the rows facing downward, with the rows of holes being in the lower two quadrants.

6.2 In case a specimen fails to meet the crushing test requirement, refer to **13.3**.

## 7. Couplings

7.1 Each standard, short, or random length of pipe shall be provided with a coupling for the purpose of maintaining alignment and to ensure close joints.

## 8. Fittings

8.1 Asbestos-cement underdrain pipe fittings shall be suitable in size, type, crushing strength, and design for the pipe with which they will be furnished.

## 9. Chemical Requirements

9.1 When tested in accordance with the Procedure section of Test Methods **C 500**, the amount of uncombined calcium hydroxide shall not exceed 1.0 % for Type II pipe.

NOTE 2—There are no chemical requirements for Type I Pipe.

**TABLE 1 Crushing Strength**

Nominal Size		Min Crushing Load	
cm	(in.)	kNm	(lbf/ft)
10	(4)	15	(1000)
15	(6)	16	(1100)
20	(8)	19	(1300)
25	(10)	20	(1400)
30	(12)	22	(1500)

**TABLE 2 Perforations**

Nominal Size		Rows of Perforations
cm	(in.)	
10	(4)	4
15	(6)	4
20	(8)	4
25	(10)	6
30	(12)	6

9.2 If the uncombined calcium hydroxide exceeds 1 %, refer to **13.4**.

## 10. Sizes and Dimensions

10.1 The nominal standard length for asbestos-cement underdrain pipe shall be either 3 or 4 m (10 or 13 ft). A maximum of 15 % of the total footage of any one size and type for any order may be furnished, at the manufacturer's option, in pipe lengths shorter than specified nominal, but not shorter than 2 m (7 ft). These shall be termed random lengths.

10.2 A tolerance of 25 mm (1 in.) shall apply to nominal standard lengths, and 152 mm (6 in.) shall apply to random lengths. For billing purposes, random lengths shall be classified to 150-mm (6-in.) increments, allowing a tolerance of + 125 and – 25 mm (+ 5 and – 1 in.).

10.3 The average inside diameter of the pipe shall not be less than nominal by 6 mm (0.25 in.) or 1½ %, whichever is greater.

## 11. Perforations

11.1 Perforations, when required, shall be circular holes,  $6 \pm 1.5$  mm ( $0.25 \pm 0.05$  in.) in diameter, arranged in rows parallel to the axis of the pipe. Perforations shall be approximately 75 mm (3 in.) center-to-center, along the rows. Rows shall be arranged in two equal groups on either side of the vertical center line of the pipe, and the total number of rows shall be as shown in **Table 2**. The lowermost rows of perforations in each group shall be separated by an arc of 1.6 rad (90°) and the upper most rows of perforations in each group shall be separated by an arc of 2.8 rad (160°). The spacing of rows between these limits shall be uniform. Holes are not prohibited from appearing at the ends of short and random lengths.

## 12. Sampling

12.1 All material tested under this specification shall be in a normal processed condition and at moisture equilibrium with the atmosphere.

12.2 For crushing tests, select one full length of pipe from each lot of each size and type of pipe. Cut one test specimen 30 cm (12 in.) long from the unmachined portion of the selected length of pipe. (**Warning**—When cutting asbestos-cement products minimize the dust that results. Prolonged or frequent breathing of significant airborne concentrations of silica or asbestos dust is hazardous. When such dusts are generated, effective measures shall be taken to prevent inhalation. Refer to approved techniques.<sup>6</sup>)

<sup>6</sup> Available from Asbestos International Association, 1235 Jefferson Davis Highway, PMB 114, Arlington, VA 22202.

12.3 When uncombined calcium hydroxide tests are requested (Section 9), one sample shall be taken from each lot of pipe. The sample to be tested shall be taken from any one of the specimens selected for the crushing test.

### 13. Inspection and Rejection

13.1 All material furnished under this specification shall conform to the requirements stated herein and shall be subjected to the factory inspection and tests prescribed in this specification. When requested by the purchaser on his order, the manufacturer shall notify the purchaser of the time that the inspection and testing will take place so that the purchaser shall arrange for witnessing such tests and inspections at his own expense. In lieu of such inspection, when requested, the manufacturer shall be prepared to certify that his product conforms to the requirements of this specification.

13.2 Each pipe and coupling shall be inspected by the manufacturer before shipment for compliance with the standards for dimensions, tolerances, and workmanship and finish (see Section 10).

13.3 Failure of any specimen tested for crushing strength to withstand 75 % of the load specified in Section 6 shall be cause for rejection of the lot from which the test specimen was taken. When any specimen tested for crushing strength withstands

over 75 % but under 100 % of the load specified in Section 6, one specimen shall be cut from each of two additional pipes of the same lot. Failure of either of these additional specimens to meet the strength requirements of Section 6 shall be cause for rejection of the entire lot from which the original sample was taken.

13.4 If the results of the uncombined calcium hydroxide test show the sample failed to meet the specification requirements, two additional specimens shall be selected and sampled for test. The failure of one of these two additional samples to meet the specification requirements of Section 9 shall be cause for rejection of the lot.

### 14. Marking and Shipping

14.1 *Standard and Random Lengths*—Each standard or random length of pipe shall be marked clearly on the outside surface with the trade name, nominal inside diameter, type, and date of manufacture in alkali resistant ink or indelible paint.

14.2 All pipe and couplings, unless otherwise specified, shall be prepared for standard commercial shipment.

### 15. Keywords

15.1 asbestos-cement; drainage; perforated; pipe; subsurface; underdrain

## SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall apply when material is supplied under this specification for U.S. Government procurement.

### S1 Packaging

S1.1 Unless otherwise specified in the contract, the material shall be packaged in accordance with the producer's standard practice which will be acceptable to the carrier at lowest rates. Containers and packing shall comply with Uniform Freight Classification Rules or National Motor Freight Classification Rules. Marking for shipment of such material shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

### S2. Responsibility for Inspection

S2.1 Unless otherwise specified in the contract or purchase order, the producer is responsible for the testing of all material to assure compliance with the requirements specified herein. Except as otherwise specified in the contract or order, the producer shall use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to assure that material conforms to prescribed requirements.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*