



## Standard Test Method for Moisture in a Graphite Sample<sup>1</sup>

This standard is issued under the fixed designation C 562; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method provides a practical determination for the percentage of moisture in a graphite sample.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C 561 Test Method for Ash in a Graphite Sample

### 3. Significance and Use

3.1 This test method is feasible only for the volatile moisture present on the graphite due to adsorption from the atmosphere and is not intended to give representative moisture data for graphite that has been exposed to liquid water contamination.

### 4. Interferences

4.1 Final weights (and therefore percent moisture values) may be influenced by the following:

4.1.1 Type and condition of desiccant.

4.1.2 Ambient relative humidity at the time of the test.

4.1.3 Timing and procedure for moving samples from desiccator to the balance.

4.1.4 Adsorptivity of the graphite sample relative to the adsorptivity of the desiccant used.

4.1.5 Residency time in the desiccator.

### 5. Apparatus

5.1 *Alumina Ceramic or Platinum Crucible or Dish*, suitable for holding sample (subsequently called sample holder).

5.2 *Analytical Balance*, capable of weighing to  $\pm 0.0002$  g.

5.3 *Drying Oven*, air convection type, capable of being controlled to  $110 \pm 2^\circ\text{C}$  ( $230 \pm 4^\circ\text{F}$ ).

5.4 *Desiccator*, charged with indicating desiccant.

### 6. Sampling

6.1 Samples may be solid or particulate. Solid bodies may be sampled by removing one or more solid pieces from the body by, for example, sawing, turning, milling, or fracturing. Particulate samples may be generated from solid bodies by drilling, using a carbide drill to minimize contamination, or by other crushing and grinding methods.

### 7. Procedure

7.1 Tare a dried sample holder using an analytical balance. Weigh a 25 to 50-g sample into the tared sample holder and reweigh both. (Perform all weighings to a precision of  $\pm 0.002$  g.)

7.2 Place the sample holder containing the sample in a drying oven maintained at  $110 \pm 2^\circ\text{C}$  ( $230 \pm 4^\circ\text{F}$ ) for 2 h. Remove from the oven and immediately place in the desiccator. When the sample has reached room temperature, remove from the desiccator and weigh immediately.

7.3 Repeat the procedure prescribed in 7.2 until a constant weight of  $\pm 0.002$  g is achieved.

7.4 The dried sample may be reserved for ash determination. (See Test Method C 561.)

### 8. Calculation

8.1 Calculate the percentage of moisture as follows:

$$\text{Moisture, \%} = [(B - C)/(B - A)] \times 100$$

where:

A = weight of sample holder,

B = weight of sample holder and sample, and

C = weight of sample holder and dried sample.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.F0 on Manufactured Carbon and Graphite Products.

Current edition approved June 1, 2005. Published August 2005. Originally approved in 1965. Last previous edition approved in 2000 as C 562-91(2000).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 9. Report

9.1 The report shall include the following information:

9.1.1 Proper identification of the sample, and

9.1.2 Results obtained from at least two moisture determinations, and their average.

## 10. Precision and Bias <sup>3</sup>

10.1 The precision of this test method was determined during a round-robin test among four laboratories testing samples split from a common sample which was ground to pass a No. 60 (250  $\mu\text{m}$ ) sieve. This sampling method was used for

---

<sup>3</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:C05-1008.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*

the round robin to minimize variations among samples provided to participating laboratories.

10.2 On this sample the mean, standard deviation between laboratories and standard deviation within laboratories were, respectively:

Mean	0.0155
Between laboratories	0.0143
Within laboratories	0.0037

10.3 No bias was noted during the round-robin test; however, the method is empirical and there is no suitable reference material that can be used to determine the bias of this test method.

## 11. Keywords

11.1 carbon; graphite; moisture