



# Standard Specification for Limestone Dimension Stone<sup>1</sup>

This standard is issued under the fixed designation C 568; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of limestone for general building and structural purposes. Refer to Guides C 1242 and C 1528 for the appropriate selection and use of limestone dimension stone.

1.2 Dimension limestone shall include stone that is sawed, cut, split, or otherwise finished or shaped and shall specifically exclude molded, cast, or otherwise artificially aggregated units of composed fragments, and also crushed and broken stone.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- C 97 Test Methods for Absorption and Bulk Specific Gravity of Dimension Stone
- C 99 Test Method for Modulus of Rupture of Dimension Stone
- C 119 Terminology Relating to Dimension Stone
- C 170 Test Method for Compressive Strength of Dimension Stone
- C 241 Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic
- C 1242 Guide for Selection, Design, and Installation of Dimension Stone Anchoring Systems
- C 1353 Test Method Using the Taber Abraser for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic
- C 1528 Guide for Selection of Dimension Stone for Exterior Use

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C18 on Dimension Stone and is the direct responsibility of Subcommittee C18.03 on Material Specifications.

Current edition approved Oct. 1, 2008. Published November 2008. Originally approved in 1965. Last previous edition approved in 2008 as C 568 – 08.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Terminology

3.1 *Definitions*—All definitions are in accordance with Terminology C 119.

## 4. Classification

4.1 Dimension limestone shall be classified into three categories, generally descriptive of those limestones having densities in approximate ranges, as follows:

4.1.1 *I (Low-Density)*—Limestone having a density ranging from 110 through 135 lb/ft<sup>3</sup> (1760 through 2160 kg/m<sup>3</sup>).

4.1.2 *II (Medium-Density)*—Limestone having a density greater than 135 and not greater than 160 lb/ft<sup>3</sup> (2160 through 2560 kg/m<sup>3</sup>).

4.1.3 *III (High-Density)*—Limestone having a density greater than 160 lb/ft<sup>3</sup> (2560 kg/m<sup>3</sup>).

## 5. Physical Requirements

5.1 Limestone supplied under this specification shall conform to the physical requirements listed in Table 1.

5.2 Limestone shall be sound, durable, and free of spalls, cracks, open seams, pits, or other defects that are likely to impair its structural integrity in its intended use.

5.3 The desired color and texture, with their permissible natural variations in material characteristics for all material to be produced for the project, shall be established by control samples. Select representative samples by viewing a sufficient number of physical samples prior to production that show the complete range of variations in color and texture of the limestone specified.

## 6. Sampling

6.1 Samples, if required, for testing to determine the characteristics and physical properties shall be representative of the limestone to be used.

## 7. Keywords

- 7.1 calcium carbonate; limestone

**TABLE 1 Physical Requirements**

NOTE—The values in **Table 1** were established using samples prepared according to the individual test methods. Finishes, other than those specified in the individual test methods, may result in a deviation from established values.

Physical Property	Test Requirements	Classification	Test Method(s)
Absorption by weight, max, %	12	I low-density	<b>C 97</b>
	7.5	II medium-density	
	3	III high-density	
Density, min, lb/ft <sup>3</sup> (kg/m <sup>3</sup> )	110 (1760)	I low-density	<b>C 97</b>
	135 (2160)	II medium-density	
	160 (2560)	III high-density	
Compressive strength, min, psi (MPa)	1800 (12)	I low-density	<b>C 170</b>
	4000 (28)	II medium-density	
	8000 (55)	III high-density	
Modulus of rupture min, psi (MPa)	400 (2.9)	I low-density	<b>C 99</b>
	500 (3.4)	II medium-density	
	1000 (6.9)	III high-density	
Abrasion resistance, min, hardness <sup>A,B,C</sup>	10	I low-density	<b>C 241/C 1353</b>
	10	II medium-density	
	10	III high-density	

<sup>A</sup> Pertains only to stone subject to foot traffic.

<sup>B</sup> The supplier of the No. 60 Alundum abrasive, Norton, has indicated that the formula for Norton treatment 138S has been changed. The new abrasive is currently more aggressive, resulting in lower abrasive hardness values ( $H_a$ ) than when the standard was initially established. As such, care should be taken when interpreting  $H_a$  values from tests using the new abrasive, particularly with regard to current ASTM stone standard specification requirements for abrasion resistance, which were developed when the original abrasive was still in use. Committee C18 is actively studying alternatives to address this issue.

<sup>C</sup> Abrasion Resistance Test Method **C 1353** will eventually replace Test Method **C 241** and it is not necessary to perform both tests. Availability of the proper equipment and materials by the testing laboratory may determine which test is performed.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*