



Standard Test Method of Thermal Shock Test on Glass Pipe¹

This standard is issued under the fixed designation C 600; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 Since thermal shock resistance is so closely related to the linear coefficient of expansion, this test method for the determination of the thermal shock resistance of glass process pipe is primarily intended to supplement test results on the linear coefficient of expansion, Test Method E 228. This thermal shock test will not ordinarily be performed except in those cases where the thermal shock resistance may be questioned.

1.2 This test method covers only two of four thermal shock possible approaches, namely independent downshock of outside and inside pipe surfaces. Downshock is more severe since a higher tensile stress is produced and, hence, more likely to produce failure.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

E 228 Test Method for Linear Thermal Expansion of Solid Materials with a Vitreous Silica Dilatometer²

3. Significance and Use

3.1 This test method provides a practical means of assessing glass pipe strength under short-duration, thermally-imposed tensile stresses. In addition to a principal role played by the linear coefficient of thermal expansion, glass surface defects can also be major factors in reducing downshock performance.

4. Apparatus

4.1 *Oven*, equipped with a device to maintain the temperature with ±5°F (±3°C) of the specified temperature. An indicating controller is recommended. Otherwise, a dial thermometer should be attached and the temperature controlled manually.

¹ This test method is under the jurisdiction of ASTM Committee C14 on Glass and Glass Products and is the direct responsibility of Subcommittee C14.05 on Glass Pipe.

Current edition approved Sept. 1, 2005. Published October 2005. Originally approved in 1967. Last previous edition approved in 2000 as C 600 – 85 (2000).

² Withdrawn.

TABLE 1 Oven Temperature Setting

Nominal Pipe Size, in.	T_{oven}	
	°F	°C
1/4	282	140
3/8	282	140
1/2	282	140
3/4	282	140
1	282	140
1 1/2	282	140
2	282	140
3	282	140
4	251	122
6	232	111

4.2 *Water Tank*, at least 18 in. (457 mm) deep with a width and length sufficient to accommodate the samples to be tested. The tank shall be filled with ice water to a depth of at least 12 in. (305 mm). The water temperature shall be maintained at 34 ± 2°F (1 ± 1°C).

4.3 *Timer*, capable of measuring seconds.

5. Sampling

5.1 A random sampling of 1 % (but not less than two pieces) of pipe and fittings shall be made.

6. Procedure

6.1 Set the oven at the proper temperature, in degrees Fahrenheit, determined as follows:

$$T_{oven} = 32 + 1.25 (\Delta T_{recommended}) \quad (1)$$

6.2 *Thermal Shock Test—Outside Surface*—Close off all open ends of sample; use glass pipe caps or flat metal plates, plus the necessary flanges, gaskets, inserts, nuts, and bolts. Keep the closed sample in the oven, at temperature, for at least 30 min. Completely submerge the sample in the tank of ice water for 30 s. Keep the time elapsed between removing the sample from the oven and submerging it in ice water not less than 15 s, nor more than 45 s. Inspect each sample for indications of failure.

6.3 *Thermal Shock Test—Inside Surface*—Close off all open ends of sample except one; use glass pipe caps or flat metal plates, plus the necessary flanges, gaskets, inserts, nuts, and bolts. Keep the partially closed sample in the oven, at temperature, for at least 30 min. Remove the sample from the oven, placing the one open end up. Pour ice water into the open end of the sample to overflowing. Keep the time elapsed between



the removal of the sample from the oven and the beginning of the time to pour the water to no less than 15 s and no more than 45 s. Pour water into the sample at a rate such that the sample shall be filled within 1 min from the start of the pouring.

NOTE 1—For tests in 6.1 through 6.3 the same sample(s) may be used for inside and outside surfaces (unless the sample fails one of the two tests).

7. Report

7.1 Report the following:

- 7.1.1 Sampling percentage,
- 7.1.2 Number, size, and description of each sample tested,
- 7.1.3 Time of transfer used,

- 7.1.4 Temperature differential used, and
- 7.1.5 Results of test:
 - 7.1.5.1 For the outside surface thermal shock test, number of samples that failed, and
 - 7.1.5.2 For the inside surface thermal shock test, number of samples that failed.

8. Precision and Bias

8.1 Due to the fail-pass nature of the test, statements on precision and bias are not applicable.

9. Keywords

9.1 glass; pipe; thermal shock

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).