



Standard Test Method for Extrusion Rate and Application Life of Elastomeric Sealants¹

This standard is issued under the fixed designation C 603; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers two laboratory procedures for determining the extrusion rate and application life (or “pot life”) of elastomeric chemically curing sealants for use in building construction.

NOTE 1—These sealants are supplied with various rheological properties ranging from pourable liquids to nonsagging pastes. Single-component sealants are supplied ready for use upon opening the container, and their rate of cure is determined by the climatic conditions to which they are exposed. Multicomponent sealants are supplied as a base component and a curing agent separately packaged. After mixing the two parts, the sealant is ready for application, and curing begins immediately.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are provided for information only.

1.3 There is no known ISO equivalent to this test method.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

C 717 Terminology of Building Seals and Sealants

3. Terminology

3.1 *Definitions*—For definitions of terms used in test method, see Terminology C 717.

4. Significance and Use

4.1 The results obtained by this test method are simply a measure of the time required to extrude a known volume of sealant through a known orifice under a predetermined pressure.

4.2 This test method is not considered a measure of cure rate.

5. Apparatus

5.1 *Caulking Gun*, 177-mL (6-fl oz) capacity, air-powered.

5.2 *Polyethylene Cartridge*, 177-mL (6-fl oz), with the front end having an inside diameter of 13.7 ± 0.05 mm (0.540 ± 0.002 in.).

5.3 *Air Supply*, providing 345 kPa (50-psi) pressure and having the necessary connection fittings for attachment to the air-powered caulking gun.

5.4 *Timing Device* (clock or watch), calibrated in seconds.

5.5 *500-mL (1-pt) Container*

6. Standard Test Conditions

6.1 Unless otherwise specified by those authorizing the tests, standard conditions for both tests are room temperature of $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 5\%$ relative humidity.

7. Procedure

7.1 *Extrusion Rate of Single-Component Sealant*—First condition the unopened container for at least 16 h at standard conditions. Then place a sufficient amount of sealant into the 177-mL (6-fl oz) cartridge to fill it completely with the plunger in place, fully retracted. Using no nozzle on the cartridge, gun the sealant at 345 kPa (50-psi) pressure into the 500-mL (1-pt) container, measuring the time in seconds required to empty the cartridge.

NOTE 2—When the printed instructions of the sealant manufacturer so recommended, heat the sealant before extruding it into the container.

7.2 *Extrusion Rate or Application Life or both, of Mixed Multicomponent Sealant*—First condition the unopened containers of both sealant and curing agent for at least 16 h at

¹ This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.20 on General Test Methods.

Current edition approved May 1, 2008. Published June 2008. Originally approved in 1969. Last previous edition approved in 2004 as C 603 - 04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

standard conditions. Then mix 400 g of the sealant with the proper amount of curing agent, stirring the mixture by hand for 5 min. Place a sufficient amount of the mixed compound into the 177-mL (6-fl oz) cartridge to fill it completely with the plunger in place, fully retracted, and set the filled cartridge aside, in a vertical position, at standard conditions, for 3 h (Note 3). Then, using no nozzle on the cartridge, gun the sealant at 345 kPa (50-psi) pressure into the 500-mL (1-pt) container, measuring the time in seconds required to empty the cartridge.

NOTE 3—Curing times and conditions for multi-component mixed compounds may vary. Therefore curing periods of longer or shorter than 3 h, and under other than the specified standard conditions, or either one of these two may be specified in some cases.

8. Report

8.1 The report on the extrusion rate of the single-component sealant shall state:

- 8.1.1 The trade name (or other identification) of the sealant.
 - 8.1.2 The time, in seconds, required to empty the cartridge (the extrusion rate), and
 - 8.1.3 Any variation, specified or otherwise, from the above described test method, including heating of the sealant if so required.
- 8.2 The report on the extrusion rate or application life, or both, of the multicomponent sealant shall state:
- 8.2.1 The trade name (or other identification) of the sealant,
 - 8.2.2 The time, in seconds, required to empty the cartridge after the 3-h (or other specified) curing period, and
 - 8.2.3 Any variations, specified or otherwise, from the above described test method, including the length of curing period and the conditions of temperature and humidity during this period.

9. Precision and Bias ³

9.1 The precision and bias calculations for this test method are based on the results of four laboratories testing five materials, each in triplicate. The results are given in Table 1.

10. Keywords

10.1 application life; extrusion rate; pot life; sealant

TABLE 1 Precision and Bias Data^A

Material	Average	Estimated Standard Deviation Within a Laboratory	Estimated Standard Deviation Between Laboratories	Repeatability Internal	Reproducibility
G1	3.6	0.32	1.24	0.91	3.40
G2	2.4	0.52	1.54	1.48	4.36
G3	5.3	0.30	2.37	0.86	6.70
G4	6.3	2.32	6.46	6.56	18.28
G5	2.1	0.22	0.89	0.62	2.51

^A At 95 % confidence a variation of as much as 6.56 can be expected within a laboratory and 18.28 between laboratories.

³ Supporting data are available from ASTM Headquarters. Request RR: C24-1010.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).