



# Standard Specification for Asbestos-Cement Organic-Foam Core Insulating Panels<sup>1</sup>

This standard is issued under the fixed designation C 659; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification covers asbestos-cement plastic-foam core panels consisting of a core of insulating cellular plastic sandwiched between and bonded to two sheets of asbestos-cement facing board. Asbestos-cement plastic-foam core panels are normally nonload-bearing panels designed for exterior and interior walls, partitions, curtain walls, and other insulation and decorative purposes.

1.2 All measurements and tests necessary for determining the conformity of asbestos-cement plastic-foam core panels with this specification are made in accordance with the test methods covered in Sections 6 and 10.

1.3 The values stated in SI units are to be regarded as the standard. The values stated in parentheses are provided for information only.

1.4 **Warning**—Breathing of asbestos dust is hazardous. Asbestos and asbestos products present demonstrated health risks for users and for those with whom they come into contact. In addition to other precautions, when working with asbestos-cement products, minimize the dust that results. For information on the safe use of chrysotile asbestos, refer to “Safe Use of Chrysotile Asbestos: A Manual on Preventive and Control Measures.”<sup>2</sup>

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See 1.4 for a specific hazard warning.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>3</sup>

**C 220** Specification for Flat Asbestos-Cement Sheets

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C17 on Fiber-Reinforced Cement Products and is the direct responsibility of C17.03 on Asbestos - Cement Sheet Products and Accessories.

Current edition approved May 1, 2008. Published July 2008. Originally approved in 1970. Last previous edition approved in 2003 as C 659 – 90(2003) <sup>$\epsilon$ 1</sup>.

<sup>2</sup> Available from The Asbestos Institute, [http://www.chrysotile.com/en/sr\\_use/manual.htm](http://www.chrysotile.com/en/sr_use/manual.htm).

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**C 236** Test Method for Steady-State Thermal Performance of Building Assemblies by Means of a Guarded Hot Box<sup>4</sup>

**C 355** Discontinued 1983; Test Methods for Water Vapor Transmission of Thick Materials; Replaced by E 96<sup>4</sup>

**D 2341** Specification for Rigid Urethane Foam<sup>4</sup>

**E 96/E 96M** Test Methods for Water Vapor Transmission of Materials

2.2 *Federal Standard:*

**Fed. Std. No. 123** Marking for Shipment (Civil Agencies)<sup>5</sup>

2.3 *Military Standard:*

**MIL-STD-129** Marking for Shipment and Storage<sup>5</sup>

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *flexural strength, n*—the average breaking load in newtons (or lbf) of specimens conditioned seven days at  $23 \pm 2^\circ\text{C}$  and  $50 \pm 10\%$  relative humidity, loaded as simple beams with the load applied equally and simultaneously at both one-third points of the span.

3.1.2 *thermal resistance, R*—of a panel, the difference in temperature which will develop under a given steady state heat flow between two parallel unit area surfaces for a given material thickness.

## 4. Materials and Manufacture

4.1 Asbestos-cement plastic-foam core sandwich panels shall be composed of a plastic-foam core sandwiched between and bonded to two asbestos-cement facing sheets. The sheets may be supplied with a factory-applied finish, a factory prime coat, or uncoated. In order to provide a balanced panel and prevent field warpage, the two asbestos-cement facings should have essentially equal vapor transmission rates.

## 5. Physical Properties

5.1 *Facings*—Asbestos-cement facing sheets shall conform to the requirements for Type F of Specification **C 220** for 3.2-mm ( $1/8$ -in.) thickness.

5.2 *Core*—The plastic-foam core as well as pertinent grade or type classification shall be as agreed upon by the purchaser

<sup>4</sup> Withdrawn.

<sup>5</sup> Available from Standardization Documents, Order Desk, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094. Attn: NPODS.

and seller. If Urethane is used, it shall conform to the requirements of Specification **D 2341**.

**5.3 Strength Properties**—The average breaking load for panel specimens conditioned for seven days at  $23 \pm 2^\circ\text{C}$  ( $70$  to  $77^\circ\text{F}$ ) and  $50 \pm 10\%$  relative humidity shall not be less than that shown in **Table 1**.

**5.4 Vapor Permeability**—The vapor permeance of the composite panel is dependent not only on the foam core, but on the adhesive, facing sheets, and the coating on such facings. The vapor permeabilities shown in **Table 2** are typical values for the core materials and are not restrictive values for the composite panel.

**5.5 Thermal Resistance, *R***—The average thermal resistance,  $R$ , =  $5^\circ\text{F}\cdot\text{ft} = 2\cdot\text{h}/\text{Btu}$  ( $\text{K}\cdot\text{m} = 2/W$ ) = 6 of the panel shall not be less than the requirements in **Table 3**.

**5.6 Adhesive Line Bond**—The bond of the glue line shall withstand weather exposure and have such quality that specimens in the flexural strength test fail within the core board and not at any of the glue lines.

## 6. Dimensional Measurements

**6.1 Significance**—These are routine measurements for the purpose of determining whether the length and width of the individual units are as ordered, to ensure that they fit together properly in application, and to determine the uniformity of the specified thickness.

**6.2 Procedure**—Measure each test specimen for thickness, using a micrometer caliper having flat anvils approximately 6.4 mm ( $1/4$  in.) in diameter and reading to 0.0254 mm (0.001 in.). Make four measurements on each specimen at the approximate midpoint of each edge of the specimen, and at least 12.7 mm ( $1/2$  in.) in from the edge. Average the four measurements, and record as the specimen thickness.

## 7. Dimensions, Mass, and Permissible Variations

**7.1 Asbestos-cement plastic-foam core panels** are normally supplied in the commercial dimensions given in **Table 4**. However, because of the frequent use of other thicknesses, the scope of this specification is not limited to only the more common thicknesses.

### 7.2 Permissible Variation in Dimensions:

**7.2.1 Thickness**—The permissible variation of any individual panel from the nominal thickness shall be  $\pm 1.2$  mm ( $3/64$  in.).

**7.2.2 Width and Length**—The permissible variation of any individual panel from the nominal length and width shall be  $\pm 3.2$  mm ( $1/8$  in.) and  $\pm 1.6$  mm ( $1/16$  in.), respectively, as measured after 48 h at  $23 \pm 2^\circ\text{C}$  ( $70$  to  $77^\circ\text{F}$ ) and  $50 \pm 5\%$  relative humidity.

**7.2.3 Squareness**—The deviation from squareness shall not exceed 1.3 mm/m ( $1/64$  in./ft) of width or length. The recom-

**TABLE 1 Flexural Strength Requirements For Panels With Third-Point Loading**

| Nominal Thickness |                     | Minimum Flexural Load |       |
|-------------------|---------------------|-----------------------|-------|
| mm                | (in.)               | N                     | (lbf) |
| 25                | (1)                 | 1330                  | (300) |
| 40                | ( $1\frac{9}{16}$ ) | 1870                  | (420) |
| 40                | (2)                 | 2270                  | (510) |

**TABLE 2 Vapor Permeability**

|             | Permeability of Core<br>perm-in. (kg/Pa·s·m) |
|-------------|--|
| Polystyrene | 5.0 ( $7.3 \times 10^{-12}$ )                |
| Urethane    | 2.0 ( $2.9 \times 10^{-12}$ )                |

**TABLE 3 Thermal Resistance, *R***

| Panel           | Nominal<br>Thickness, in. | <i>R</i> value at 75°F, (24°C), mean<br>Temperature, min. [ $^\circ\text{F}\cdot\text{ft}^2\cdot\text{h}/\text{Btu}$<br>( $\text{K}\cdot\text{m}^2/\text{W}$ )] |             |
|-----------------|---------------------------|---|-------------|
|                 |                           | Polystyrene   | Urethane    |
| 1               | $3/4$                     | 2.70 (0.48)   | 4.35 (0.76) |
| $1\frac{9}{16}$ | $1\frac{5}{16}$           | 4.76 (0.84)   | 7.69 (1.35) |
| 2               | $1\frac{3}{4}$            | 6.25 (1.10)   | 10.0 (1.75) |

**TABLE 4 Standard Sizes**

|                     |                        |                                |
|---------------------|------------------------|--------------------------------|
| Length, ft (m)      | 6, 8, 9, 10, 12        | (1.83, 2.44, 2.74, 3.05, 3.66) |
| Width, ft (m)       | 4                      | (1.22)                         |
| Thickness, in. (mm) | 1, $1\frac{9}{16}$ , 2 | (25, 40, 51)                   |

mended tools for measuring squareness are a feeler gage and metal carpenter square.

## 8. Workmanship, Finish, and Appearance

**8.1 Workmanship**—Panels shall have a commercially acceptable surface on both sides and be free of major defects that will impair appearance, erection, use, or serviceability.

**8.2 Finish**—The surface on both sides of the panel may be smooth, grained, granuled, coated, or otherwise textured as specified by the purchaser.

**8.3 Color**—Both surfaces of the panel will be the natural color of the asbestos-cement product or may be colored by the addition of mineral pigments, chemical impregnation, pigmented coatings, veneers, or embedded mineral granules as specified by the purchaser.

## 9. Sampling

**9.1** Select at random a number of panels from each shipment or fraction thereof representing a product of the same kind. The following table shows the number of panels to be selected from shipments of various sizes:

| Number of Panels<br>in Shipment | Number of<br>Samples |
|---------------------------------|----------------------|
| 500 and under                   | 3                    |
| 501 to 1000                     | 5                    |
| 1001 to 1728                    | 6                    |
| 1729 to 2744                    | 7                    |
| 2745 to 4096                    | 8                    |
| 4097 to 5832                    | 9                    |
| 5833 to 8000                    | 10                   |

## 10. Test Methods

### 10.1 Flexural Strength:

**10.1.1 Procedure**—Cut two specimens 305 by 760 mm (12 by 30 in.), from each panel to be tested, with the long dimension of the samples parallel to the long dimension of the panel. Condition each specimen for seven days at  $23 \pm 2^\circ\text{C}$  ( $70$  to  $77^\circ\text{F}$ ) and  $50 \pm 10\%$  relative humidity. Determine the flexural strength of each specimen by placing the specimen on supports that do not exert longitudinal constraint (rocker-type

bearing edges or rollers with a 3 mm (1/8 in.) minimum and a 13 mm (1/2 in.) maximum radius) and applying the load equally and simultaneously at both one-third points of the span through similar edges bearing against either surface of the specimen. The test span shall be 610 ± 1.6 mm (24 ± 1/16 in.) and the load line and supports shall be parallel. Increase the load applied at a uniform rate to produce a failure of the specimen in 1 to 2 min. The error in the load reading shall not exceed 1 % of the maximum load. Report the flexural strength as the average breaking load, in newtons (or pounds-force), for all the specimens tested.

10.1.2 **Warning**—see 1.4.

10.2 *Vapor Permeability*:

10.2.1 *Significance*—The purpose of this test method is to obtain, by means of simple apparatus, reliable values in uniform units of measurement for the rate of water-vapor transmission of insulating and related materials. These values are for use in design, manufacture, and marketing. Correlation of test values with any given use must be determined by experience.

10.2.2 *Procedure*—Test asbestos-cement plastic-foam core insulating panels in accordance with the Desiccant Method given in Test Methods **C 355**.

10.3 *Thermal Resistance, R*:

10.3.1 *Procedure*—Test asbestos-cement plastic-foam core insulating panels in accordance with Test Method **C 236**. Thermal resistance is calculated as the reciprocal of thermal conductance.

## 11. Inspection and Certification

11.1 Inspection and certification of the material shall be as agreed upon by the purchaser and seller as part of the purchase contract.

## 12. Packaging and Package Marking

12.1 *Commercial Quantities*—The commercial unit for marketing flat panels is the square foot. **Table 4** lists sizes generally available commercially.

12.2 *Commercial Packaging*—Asbestos-cement plastic-foam core panels shall be so shipped as to ensure acceptance by common carrier. There is no standard package. The material is usually shipped in bulk, but may be crated when so specified by the purchaser.

12.3 *Storage*—Asbestos-cement plastic-foam core panels should be piled on sufficiently firm supports that will keep the panels level and flat. The panels shall be piled with the edges square and flush, and covered to provide protection from the weather until used.

## SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall apply when material is supplied under this specification for U.S. Government procurement.

### S1. Packaging

S1.1 Unless otherwise specified in the contract, the material shall be packaged in accordance with the producer's standard practice which will be acceptable to the carrier at lowest rates. Containers and packing shall comply with Uniform Freight Classification Rules<sup>6</sup> or National Motor Freight Classification Rules.<sup>7</sup> Marking for shipment of such material shall be in accordance with **Fed. Std. No. 123** for civil agencies and **MIL-STD-129** for military agencies.

<sup>6</sup> Available from The Uniform Classification Commission, Room 1106, 222 S. Riverside Plaza, Chicago, IL 60606.

<sup>7</sup> Available from National Motor Freight Inc., 1616 P. St., N.W., Washington, DC 20036.

### S2. Responsibility for Inspection

S2.1 Unless otherwise specified in the contract or purchase order, the producer is responsible for the testing of all material to assure compliance with the requirements specified herein. Except as otherwise specified in the contract or order, the producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to assure that material conforms to prescribed requirements.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*