



# Standard Test Method for Yield Strength of Enameling Steels After Straining and Firing<sup>1</sup>

This standard is issued under the fixed designation C 774; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers determination of the yield strength of steel specimens after simulated forming and enamel firing operations.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**A 370** Test Methods and Definitions for Mechanical Testing of Steel Products

**E 8** Test Methods for Tension Testing of Metallic Materials

## 3. Definition

3.1 *quarter lines*—imaginary lines parallel to the direction of rolling, positioned at a distance from the sheet mill edge equal to one quarter of the sheet width.

## 4. Summary of Test Method

4.1 Representative sheet-steel specimens are selected, strained in tension to simulate forming, heat treated to simulate enamel firing, and tension tested for determination of yield strength.

## 5. Significance and Use

5.1 In the manufacture of porcelain enameled ware, sheet steel is subjected to forming operations and subsequently to firing of the enamel at temperatures, typically, of 1400 to 1550°F (760 to 844°C). Some steels used for porcelain enameling are subject to grain growth in critically strained areas resulting in loss of strength.

5.2 This may lead to easy deformation of the steel and damage to the porcelain enamel coating.

5.3 This test method may be correlated with transit or use tests to evaluate the suitability of steel for porcelain enameled ware.

## 6. Apparatus

6.1 *Shear* for cutting blanks.

6.2 *Equipment* for cutting or machining tension specimens.

6.3 *Gage*, 2-in. (50.8-mm), for marking tension specimens.

6.4 *Tension-Testing Equipment*, as described in Test Methods and Definitions **A 370**.

6.5 *Specimen-Supporting Rack*, slotted to support specimens on edge spaced 1 in. (25.4 mm) apart.

6.6 *Furnace*, capable of heating the test specimens and their supporting rack to the firing temperature in 2 min.

## 7. Reagents and Materials

7.1 *Sheet Steel*, sufficient in size to provide the test specimen, described in Section 8.

7.2 *Solvent*, such as acetone or isopropyl alcohol.

7.3 *Hydrochloric Acid (1+1)*—Dilute 1 volume of concentrated hydrochloric acid (HCl, sp gr 1.19) with 1 volume of water.

## 8. Sampling

8.1 Obtain ten test samples, each approximately 1 by 9 in. (25 by 229 mm), from within the quarter lines of the sheet sample, the long dimension being in the direction of rolling.

## 9. Procedure

9.1 Remove burrs from the cut edges of the test samples.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.12 on Materials for Porcelain Enamel and Ceramic-Metal Systems.

Current edition approved April 1, 2006. Published April 2006. Originally approved in 1974. Last previous edition approved in 2000 as C 774 – 88 (2000).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

9.2 Mark 2-in. (50.8-mm) gage lengths in the middle of the test samples and strain in tension. Maintain a minimum of 1 in. (25.4 mm) of length between the grips of the tension-testing machine and the gage marks.

9.3 Elongate duplicate test samples to nominal strain levels of 0, 8, 12, 16, and 20 %. Measure the elongation with extensometers, dividers, or other means.

9.4 Remove the test samples from the tension machine and measure actual strain to the nearest 0.01 in. (0.25 mm).

9.5 Clean the strained test samples with the solvent and fire in air atmosphere at  $1450 \pm 10^\circ\text{F}$  ( $788 \pm 5^\circ\text{C}$ ) for 4 min. Test samples may be hung from hooks or supported on edge spaced 1 in. (25.4 mm) apart (if the latter, be sure to support in a manner to prevent sagging during firing). The test samples should reach the firing temperature within  $2.0 \pm 0.5$  min.

9.6 Remove the samples from the furnace and air cool.

9.7 Descale the fired samples in a HCl (1+1) solution containing a few drops of an inhibitor, such as formaldehyde, at a temperature of 70 to 100°F (21 to 38°C). Promptly rinse the test samples and dry.

9.8 Machine the descaled test samples to make standard rectangular tension tests specimens in accordance with Test Methods and Definitions **A 370**. The specimens shall have a minimum length of 8 in. (204 mm) and the sides of the reduced section shall be parallel.

9.9 Measure the thickness and width of each specimen, and test for yield strength as described in Test Methods **E 8** at a crosshead speed of 0.10 in. (2.5 mm)/min. Determine the yield strength at the lower point or by the 0.5 % extension under load.

## 10. Report

10.1 Report the yield strengths determined for the duplicate specimens at each of the five strain levels.

10.2 Report the actual strain imparted to each specimen.

## 11. Precision and Bias

11.1 The precision and bias of yield strength and strain in this test method would be identical to the precision and bias of Test Methods **E 8**. Refer to this standard for up-to-date precision and bias.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*