



Standard Test Method for Rebound Number of Hardened Concrete¹

This standard is issued under the fixed designation C 805/C 805M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This test method covers the determination of a rebound number of hardened concrete using a spring-driven steel hammer.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C 42/C 42M Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete

C 125 Terminology Relating to Concrete and Concrete Aggregates

C 670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

E 18 Test Methods for Rockwell Hardness of Metallic Materials

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this test method, refer to Terminology **C 125**.

4. Summary of Test Method

4.1 A steel hammer impacts, with a predetermined amount of energy, a steel plunger in contact with a surface of concrete, and the distance that the hammer rebounds is measured.

5. Significance and Use

5.1 This test method is applicable to assess the in-place uniformity of concrete, to delineate regions in a structure of poorer quality or deteriorated concrete, and to estimate in-place strength.

5.2 Relationships between rebound number and concrete strength that are provided by instrument manufacturers shall be used only to provide indications of relative concrete strength at different locations in a structure. To use this test method to estimate strength, it is necessary to establish a relationship between strength and rebound number for a given concrete mixture and given apparatus. Establish the relationship by correlating rebound numbers measured on the structure with the strengths of cores taken from corresponding locations. At least two replicate cores shall be taken from at least six locations with different rebound numbers. Select test locations so that a wide range of rebound numbers in the structure is obtained. Obtain, moisture condition, and test cores in accordance with Test Method **C 42/C 42M**.

NOTE 1—See ACI 228.1R³ for additional information on developing the relationship and on using the relationship to estimate in-place strength.

5.3 For a given concrete mixture, the rebound number is affected by factors such as moisture content of the test surface, the method used to obtain the test surface (type of form material or type of finishing), vertical distance from the bottom of a concrete placement, and the depth of carbonation. These factors need to be considered in interpreting rebound numbers.

5.4 Different hammers of the same nominal design may give rebound numbers differing from 1 to 3 units. Therefore, tests should be made with the same hammer in order to compare results. If more than one hammer is to be used, perform tests on

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.64 on Nondestructive and In-Place Testing.

Current edition approved Aug. 1, 2008. Published September 2008. Originally approved in 1975. Last previous edition approved in 2002 as C 805 – 02.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ ACI 228.1R-95, "In-Place Methods to Estimate Concrete Strength," American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

*A Summary of Changes section appears at the end of this standard.

a range of typical concrete surfaces so as to determine the magnitude of the differences to be expected.

5.5 This test method is not suitable as the basis for acceptance or rejection of concrete.

6. Apparatus

6.1 *Rebound Hammer*, consisting of a spring-loaded steel hammer that when released strikes a steel plunger in contact with the concrete surface. The spring-loaded hammer must travel with a consistent and reproducible velocity. The rebound distance of the steel hammer from the steel plunger is measured on a linear scale attached to the frame of the instrument.

NOTE 2—Several types and sizes of rebound hammers are commercially available to accommodate testing of various sizes and types of concrete construction.

6.2 *Abrasive Stone*, consisting of medium-grain texture silicon carbide or equivalent material.

6.3 *Test Anvil*, approximately 150-mm [6-in.] diameter by 150-mm [6-in.] high cylinder made of tool steel with an impact area hardened to 66 ± 2 HRC as measured by Test Methods E 18. An instrument guide is provided to center the rebound hammer over the impact area and keep the instrument perpendicular to the surface.

6.4 *Verification*—Rebound hammers shall be serviced and verified annually and whenever there is reason to question their proper operation. Verify the functional operation of a rebound hammer using the test anvil described in 6.3. During verification, support the test anvil on a bare concrete floor or slab. The manufacturer shall report the rebound number to be obtained by a properly operating instrument when tested on an anvil of specified hardness.

NOTE 3—Typically, a rebound hammer will result in a rebound number of 80 ± 2 when tested on the anvil described in 6.3. The test anvil needs to be supported on a rigid base to obtain reliable rebound numbers. Verification on the test anvil does not guarantee that the hammer will yield repeatable data at other points on the scale. The hammer can be verified at lower rebound numbers by using blocks of polished stone having uniform hardness. Some users compare several hammers on concrete or stone surfaces encompassing the usual range of rebound numbers encountered in the field.

7. Test Area and Interferences

7.1 *Selection of Test Surface*—Concrete members to be tested shall be at least 100 mm [4 in.] thick and fixed within a structure. Smaller specimens must be rigidly supported. Avoid areas exhibiting honeycombing, scaling, or high porosity. Do not compare test results if the form material against which the concrete was placed is not similar (see Note 4). Troweled surfaces generally exhibit higher rebound numbers than screeded or formed finishes. If possible, test structural slabs from the underside to avoid finished surfaces.

7.2 *Preparation of Test Surface*—A test area shall be at least 150 mm [6 in.] in diameter. Heavily textured, soft, or surfaces with loose mortar shall be ground flat with the abrasive stone described in 6.2. Smooth-formed or troweled surfaces do not have to be ground prior to testing (see Note 4). Do not compare results from ground and unground surfaces. Remove free surface water, if present, before testing.

NOTE 4—Where formed surfaces were ground, increases in rebound

number of 2.1 for plywood formed surfaces and 0.4 for high-density plywood formed surfaces have been noted.⁴ Dry concrete surfaces give higher rebound numbers than wet surfaces. The presence of surface carbonation can also result in higher rebound numbers.⁵ In cases of a thick layer of carbonated concrete, it may be necessary to remove the carbonated layer in the test area, using a power grinder, to obtain rebound numbers that are representative of the interior concrete. Data are not available on the relationship between rebound number and thickness of carbonated concrete. The user should exercise professional judgment when testing carbonated concrete.

7.3 Do not test frozen concrete.

NOTE 5—Moist concrete at 0 °C [32 °F] or less may exhibit high rebound values. Concrete should be tested only after it has thawed. The temperatures of the rebound hammer itself may affect the rebound number. Rebound hammers at -18 °C [0 °F] may exhibit rebound numbers reduced by as much as 2 or 3 units⁶.

7.4 For readings to be compared, the direction of impact, horizontal, downward, upward, or at another angle, must be the same or established correction factors shall be applied to the readings.

7.5 Do not conduct tests directly over reinforcing bars with cover less than 20 mm [0.75 in.].

NOTE 6—The location of reinforcement may be established using reinforcement locators or metal detectors. Follow the manufacturer's instructions for proper operation of such devices.

8. Procedure

8.1 Hold the instrument firmly so that the plunger is perpendicular to the test surface. Gradually push the instrument toward the test surface until the hammer impacts. After impact, maintain pressure on the instrument and, if necessary, depress the button on the side of the instrument to lock the plunger in its retracted position. Read the rebound number on the scale to the nearest whole number and record the rebound number. Take ten readings from each test area. No two impact tests shall be closer together than 25 mm [1 in.]. Examine the impression made on the surface after impact, and if the impact crushes or breaks through a near-surface air void disregard the reading and take another reading.

9. Calculation

9.1 Discard readings differing from the average of 10 readings by more than 6 units and determine the average of the remaining readings. If more than 2 readings differ from the average by 6 units, discard the entire set of readings and determine rebound numbers at 10 new locations within the test area.

10. Report

10.1 Report the following information, if known, for each test area.

10.1.1 General information:

10.1.1.1 Date of testing,

⁴ Gaynor, R. D., "In-Place Strength of Concrete—A Comparison of Two Test Systems," and "Appendix to Series 193," National Ready Mixed Concrete Assn., TIL No. 272, November 1969.

⁵ Zoldners, N. G., "Calibration and Use of Impact Test Hammer," *Proceedings*, American Concrete Institute, Vol 54, August 1957, pp. 161–165.

⁶ National Ready Mixed Concrete Assn., TIL No. 260, April 1968.

- 10.1.1.2 Air temperature and time of testing,
- 10.1.1.3 Age of concrete, and
- 10.1.1.4 Identification of test location in the concrete construction and the size of member tested.
- 10.1.2 Information about the concrete:
 - 10.1.2.1 Mixture identification and type of coarse aggregate, and
 - 10.1.2.2 Specified strength of concrete.
- 10.1.3 Description of test area:
 - 10.1.3.1 Surface characteristics (trowelled, screeded, formed),
 - 10.1.3.2 If applicable, type of form material used for test area,
 - 10.1.3.3 If surface was ground and depth of grinding,
 - 10.1.3.4 If applicable, curing conditions, and
 - 10.1.3.5 Surface moisture condition (wet or dry).
- 10.1.4 Hammer information:
 - 10.1.4.1 Hammer identification or serial number, and
 - 10.1.4.2 Date of hammer verification.
- 10.1.5 Rebound number data:

- 10.1.5.1 Orientation of hammer during test,
- 10.1.5.2 On vertical surfaces (walls, columns, deep beams), relative elevation of test region,
- 10.1.5.3 Individual rebound numbers,
- 10.1.5.4 Remarks regarding discarded readings,
- 10.1.5.5 Average rebound number, and
- 10.1.5.6 If applicable, description of unusual conditions that may affect test readings.

11. Precision and Bias

11.1 *Precision*—The single-specimen, single-operator, machine, day standard deviation is 2.5 units (1s) as defined in Practice C 670. Therefore, the range of ten readings should not exceed 12.

11.2 *Bias*—The bias of this test method cannot be evaluated since the rebound number can only be determined in terms of this test method.

12. Keywords

12.1 concrete; in-place strength; nondestructive testing; rebound hammer; rebound number

SUMMARY OF CHANGES

Committee C09 has identified the location of selected changes to this test method since the last issue, C 805 – 02, that may impact the use of this test method. (Approved August 1, 2008)

- (1) The standard was revised as a combined units designation.
- (2) Revised 5.2 by requiring a correlation to be developed only by using cores.
- (3) Revised 5.3 by adding information on the effect of elevation in a concrete placement.
- (4) Revised 5.5 to clarify that the method is not suitable to accept or reject concrete.
- (5) Revised 7.2 by adding a provision to remove free water before testing. Revised Note 4 by deleting the sentence referring to wetting of the surface.
- (6) Revised Section 10 Report to provide more logical groupings of the information to be reported and to acknowledge that all the information may not be known.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).