



Standard Practice for Preparing Refractory Castable Specimens by Cold Gunning¹

This standard is issued under the fixed designation C 903; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers a procedure for preparing refractory castable specimens usually containing calcium aluminate cement with or without metal fibers by cold nozzle-mix gunning. Specimens prepared in accordance with this practice are intended for use in standard ASTM test methods required for evaluating gunned materials.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C 401 Classification of Alumina and Alumina-Silicate Castable Refractories

C 865 Practice for Firing Refractory Concrete Specimens

3. Significance and Use

3.1 The properties of refractory castables can be affected by their method of installation. This practice attempts to minimize the variables encountered during installation by pneumatic gunning.

3.2 This practice provides parameters to produce gunned specimens for use in other ASTM test methods.

3.3 This practice may be used to produce specimens for acceptance testing, service evaluation, manufacturing control, and research and development.

3.4 Differences between various kinds of equipment and the differences in procedures and operator techniques may result in significant variations in the physical properties of the gunned specimens. It is recommended that the same operator use the

same equipment to produce specimens for referee testing agreed to by the involved testing parties. The specific operating parameters should be shown in the report.

3.5 Although this practice is specifically designed for refractory castables containing calcium aluminate cement, it may be used with minor modifications for gun mixes containing other bond systems.

4. Apparatus

4.1 *Gun*, pneumatic nozzle-mix.³ At least 50 ft (15.2 m) of hose should be available. Acceptable nozzle diameters range from 1 to 2 in. (25 to 51 mm).

4.2 *Air Compressor*, capable of delivering sufficient pressure and volume to adequately move castable to the gun. The compressor should be able to supply at least 250 ft³ (7 m³)/min.

4.3 *Forms*, suitable nonabsorbent type, which will vary in size in accordance with the number of samples being prepared, but are typically 36 by 36 by 5½ in. (915 by 915 by 140 mm). Forms should be sized to prevent rebound entrapment. The use of ½ inch hardware cloth as sidewalls of the form allows most of the rebound to pass through. This reduces the size of the form required to achieve the desired standard sized central portion of 24 by 24 in. (610 by 610 mm).

4.4 Suitable eye and hand protection must be worn capable of protection against high velocity refractory particles and steel fibers.

5. Procedure

5.1 Store the castable to be gunned at 70 to 85°F (20 to 27°C) for 24 h prior to gunning.

5.2 Oil the forms lightly. Typically 10W-30 oil is used. Place the form against a rigid surface at an angle of 80 to 90° to the horizontal.

5.3 If recommended by the supplier, predampen the castable by mixing with potable water in a paddle mixer for 1 to 5 min or follow manufacturer's specific instructions. In general, regular (dense) castables require 2 to 4 % of predampening water and lightweight (insulating) castables require 5 to 8 %.

NOTE 1—Castables that contain a high-purity cement may benefit by aging for 5 to 10 min after dampening before gunning. This "aging"

¹ This practice is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.09 on Monolithics.

Current edition approved March 1, 2008. Published April 2008. Originally approved in 1979. Last previous edition approved in 2004 as C 903 – 98 (2004).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Equipment available from Allentown Equipment Co., 421 Schantz Road, Allentown, PA 18104, <http://www.allentownequipment.com>, has been found suitable for this purpose (Model N-3 or N-2).

procedure should be used if gunning without it produces excessive rebound, dusting, or slumping.

NOTE 2—Treat castables containing metal fibers in a normal manner. If metal fibers are to be added to the gunning material, add them to the paddle mixer before any water is introduced. The amount of fiber to be added and the methods of reporting this amount shall be agreed upon by the parties involved. To prevent clumping of the fibers they should be added slowly through a suitable screen of ½ in. mesh. Fibers larger than 1 in. may require larger openings. If any predampening water is to be added, dry mix for two to three min before adding water.

5.4 Gun the castable into the form at a distance of 3 to 4 ft (0.91 to 1.2 m) from gun nozzle. Hold the gun nozzle at 90° to the form. Gunning pressures are suggested to be approximately 40 psi (276 kPa) for regular-weight castables and approximately 20 psi (138 kPa) for insulating refractory castables. If more than 50 ft (15 m) of hose is used, it may be necessary to add 5 psi (34 kPa) for each additional 50 ft. These conditions and the amount of potable water used must be adjusted by the nozzleman for acceptable rebound. The gunning pattern involves moving the nozzle in a circular motion, back and forth across the form, beginning at the bottom. Report any unusual dusting, slumping, or other unique characteristics of the refractory castable. The water, material, and environment temperature shall also be reported.

NOTE 3—For referee tests all participating laboratories should agree on a specific gun pressure and other test parameters to obtain reproducible results. Excessive air pressures and hose lengths may cause changes in properties of the gunned castable especially in properties of gunned insulating castables.

5.5 Trim the gunned surface approximately parallel to the back of the form. As soon as possible after gunning, score the panel as deep as possible in from all sides to provide a standard sized central portion of 24 by 24 in. (610 mm by 610 mm) free from rebound. See Practice **C 865** for procedures concerning the measurement of specimens.

5.6 Cover the castable surface with a curing medium, for example a curing compound or polyethylene plastic sheet. For

calcium aluminate bonds, optimum curing temperature is 90 to 95°F (32 to 35°C) for 24 + 0.5 h.

5.7 Cut suitably sized lamination-free specimens from the central section. Cut specimen to exclude the portion nearest the backboard to eliminate trapped rebound. Identify the gunned face or gunning direction on each specimen since it may influence the results of subsequent tests.

5.8 Specimens prepared according to section 5.7 that will be used for further testing shall be placed in a 150°F oven; hold until all specimens have been inserted. Increase temperature at a rate of 50°F/h (28°C/h) maximum from 150°F to between 220° to 230°F (105 to 100°C) and hold for at least 15 h prior to testing or firing in a prescribed manner.

5.9 Determine specific properties by selected test procedures.

6. Report

6.1 Report the following information:

6.1.1 Specific predampening water content and type of mixer,

6.1.2 Premix time,

6.1.3 Temperature of the water, castable, and environment,

6.1.4 Aging time (if any),

6.1.5 Type of gun, length and diameter of hose,

6.1.6 Gunning pressure employed,

6.1.7 Nozzle size and type,

6.1.8 Size and type of form used,

6.1.9 Type and amount (by weight or volume) of any metal fibers added prior to gunning, and

6.1.10 Curing time, temperature and environment.

6.2 The report may also specify the amount of rebound and any unusual gunning characteristics observed.

6.3 The report may include any other parameters agreed to by the parties involved.

7. Keywords

7.1 gunning; rebound; predampening; refractory castable; specimens

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).