



Standard Test Method for Time of Setting of Grouts for Preplaced-Aggregate Concrete in the Laboratory¹

This standard is issued under the fixed designation C 953; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This method covers the determination test of time of setting of hydraulic cement grout mixtures used in preplaced-aggregate (PA) concrete using the vicat apparatus.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C 191 Test Methods for Time of Setting of Hydraulic Cement by Vicat Needle

C 938 Practice for Proportioning Grout Mixtures for Preplaced-Aggregate Concrete

C 511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes

3. Summary of Method

3.1 The time of setting, initial and final, of a sample of fluid grout is determined using the Vicat apparatus.

4. Significance and Use

4.1 This test method determines the setting time of grout mixed to the fluid consistency required for its use in PA concrete.

4.2 The time of setting is also useful in determining the acceptability of components of grout that must be mixed to the fluid consistency required for production of PA concrete.

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.41 on Concrete for Radiation Shielding.

Current edition approved Feb. 1, 2006. Published February 2006. Originally approved in 1981. Last previous edition approved in 1997 as C 953 – 87(1997).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5. Apparatus

5.1 *Vicat Apparatus*, in accordance with Test Method **C 191**.

5.2 *Moist Room*, maintained in accordance with Specification **C 511**.

6. Test Sample

6.1 The test sample shall consist of at least 300 mL of grout taken from a freshly-mixed batch prepared in accordance with Practice **C 938** obtained from a mixer at the laboratory or construction site.

7. Procedure

7.1 Warm the Vicat conical ring and base plate to approximately 100 °C.

7.2 Apply a thin film of paraffin wax to the base of the conical ring and place the waxed conical ring on the base plate. Place a weight on the conical ring to ensure intimate contact with the base plate and allow the conical ring and plate to cool to room temperature.

7.3 Fill the conical ring apparatus with grout flush with its top within 2 min after completion of mixing. Strike off the grout flush with the top of the conical ring by a single oblique stroke of a sharp-edged trowel held at a slight angle to the top of the ring. Smooth the top, if necessary, with a few light touches of the pointed end of the trowel. Take care not to compress the sample during these cutting and smoothing operations. The time of completion of molding shall be taken as the start of measurement of time of set.

7.4 Store the specimen in the moist room.

7.5 Determine the time of setting using the procedure described in Test Method **C 191** except that the first reading shall be taken 3 h \pm 15 min after pouring the specimen.

NOTE 1—Grouts used to evaluate grout fluidifier or for use in PA concrete will normally reach initial set in about 4 h.

8. Report

8.1 The report shall include the following:

8.1.1 Identification of the grout sample,

8.1.2 Time of initial setting and final setting in hours and minutes,

8.1.3 Temperature of group sample at the beginning of the test, and

*A Summary of Changes section appears at the end of this standard.

8.1.4 Ambient temperature during the test.

9.2 *Bias*—No statement on Bias can be prepared because there are no standard reference materials.

9. Precision and Bias

9.1 *Precision*—When data have been compiled that are suitable for use in preparing a precision statement, such statement will be prepared.

10. Keywords

10.1 grout; replaced-aggregate concrete; time of setting

SUMMARY OF CHANGES

Committee C09 has identified the location of selected changes to this test method since the last issue, C 953 – 87(1997), that may impact the use of this test method. (Approved February 1, 2006)

(I) Added new paragraph 1.2 and renumbered subsequent paragraphs.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).