



## Standard Test Method for Kerosene Retention of Asbestos<sup>1</sup>

This standard is issued under the fixed designation C 1124; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the determination of the kerosene retention capacity of asbestos fiber by filtering after mixing and measuring the volume of liquid retained by difference.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* See Section 8.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 1655 Specification for Aviation Turbine Fuels<sup>2</sup>
- D 2590 Test Method for Sampling Chrysotile Asbestos<sup>3</sup>
- D 2946 Terminology Relating to Asbestos<sup>3</sup>
- D 3879 Test Method for Sampling Amphibole Asbestos<sup>3</sup>
- E 11 Specification for Wire-Cloth Sieves for Testing Purposes<sup>4</sup>
- E 177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods<sup>4</sup>

#### 2.2 Other Standards:

- US Federal Specifications, VV-K-211 d, Kerosene<sup>5</sup>
- Canadian Government Specifications Board CAN 2-3.3-M85 Kerosene<sup>6</sup>
- United Kingdom, Ministry of Defense Specification DEF-2403-A<sup>7</sup>

### 3. Terminology

- 3.1 *Definitions*—Refer to Terminology D 2946.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C-17 on Fiber-Reinforced Cement Products and is the direct responsibility of Subcommittee C17.03 on Asbestos-Cement Sheet Products and Accessories.

Current edition approved Oct. 26, 1990. Published December 1990. Originally published as C 1124 – 89. Last previous edition C 1124 – 89.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 05.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 04.05.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 14.02.

<sup>5</sup> Available from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

<sup>6</sup> Available from The Secretary, Canadian General Standard Board, Ottawa, ONT, Canada K1A 1G6.

<sup>7</sup> Available from Her Majesty's Stationery Office, London, England.

### 4. Summary of Test Method

4.1 A slurry of asbestos fiber is formed by mixing in a known volume of kerosene. The slurry is then drained on a standard 177 μm (U.S. No. 80) screen as defined in Specification E 11, and the kerosene that drains out in 15 min is measured. The quantity of kerosene retained is obtained by difference.

### 5. Significance and Use

5.1 The kerosene retention value is an indication of the degree of fiberization and of the absorptivity of a given grade of asbestos.

5.2 Since the retention of the fibrous fractions is much greater than that of the non-fibrous fractions, this test method may be used to compare the fibrous content of otherwise similar grades of asbestos.

### 6. Apparatus

6.1 *Kerosene Drainage Apparatus*—Described in Fig. 1 and Fig. 2.

### 7. Reagents and Materials

7.1 *Kerosene*, meeting one of the following specifications:

- 7.1.1 US Federal Specifications, VV-K-211 d, Kerosene.
- 7.1.2 Jet A Kerosine specified in Specification D 1655.
- 7.1.3 United Kingdom, Ministry of Defense Specification DEF-2403-A.
- 7.1.4 Kerosine CGSB Spec CAN 2-3.3-M85.

### 8. Hazards

8.1 When handling asbestos use reasonable precautions to avoid creating dust. Prolonged or frequent breathing of significant concentrations of airborne asbestos dust may cause serious bodily harm.

### 9. Sampling, Test Specimens, and Test Units

#### 9.1 Sampling:

9.1.1 Take samples in accordance with Test Methods D 2590 in the case of chrysotile asbestos or Test Method D 3879 in the case of amphibole asbestos.

#### 9.2 Test Specimens:

9.2.1 Two specimens each of  $50 \pm 0.05$  g are required.

### 10. Procedure

10.1 Put a 50 g specimen into a 400 cm<sup>3</sup> beaker and add 325




FIG. 1 Kerosene Retention Apparatus Assembly

$\pm 1 \text{ cm}^3$  of kerosene.

10.2 Mix with a spatula for 120 s (2 min).

10.3 Wet the drainage cylinder and screen with kerosene and drain 1 min.

10.4 Place a 250- $\text{cm}^3$  graduated cylinder beneath the drainage cylinder outlet.

10.5 Immediately transfer the slurry in one continuous motion to the drainage cylinder.

10.6 Start a stopwatch simultaneously.

10.7 After draining for 900 s (15 min), read the volume of kerosene drained into the graduate, and record this value to the nearest  $\text{cm}^3$ .

10.8 Discard the asbestos retained on the screen, rinse clean with running hot water, and dry the apparatus.<sup>8</sup> Thus it will be ready for the next test.

10.9 Repeat this procedure with the second specimen.

## 11. Calculation

11.1 For each of the two readings, subtract the value obtained, in  $\text{cm}^3$ , from the initial quantity of kerosene (325  $\text{cm}^3$ ). Multiply these differences by two to obtain the kerosene retention values per 100 g of asbestos fiber.

11.2 *Example*—If the reading on the graduated cylinder was 215  $\text{cm}^3$ , then the kerosene retention




FIG. 2 Retention Apparatus Detail

$$\text{value} = (325 - 215) \times 2 = 220 \text{ cm}^3/100 \text{ g.}$$

## 12. Report

12.1 Report the average of two kerosene retention values in  $\text{cm}^3/100 \text{ g}$ .

12.2 Fully identify the sample tested as to designation and origin.

## 13. Precision and Bias

### 13.1 Acceptance of Results:

13.1.1 Results on two specimens must agree within 2 % of the average. If this is not attained, repeat the test until two results within 2 % from the average are obtained.

### 13.2 Precision:

13.2.1 The single-laboratory, multi-operator-apparatus day precision (repeatability) is  $\pm 2 \%$  (two sigma limits expressed in units of percentage) as defined in Practice E 177 over the range of 200 to 400  $\text{cm}^3/100 \text{ g}$ .

### 13.3 Bias:

13.3.1 No justifiable statement on the bias of this test method can be made since the true values cannot be established by an accepted referee method.

13.3.2 A partial verification of the repeatability that confirmed the above data is on file. A copy is available upon request.<sup>9</sup>

<sup>8</sup> A jet of clean dry compressed air may be used to accelerate the drying.

<sup>9</sup> Supporting data is available from ASTM Headquarters. Request RR: C17-1002.

## **14. Keywords**

14.1 absorption; asbestos; kerosene; kerosene retention; oil;  
oil absorption; retention capacity

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*