Standard Test Method for Loose Density of Asbestos¹

This standard is issued under the fixed designation C 1162; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the loose density of asbestos fiber for Groups 5 to 9, inclusive.²,³

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See Section 7.

2. Referenced Documents

2.1 ASTM Standards:

- D 2590 Test Method of Sampling Chrysotile Asbestos⁴
- D 2946 Terminology Relating to Asbestos⁴
- D 3639 Test Method for Classification of Asbestos by Quebec Standard Test⁴

D 3879 Test Method for Sampling Amphibole Asbestos⁴

 $E\ 177\ Practice \ for \ Use \ of \ the \ Terms \ Precision \ and \ Bias \ in \ ASTM \ Test \ Methods^5$

2.2 Other Standard:

Quebec Standard Designation of Chrysotile Asbestos Fiber Grades³

3. Terminology

3.1 Definitions-Refer to Terminology D 2946.

4. Summary of Test Method

4.1 The test method consists of measuring the weight of a $1770\text{-cm}^3(\frac{1}{16} \text{ ft}^3)$ volume of asbestos fiber, and of computing the loose density in kilograms per cubic meter (pounds per cubic foot).

5. Significance and Use

5.1 Loose density gives an indication of the degree of fiberization, harshness, and loftiness of asbestos fiber.

6.1 *Container*, 1770 cm³($\frac{1}{16}$ ft³) in volume made of plastic tubing 12.7 cm (5 in.) inner diameter, with 6-mm (0.25-in.) thick walls and 13.4-cm (5.5-in.) internal height (commercially available tubing). The bottom consists of a flat disk of the same plastic cemented to the tubing.

6.2 Scoop, capable of holding at least 2.8 dm³(0.1 ft³).
6.3 Straight-edged Spatula or Ruler.

7. Safety Hazards

7.1 When handling asbestos use reasonable precautions to avoid creating dust. Prolonged or frequent breathing of significant concentrations of airborne asbestos dust may cause serious bodily harm.

8. Sampling, Test Specimens, and Test Units

8.1 *Sampling*—Take samples in accordance with Test Method D 2590 in the case of chrysotile asbestos or Test Method D 3879 in the case of amphibole asbestos.

8.2 Test Specimens:

8.2.1 The test specimen must exceed the volume of the container by approximately 50 %. Therefore its volume must be at least 2.8 dm³(0.1 ft³).

8.2.2 Two specimens are required.

9. Procedure

9.1 Place the specimen in the scoop and hold the latter 8 to 10 cm (3 to 4 in.) above the container.

9.2 Pour the specimen into the container using a continuous shaking motion and fill the container to overflowing.

9.3 Using the spatula, or a ruler, immediately level off the fiber to the top of the container. Do this in several passes to avoid compressing the fiber.

9.4 Determine the mass of fiber contained in the measure to the nearest 2 g (0.1 oz).

Note 1—The mass in ounces is equivalent to the loose density in pounds per cubic foot.

9.5 Repeat the procedure on the second specimen.

10. Calculation

10.1 Calculate the loose density in kilograms per cubic centimetre (pounds per cubic foot).

10.3 If equivalent units are desired, divide results in kilograms per cubic metre by 16.03 to get pounds per cubic foot.

Copyright © ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States.

azmanco.com

¹ This test method is under the jurisdiction of ASTM Committee C-17 on Fiber-Reinforced Cement Productsand is the direct responsibility of Subcommittee C17.03 on Asbestos–Cement Sheet Products and Accessories.

Current edition approved Oct. 26, 1990. Published December 1990.

² As determined by Test Method D 3639.

³ The classification is available from the Asbestos Institute, 1130 Sherbrooke St. West, Suite 410 Montreal, QC, Canada, H3A 2M8.

⁴ Annual Book of ASTM Standards, Vol 04.05. ⁵ Annual Book of ASTM Standards, Vol 14.02.

^{6.} Apparatus

^{10.2} Average the results of the two specimens.

11. Report

11.1 Report results in kilograms per cubic centimetre (pounds per cubic foot).

11.2 Fully identify the sample as to designation and origin.

12. Precision and Bias

12.1 Precision:

12.1.1 The single-laboratory-apparatus multi-operatorday precision (repeatability) is ± 2 % (two sigma limits expressed in units of percentage) (2*S* %) as defined in Practice E 177 over the range of 160 to 1600 kg/m³(10 to 100 lb/ft³).

12.1.2 A partial verification of the repeatability that confirmed the above data is on file at ASTM Headquarters.⁶

12.2 *Bias*—No justifiable statement on the bias can be made since the true values of loose density cannot be established by an accepted referee method.

13. Keywords

13.1 asbestos; bulk; bulk density; loose density

⁶ Request RR:C17-1003.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

azmanco.com