



## Standard Specification for Firebox Brick for Residential Fireplaces<sup>1</sup>

This standard is issued under the fixed designation C 1261; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification covers brick intended for use as the lining in the fireboxes of residential fireplaces.

1.2 Firebox brick are manufactured from clay, fire clay, shale, or similar naturally occurring earthy substances and subjected to a heat treatment at elevated temperatures (firing). The heat treatment must develop a fired bond between the particulate constituents to provide the strength and durability requirements of this specification.

NOTE 1—Firebox brick are typically installed using ground fire clay mortar or refractory mortar. Mortar joints are typically  $\frac{1}{8}$  in. (3.2 mm) thick, just thick enough to accommodate dimensional variations in the firebox brick.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 The text of this specification references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this specification.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- C 24 Test Method for Pyrometric Cone Equivalent (PCE) of Fire Clay and High Alumina Refractory Materials
- C 43 Terminology of Structural Clay Products
- C 67 Test Methods of Sampling and Testing Brick and Structural Clay Tile

### 3. Terminology

3.1 *Definitions*—For definitions of terms relating to this specification, see Terminology C 43.

### 4. Materials, Manufacture, and Finish

4.1 Clay, as it occurs in nature, differs in composition and physical properties. These differences are compensated for by varying the manufacture processes of forming and firing. In order to be satisfactory for firebox brick production, clays must have plasticity that permits them to be shaped or molded when mixed with water. Clays must also have sufficient tensile strength to maintain shape.

4.2 Firebox brick are shaped during manufacture by molding, pressing, or extruding and cutting. Firebox brick shall be 100 % solid with no cores or frogs.

4.3 Firebox brick shall be free of defects, deficiencies, and surface treatments, including coatings, that would interfere with the proper setting of the brick or significantly impair the strength or performance of the construction.

### 5. Physical Properties

5.1 *Modulus of Rupture*—Residential firebox brick shall have a minimum modulus of rupture of 500 psi (3.45 MPa).

5.2 *Pyrometric Cone Equivalent (PCE)*—Firebox brick shall have a minimum pyrometric cone equivalent (PCE) of 13.

### 6. Dimensions and Permissible Variations

6.1 *Size*—The size of the firebox brick shall be as specified by the purchaser. In the sample of units, no firebox brick shall depart from the specified size by more than the maximum permissible variation given in Table 1.

6.2 *Warpage*—Tolerances for distortion or warpage of face or edges of individual brick from a plane surface and from a straight line, respectively, shall not exceed the maximum permissible distortion given in Table 1.

6.3 *Visual Inspection*—The brick, as delivered to the site, shall conform by visual inspection to the samples approved as the standard of comparison. Minor indentations or surface cracks incidental to the usual method of manufacturing or the chippage resulting from the customary methods of handling in shipments and delivery shall not be deemed grounds for rejection.

6.4 *Variation of Appearance Requirements*—When units are required for decorative installations that have appearance requirements, that is, size variation, distortion, or chippage, other than those prescribed by this specification, the purchaser

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.02 on Brick and Structural Clay Tile.

Current edition approved January 1, 2004. Published February 2004. Originally approved in 1994. Last previous edition approved in 1998 as C 1261 – 98.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Tolerances on Dimensions**

| Specified Dimension,<br>in. (mm) | Maximum Permissible<br>Variation, $\pm$ in. (mm) | Maximum<br>Permissible<br>Distortion, in. (mm) |
|----------------------------------|--|--|
| 3 (76) and under                 | $\frac{1}{16}$ (1.6)                             | $\frac{1}{32}$ (0.8)                           |
| over 3 to 4 (76 to 102), incl    | $\frac{1}{16}$ (1.6)                             | $\frac{3}{64}$ (1.2)                           |
| over 4 to 6 (102 to 152), incl   | $\frac{3}{32}$ (2.4)                             | $\frac{1}{16}$ (1.6)                           |
| over 6 to 8 (152 to 203), incl   | $\frac{1}{8}$ (3.2)                              | $\frac{5}{64}$ (2.0)                           |
| over 8 to 12 (203 to 305), incl  | $\frac{5}{32}$ (4.0)                             | $\frac{1}{8}$ (3.2)                            |

shall specify the required maximum permissible variation in size or distortion and the allowable extent of chipping.

6.5 *Waste*—The number of firebox brick in a delivery that are broken or otherwise fail to meet the requirements of Table 1 shall not exceed 5 %.

## 7. Sampling and Testing

7.1 The brick shall be sampled in accordance with Test Methods C 67. Test firebox brick in accordance with Test

Methods C 67 for modulus of rupture, size, and warpage; and Test Method C 24 for pyrometric cone equivalence.

7.2 The manufacturer or the seller shall furnish specimens for tests without charge. The place or places of selection shall be designated when the purchase order is placed.

NOTE 2—Unless otherwise specified in the purchase order, the cost of tests is typically borne as follows: If the results of the tests show that the brick do not conform to the requirements of this specification, the cost is typically borne by the seller. If the results of the tests show that the brick do conform to the requirements of this specification, the cost is typically borne by the purchaser.

## 8. Keywords

8.1 brick; firebox; fireplace

## SUMMARY OF CHANGES

Committee C15 has identified the location of selected changes to this standard since the C 1261–98 edition that may impact the use of this standard.

(I) Non-mandatory wording in Section 6.5 was revised to be mandatory.

Committee C15 has identified the location of selected changes to this standard since the C 1261–96 edition that may impact the use of this standard.

(I) Paragraph 6.4 was separated into two sections, with the new section titled “Variation of Appearance Requirements.”

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*