



Standard Specification for Sampling, Inspection, Rejection, Certification, Packaging, Marking, Shipping, Handling, and Storage of Gypsum Board¹

This standard is issued under the fixed designation C 1264; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers sampling; inspection; rejection; certification; packaging and marking; and shipping, handling, and storage of gypsum board.

2. Sampling

2.1 When specified by the purchase agreement, samples of gypsum board shall be taken at the place of manufacture or at the destination. If the samples are taken at the destination, such samples shall be taken within 24 h of the receipt of the material.

2.2 At least 0.25 % of the number of gypsum boards in a shipment, but not less than three boards, shall be so selected as to be representative of the shipment and shall constitute a sample for the purpose of tests by the purchaser or user.

3. Inspection

3.1 Inspection of the gypsum board shall be agreed upon between the purchaser and the producer or supplier as part of the purchase agreement.

4. Rejection

4.1 Rejection of gypsum board that fails to conform to the requirements of the specification shall be reported to the producer or supplier promptly and in writing. The notice of rejection shall contain a statement documenting how the

gypsum board has failed to conform to the requirements of the specification.

5. Certification

5.1 When specified in the purchase agreement, a producer's or supplier's report shall be furnished at the time of shipment certifying that the product is in compliance with the ASTM specification referencing this specification.

6. Packaging and Marking

6.1 Unless otherwise specified in the purchase agreement, each board or package shall have legibly marked thereon the following: the thickness; the name of the producer or supplier; the brand name, if any; and the ASTM specification for the product.

7. Shipping, Handling, and Storage

7.1 Gypsum board shall be shipped so as to be kept dry.

7.2 Gypsum board shall be stored so as to be kept dry, preferably inside a building, under a roof. Gypsum board shall be neatly stacked flat with care taken to prevent sagging or damage to edges, ends, and surfaces.

7.3 Where necessary to store gypsum board outside, it shall be stacked flat, off the ground, supported on a level platform, and fully protected from weather and direct sunlight exposure.

8. Keywords

8.1 certification; gypsum; gypsum board; handling; inspection; marking; packaging; rejection; sampling; shipping; storage

¹ This specification is under the jurisdiction of ASTM Committee C-11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.01 on Specifications and Test Methods for Gypsum Products.

Current edition approved Oct. 10, 1999. Published December 1999. Originally published as C 1264 – 94. Last previous edition C 1264/C 1264M – 95.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).