



Standard Test Method for Measuring Consistency of Castable Refractory Using a Flow Table¹

This standard is issued under the fixed designation C 1445; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the procedure for determining the consistency of castable refractory mixes by the flow table method.

1.2 This test method applies to regular weight castable refractories, insulating castable refractories, and castable refractories that require heavy vibration for forming, which are described in Classification C 401. They also apply to such castables containing metal fibers.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

C 71 Terminology Relating to Refractories²

C 230 Specification for Flow Table for Use in Tests of Hydraulic Cement³

C 401 Classification of Alumina and Alumina-Silicate Castable Refractories²

C 860 Practice for Determining the Consistency of Refractory Castable Using the Ball-in-Hand Test²

D 346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis⁴

3. Significance and Use

3.1 The amount of water used in a castable mix for preparing test specimens has a significant influence on subsequent test results. This test method is used primarily to determine and reproduce the consistency required for the optimum casting of refractory castables in the preparation of

test specimens and to express that consistency quantitatively. The correct water content is one of the major factors that must be controlled to obtain uniform test specimens. Excess water can reduce strength, increase volume shrinkage, and promote segregation of the castable ingredients. Insufficient water can produce “honeycombs” (air voids) in the castable because of poor consolidation during placement and prevent complete hydration of cement.

3.2 The flow table (see sketches in Specification C 230) has been found to be an excellent tool for measuring the consistency of a castable and should be used in cases where a numerical result is required. Since castables differ somewhat in their “body” or plasticity, it has been found that a good casting range, expressed numerically, might vary from castable to castable. While one material may cast well between 40 and 60 % flow, another material may need to be in the 60 to 80 % flow range to properly flow. Because of this, it has been found that no arbitrary optimum range can be stated for all castables. The flow table then becomes a tool for measuring the flow and not determining it. It can allow the operator to follow the manufacturer’s recommendations or to reproduce the consistency of a particular castable between laboratories.

3.3 Total time of wet mixing must be closely controlled to obtain reproducible results.

3.4 This test method is not intended to be used to determine the proper water content for gunning applications, although it may provide information of value for interpretation by a skilled operator.

4. Apparatus

4.1 *Balance*, 15-lb (6.8-kg) capacity, with sensitivity of 0.002 lb (1 g).

4.2 *Flow Table, Mold, and Calipers*, conforming to the requirements of Specification C 230.

4.3 *Tamper*, A nonabsorbing, nonabrasive, non-brittle material such as a rubber compound having a Shore A durometer hardness of 80 ± 10 or seasoned oak wood rendered nonabsorbing by immersion for 15 min. In paraffin at approximately 392°F (200°C), and the tamper shall have a cross section of ½ by 1 in. (13 by 25 mm) and a convenient length of 5 to 6 in. (127 to 152 mm). The tamping face shall be flat and at right angles to the length of the tamper.

4.4 *Trowel*, having a steel blade 4 to 6 in. (100 to 150 mm)

¹ This test method is under the jurisdiction of ASTM Committee C-8 on Refractories and is the direct responsibility of Subcommittee C08.09 on Monolithic Refractories.

Current edition approved Oct. 10, 1999. Published January 2000.

² *Annual Book of ASTM Standards*, Vol 15.01.

³ *Annual Book of ASTM Standards*, Vol 04.01.

⁴ *Annual Book of ASTM Standards*, Vol 05.05.

in length, with straight edges.

4.5 *Castable Mixer*—Either a manually or electrically operated (see Fig. 1) mechanical mixer⁵ may be used to prepare batches for the consistency determination. Size the mixing bowl to contain 50 to 70 % volume loading with the dry batch.

NOTE 1—Castable-water requirement variation becomes more significant as dry volume loadings drop below 50 % of the capacity of the mixer bowl because the water required to wet the bowl surfaces changes more rapidly with decreasing volume loadings.

4.6 *Thermometer*, dial-type, metal, with a range from 0 to 180°F (−18 to 80°C).

4.7 *Vibrating Table*—An electric vibrating table with 3600 Hz and at least a 1-ft² surface.

4.8 *Sample Splitter*, designed to reduce the castable to the desired weight and ensure that the grain size distribution is representative of the original batch.

NOTE 2—A Jones or riffle-type sample splitter is satisfactory, provided the openings are large enough to accommodate the largest aggregate particle. If a sample splitter is not available, hand reduction by the cone-and-quarter method may be used. Follow the applicable portions of this test method as described in Practice D 346.

5. Sampling

5.1 At the time of use, the dry castable mix should be between 68 and 72°F (20 and 22°C). The temperature is measured by inserting the full length of the dial-thermometer stem into the material until the reading is constant.

5.2 Reduce the mass of the castable mix with a sample splitter to obtain the desired batch size in accordance with 5.3. Take precautions to prevent segregation. If additional batches are required, they should also be reduced to the desired batch size with a sample splitter.

5.3 Batch sizes for the flow table test normally consist of 10 lb (4.5 kg) for a regular weight or 5 lb (2.3 kg) for an insulating castable. Mixer size may dictate other sizes. (See 4.5).

6. Procedure

6.1 Preparation of Castable Sample:

⁵ Mixers having various capacities, available from the Hobart Manufacturing Co., Troy, OH, have been found suitable for this purpose.

6.1.1 Weigh the castable sample (see 5.3) to the nearest 0.02 lb (9 g). Place the batch in the mixer described in 4.5 (see Note 1), and dry mix for 1 min. While the mixer is operating at slow speed, add 90 % of the estimated water requirement having a temperature between 68 and 72°F (20 and 22°C), within ½ min. Operate the mixer at 50 to 60 rpm, then add additional water in small amounts from a tared container, and mix until the batch appears to have the desired flow.

6.1.2 The total actual wet mixing time, including water additions, should be 3 min ± 10 s for dense castables, 5 min ± 10 s for insulating castables, and 4 to 6 min for mixes needing heavy vibration, unless specified differently by the manufacturer.

NOTE 3—Mixing times of less than 5 min for insulating castables may influence the results because lightweight aggregates usually soak up water during the initial stages of mixing and affect the consistency of the batch. Depending on the aggregate type, particle breakdown may occur with excessive mixing time. This was not observed in subcommittee round-robin tests with a 5-min mixing time using a variety of lightweight castables.

6.2 Determination of Flow:

6.2.1 For mixes that do not require heavy vibration for forming, such as regular weight and insulating castable refractories, proceed with flow determination in the following manner:

6.2.1.1 Carefully wipe the flow-table top until clean and dry, and place the flow mold at the center. Place a layer of castable about 1 in. (25 mm) in thickness into the mold, and tamp 20 times with the tamper. The tamping pressure should be just sufficient to ensure uniform filling of the mold. Fill the mold with additional castable, and tamp as specified for the first layer. Cut off the castable to a plane surface flush with the top of the mold by drawing the straightedge of a trowel (held nearly perpendicular to the mold) with a sawing motion, across the top of the mold. Wipe the table top around the mold until clean and dry. Carefully remove any water from around the edge of the flow mold. Lift the mold away from the castable within 1 min after completing the mixing operation described in 6.1.1.

6.2.2 For castables that require heavy vibration for forming, proceed with flow determination in the following manner:

6.2.2.1 Place the mold with large end up on the vibrating table. Place an excess amount of castable into the mold. Turn on the vibrating table while holding the sample mold firmly on the table. Vibrate the sample until all the large air bubbles cease evolving from the castable and the castable fills out the mold. Cease vibration. Scrape off the excess castable above the upper rim of the mold with a straightedge trowel. Vibrate the sample again until its upper surface is smooth and even with the upper rim of the sample mold. The total vibration time should be no more than 30 s. Rotate the sample mold on the vibrating table so that the sample will not adhere to the table. Slide the sample off the vibrating table and place it, inverted, onto the center of a clean, dry flow table. Lift the mold vertically from the table while pressing down upon the castable sample so that minimal deformation of the sample occurs. Lift the mold away from the castable within 1 min after completing the mixing operation described in 6.1.1.

6.2.3 Immediately drop the table 15 times in 9 s a height of



FIG. 1 Special Mixer for Castable Refractories

½ in. (13 mm). This distance is automatically controlled by a cam in a properly constructed flow table (see Specification C 230). The flow is the resulting increase in average base diameter of the castable mass, expressed as a percentage of the original base diameter. The special caliper shown in Fig. 1 of Specification C 230 is graduated to indicate one fourth of the actual flow so that the readings of four measurements may be added to give the flow value, eliminating calculations of the average of four individual measurements. Using the special caliper, make four measurements of the base diameter of the castable mass at equivalently spaced intervals. Sum the four measurements to obtain the percent flow.

6.2.4 In reproducing a consistency within a specified flow range, it may be necessary to make several trial mixes with varying percentages of water. Make each trial with a fresh batch.

7. Report

7.1 Report the following information:

7.1.1 The type of mixer used to prepare the test batch.

7.1.2 The amount of water used in each batch (% by wt. dry castable).

7.1.3 The total mixing time (minutes).

7.1.4 The dry mix temperature, °F (°C).

7.1.5 The water temperature, °F (°C).

7.1.6 The percent flow directly from the sum of the special calipers, or calculated as follows if using standard calipers:

$$\frac{(\text{average base diameter} - \text{original base diameter})}{\text{original base diameter}} \times 100 (\%)$$

8. Precision and Bias

8.1 *Precision*—The repeatability standard deviation has been determined to be 1.71 on a refractory castable having an grand average flow of 31.15 %.⁶ The reproducibility standard deviation from the same testing was 0.24. The combined repeatability and reproducibility standard deviation was 1.73.

NOTE 4—This information was based upon a Gauge Repeatability and Reproducibility study performed by North American Refractories Company using multiple trials and multiple operators, but only one flow table. Additional precision testing between laboratories must be conducted on this test method.

8.2 *Bias*—While a standard reference material now exists which could be used for interlaboratory testing of bias,⁷ this work has not yet been completed.

9. Keywords

9.1 castable; concrete; consistency; flow; mixing; refractory; flow-table

⁶ Supporting data have been filed at ASTM Headquarters and may be obtained by requesting Research Report RR C08-1015.

⁷ Laboratory Flow Table Calibration Mixture available from Cement and Concrete Reference Laboratory; Building Research, 226-Room A365; National Institute of Standards and Technology; Gaithersburg, MD 208989.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).