



Standard Specification for Gypsum Lath¹

This standard is issued under the fixed designation C 37/C 37M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification covers plain and foil-backed types of gypsum lath which is designed to be used as a base for application of gypsum plaster (see Specification C 28).

NOTE 1—Specification C 841 contains application procedures for interior lathing and furring, and Specification C 842 contains application procedures for interior gypsum plaster.

1.2 The values stated in either inch-pound or SI (metric) units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system shall be used independent of the other. Values from the two systems shall not be combined.

1.3 The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 ASTM Standards:

- C 11 Terminology Relating to Gypsum and Related Building Materials and Systems²
- C 28 Specification for Gypsum Plasters²
- C 473 Test Methods for Physical Testing of Gypsum Panel Products²
- C 841 Specification for Installation of Interior Lathing and Furring²
- C 842 Specification for Application of Interior Gypsum Plaster²
- C 1264 Specification for Sampling, Inspection, Rejection, Certification, Packaging, Marking, Shipping, Handling, and Storage of Gypsum Board²
- E 96 Test Methods for Water Vapor Transmission of Materials³
- E 119 Test Methods for Fire Tests of Building Construction and Materials⁴

¹ This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.01 on Specifications and Test Methods for Gypsum Products. Current edition approved May 10, 2001. Published July 2001. Originally published as C 37 – 21 T. Last previous edition C 37 – 99.

² Annual Book of ASTM Standards, Vol 04.01.

³ Annual Book of ASTM Standards, Vol 04.06.

⁴ Annual Book of ASTM Standards, Vol 04.07.

3. Terminology

3.1 Definitions of terms shall be in accordance with Terminology C 11.

4. Materials and Manufacture

4.1 Plain gypsum lath shall consist of a noncombustible core, essentially gypsum, surfaced with paper bonded to the core.

4.2 Foil-backed gypsum lath shall consist of plain gypsum lath with a layer of aluminum foil laminated to the back surface.

NOTE 2—Foil-backed gypsum lath shall be installed with the foil surface against the framing members. The foil surface is not adapted to receive or retain plaster.

4.3 Gypsum lath, type X (special fire-resistant) designates gypsum lath complying with this specification that provides not less than 1 h fire-resistance for lath $\frac{3}{8}$ in. [9.5 mm] thick, applied perpendicular with and on each side of load bearing 2×4 wood studs spaced 16 in. [406 mm] o.c. with blue lath nails, $1\frac{1}{8}$ in. [29 mm] long, 0.092 in. [2.3 mm] diameter shank, $\frac{1}{64}$ in. [7.5 mm] diameter heads, spaced 5 in. [127 mm] o.c. with lath joints staggered 16 in. [406 mm] on each side of the partition, over which is applied $\frac{1}{2}$ in. [12.7 mm] of 1:2 gypsum sand plaster, and tested in accordance with the requirements of Test Method E 119.

NOTE 3—Consult producers for independent test data on assembly details and fire resistance classifications for other types of construction. See fire test reports, or listings from recognized fire testing laboratories, for assembly particulars, materials, and classifications.

NOTE 4—The definition of type X as given in 4.3 is intended only as a test to define the gypsum lath as meeting the requirements of type X. This test does not indicate a preferred application nor does it limit the use of the product in other fire rated assemblies.

5. Physical Properties

5.1 Specimens shall be taken from the samples obtained in accordance with Specification C 1264.

5.2 Specimens shall be tested in accordance with Test Methods C 473.

5.2.1 *Flexural Strength*—The specimens shall be tested face up and face down. The average breaking load shall be not less than the following:

Method A

Method B

*A Summary of Changes section appears at the end of this standard.

Thickness, in. [mm]	Load, lbf [N] Bearing Edges Across Fiber of Surfacing	Load, lbf [N] Bearing Edges Parallel to Fiber of Surfacing	Load, lbf [N] Bearing Edges Across Fiber of Surfacing	Load, lbf [N] Bearing Edges Parallel to Fiber of Surfacing
3/8 [9.5]	60 [267]	25 [111]	56 [249]	21 [93]
1/2 [12.7]	100 [445]	35 [156]	97 [431]	31 [138]

5.2.2 Humidified Deflection—The specimens shall have an average deflection of not more than the following:

Thickness, in. [mm]	Humidified Deflection, Eighths of an inch [mm]
3/8 [9.5]	15 [48]
1/2 [12.7]	10 [32]

5.2.3 Core, End, and Edge Hardness—The specimens shall have an average hardness of not less than 15 lbf [67 N] when tested by Method A and 11 lbf [49 N] when tested by Method B.

5.2.4 Nail-Pull Resistance—The specimen shall have an average nail-pull resistance of not less than the following:

Thickness, in. [mm]	Method A Nail Pull Resistance, lbf [N]	Method B Nail Pull Resistance, lbf [N]
3/8 [9.5]	50 [222]	46 [205]
1/2 [12.7]	70 [312]	66 [294]

5.3 Foil Backed Gypsum Lath:

5.3.1 Foil-backed gypsum lath shall meet all of the requirements for gypsum lath.

5.3.2 When tested in accordance with Test Method E 96, the permeance of foil-backed gypsum lath shall be not more than 0.30 perm [17 ng/Pa·s·m²] (Desiccant Method) for the condition of 50 % relative humidity on the face of the lath and 0 % relative humidity on the foil-covered back side of the lath.

6. Dimensions and Tolerances

6.1 Specimens shall be taken from the samples obtained in

accordance with Specification C 1264.

6.2 Thickness, width, length, and end squareness shall be determined in accordance with Test Methods C 473.

6.2.1 Thickness—The nominal thickness shall be 3/8 or 1/2 in. [9.5 or 12.7 mm] with tolerances in the nominal thickness of $\pm 1/32$ in. [0.8 mm] and with local variations of $\pm 1/16$ in. [1.6 mm] from the nominal thickness.

6.2.2 Width—The nominal width shall be up to 48 in. [1220 mm], with a tolerance of $3/16$ in. [5 mm] under and $1/8$ in. [3 mm] over the specified width.

6.2.3 Length—The nominal length shall be 32, 36, 48, and up to 144 in. [810, 910, 1220, and 3660 mm] and tolerances shall be $1/4$ in. [6 mm] under and $1/8$ in. [3 mm] over the specified width.

6.2.4 End Squareness—Corners shall be square with a tolerance of $\pm 1/4$ in. [6 mm] in the full width of the lath.

6.3 Edges and Ends—The edges and ends shall be straight and either round or square.

7. Finish and Appearance

7.1 The surfaces of gypsum lath shall be true and free from imperfections that render the lath unfit to receive and retain gypsum plasters.

7.2 Gypsum lath having burred or broken corners shall be considered acceptable provided that the burred or broken portion is not more than 1 in. [25 mm] in either dimension.

8. Sampling, Inspection, Rejection, Certification, Packaging, Marking, Shipping, Handling and Storage

8.1 Shall be in accordance with Specification C 1264.

9. Keywords

9.1 gypsum; gypsum lath; gypsum lath, type X; foil-backed; ceiling; partitions; wall

SUMMARY OF CHANGES

Committee C-11 has identified the location of selected changes to this standard since the last issue, C 37/C 37M-99, that may impact the use of this standard.

(I) Note 3 was revised.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).