



Standard Specification for Marble Dimension Stone (Exterior)¹

This standard is issued under the fixed designation C 503; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of marble for general (exterior) building and structural purposes.

1.2 Dimension marble shall include stone that is sawed, cut, split, or otherwise finished or shaped and shall specifically exclude molded, cast, or otherwise artificially aggregated units composed of fragments, and also crushed and broken stone.

2. Referenced Documents

2.1 ASTM Standards:²

C 97 Test Methods for Absorption and Bulk Specific Gravity of Dimension Stone

C 99 Test Method for Modulus of Rupture of Dimension Stone

C 119 Terminology Relating to Dimension Stone

C 170 Test Method for Compressive Strength of Dimension Stone

C 241 Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic

C 880 Test Method for Flexural Strength of Dimension Stone

C 1353 Test Method Using the Taber Abraser for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic

3. Terminology

3.1 *Definitions*—All definitions are in accordance with Terminology C 119.

3.1.1 *marble, n*—a crystalline rock composed predominantly of one or more of the following minerals: calcite, dolomite, or serpentine and capable of taking a polish (see Terminology C 119).

4. Classification

4.1 Dimension marble (exterior) is classified as follows:

4.1.1 *I Calcite.*

4.1.2 *II Dolomite.*

4.1.3 *III Serpentine.*

4.1.4 *IV Travertine.*

5. Physical Properties

5.1 Marble supplied under this specification shall conform to the physical requirements prescribed in Table 1.

5.2 Marble for exterior use shall be sound, durable, and free of spalls, cracks, open seams, pits, or other defects that are likely to impair its structural integrity in its intended use.

5.3 The desired color and texture, with their permissible natural variations in material characteristics for all material to be produced for the project, shall be established by control samples. Select representative samples by viewing a sufficient number of physical samples prior to production that show the complete range of variations in color and texture of the marble specified.

6. Sampling

6.1 Samples, if required, for testing to determine the characteristics and physical properties shall be representative of the marble to be used.

¹ This specification is under the jurisdiction of ASTM Committee C18 on Dimension Stone and is the direct responsibility of Subcommittee C18.03 on Material Specifications.

Current edition approved Dec. 1, 2003. Published January 2004. Originally approved in 1962. Last previous edition approved in 1999 as C 503 – 99^{ε1}.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



TABLE 1 Physical Requirements

NOTE—The material property values in Table 1 were established using samples prepared according to the individual test methods. Finishes, other than those specified in the individual test methods, may result in a deviation from established values..

Physical Property	Test Requirements	Classification(s)	Test Method(s)
Absorption by weight, max, %	0.20	I, II, III, IV	C 97
Density, min, lb/ft ³ (kg/m ³)	162 (2595)	I Calcite ^A	C 97
	175 (2800)	II Dolomite ^A	
	168 (2690)	III Serpentine ^A	
	144 (2305)	IV Travertine ^A	
Compressive strength, min, psi (MPa)	7500 (52)	I, II, III, IV	C 170
Modulus of rupture, min, psi (MPa)	1000 (7)	I, II, III, IV	C 99
Abrasion resistance, min, hardness ^{B,C,D}	10	I, II, III, IV	C 241/C 1353
Flexural strength, min, psi (MPa)	1000 (7)	I, II, III, IV	C 880

^A See Terminology C 119 for definitions of calcite, dolomite, serpentine, and travertine marbles.

^B Pertains only to stone subject to foot traffic. Where two or more marbles are combined for color and design effects, there should be no greater difference than five points in abrasion resistance.

^C The supplier of the No. 60 Alundum abrasive, Norton, has indicated that the formula for Norton treatment 138S has been changed. The new abrasive is currently more aggressive, resulting in lower abrasive hardness values (H_a) than when the standard was initially established. As such, care should be taken when interpreting H_a values from tests using the new abrasive, particularly with regard to current ASTM stone standard specification requirements for abrasion resistance, which were developed when the original abrasive was still in use. Committee C18 is actively studying alternatives to address this issue.

^D Abrasion Resistance Test Method C 1353 will eventually replace Test Method C 241 and it is not necessary to perform both tests. Availability of the proper equipment and materials by the testing laboratory may determine which test is performed.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).