



Standard Classification of Fireclay and High-Alumina Plastic Refractories and Ramming Mixes¹

This standard is issued under the fixed designation C 673; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This classification covers fireclay and high-alumina plastic refractories and ramming mixes that can be pounded or rammed into place to form a monolithic structure. The terms “plastic” and “ramming mix” are generally intended to describe the workability of the material. In this regard, plastics are considered to be materials having a workability index of more than 15 % in accordance with Test Method C 181, while ramming mixes generally have less than 15 % workability by the same procedure.

2. Referenced Documents

2.1 ASTM Standards:

C 24 Test Method for Pyrometric Cone Equivalent (PCE) of Fireclay and High-Alumina Refractory Materials²

C 181 Test Method for Workability Index of Fireclay and High-Alumina Plastic Refractories²

NOTE 1—Chemical analysis of refractory products are determined by a combination of x-ray fluorescence (XRF) and inductively coupled plasma (ICP) using standard reference materials (SRM); including various types of minerals and refractory materials which are available from the National Institute of Standards and Technology and other appropriate sources.

3. Significance and Use

3.1 This classification defines a group of classes for use by those producing or purchasing fireclay and high-alumina plastic refractories and ramming mixes. Each class is limited by PCE, or alumina content, or both. This classification is frequently used as a specification when the properties shown in Table 1 are the only items specified.

4. Classifications

4.1 Fireclay plastic refractories and ramming mixes are divided into two different classifications: (1) super-duty, and (2) high-duty.

¹ This classification is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.09 on Monolithic Refractories.

Current edition approved April 10, 2003. Published June 2003. Originally approved in 1971. Last previous edition approved in 1997 as C 673 – 84 (1997).

² Annual Book of ASTM Standards, Vol 15.01.

TABLE 1 Classification of Fireclay and High-Alumina Plastic Refractories and Ramming Mixes

Class	PCE, min	Al ₂ O ₃ , %
High-duty	31	NR ^A
Super-duty	32½	NR
60 % alumina	35	57.6 to 62.5
65 % alumina	35-36	62.6-67.5
70 % alumina	36	67.6 to 72.5
80 % alumina	37	77.6 to 82.5
85 % alumina	NR	82.6 to 87.5
90 % alumina	NR	87.6 to 92.5
95 % alumina	NR	92.6 to 97.5
100 % alumina	NR	>97.5

^ANR = not required.

4.2 High-alumina plastic refractories and ramming mixes are divided into eight different classifications: (1) 60 % alumina, (2) 65 % alumina, (3) 70 % alumina, (4) 80 % alumina, (5) 85 % alumina, (6) 90 % alumina, (7) 95 % alumina, and (8) 100 % alumina.

5. Basis of Classification

5.1 The properties required for compliance with a particular classification are shown in Table 1.

6. Test Methods

6.1 The determination of aluminum oxide (Al₂O₃) on an ignition-free basis, as required by this classification, as determined by XRF and ICP.

6.2 The determination of the pyrometric cone equivalent (PCE), as required by this classification, shall be in accordance with Test Method C 24.

7. Retests

7.1 Because of possible variables that may result from sampling or an unsatisfactory reproducibility of tests by different laboratories, the material may be resampled and retested at the request of either the purchaser or the manufacturer. This could apply where the first test results may not conform to the requirements prescribed in this classification. Therefore, the final results to be used shall be the average of at least two series of tests, each of which has been obtained by following the specified testing procedures in detail.



8. Keywords

ramming mixes; workability

8.1 classification; fireclay plastic refractories; fireclay ramming mixes; high-alumina plastic refractories; high-alumina

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).