



## Standard Practice for Preparing Test Specimens From Basic Refractory Gunning Products by Pressing<sup>1</sup>

This standard is issued under the fixed designation C 973; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice covers a procedure for preparing test specimens from basic refractory gunning products by pressing prepared material in a mold. After pressing, test specimens prepared from dolomitic mixes are subjected to a prescribed heat treatment. Specimens prepared in accordance with this procedure are intended for use in ASTM test methods.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Significance and Use

2.1 This practice defines a procedure that ensures consistent preparation of specimens for product testing and evaluation.

2.2 This practice can be used in the laboratories of producers, users, and general-interest parties for research and development or quality-control work. It is particularly useful for interlaboratory comparisons on products, for repetitive evaluations or comparisons of products or product equality, and in specifying a uniform preparation practice for specimens for acceptance testing.

2.3 In using this practice, it must be recognized that the structure of laboratory-pressed specimens may differ significantly from the structure of material gunned in field applications.

### 3. Apparatus

3.1 *Mixer*, bench-type, Hobart or equivalent.

3.2 *Press*, mechanical or hydraulic.

3.3 *Steel Molds*.

3.4 *Furnace*.

3.5 *Oven*, air-circulating.

3.6 *Desiccator*.

3.7 *Trowel*.

### 4. Procedure

4.1 Store the material to be tested at  $85 \pm 2^\circ\text{F}$  ( $29.5 \pm 1^\circ\text{C}$ ) for 24 h prior to testing. Dolomitic materials should be stored in airtight containers.

4.2 Reduce the sample to the desired batch size with a sample splitter or by quartering taking precautions to prevent segregation. Sufficient material should be batched to provide at least a 10 % excess over test specimen requirements.

4.3 Add the weighed, dry batch to the mixer and dry-mix at low speed for 30 s. Continue to mix at low speed while adding the required amount of water (see 4.3.1) within 30 s. Wet-mix at low speed for 3 min.

4.3.1 Use the amount of water and mixing time (if different from above) recommended by the manufacturer. The water must be potable and at a temperature of  $85 \pm 2^\circ\text{F}$  ( $29.5 \pm 1^\circ\text{C}$ ). Measure the water addition to the nearest 0.1 % by weight.

4.4 Specimens of the desired size should be pressed immediately after the batch is mixed. Weigh the proper amount of material (see 4.4.1) for each specimen to the nearest 0.02 lb (10 g), and distribute the mix uniformly in the mold using the narrow edge of a trowel. (The remainder of the batch should be covered with a damp cloth during the pressing procedure). Press test specimens at 1800 psi (12.41 MPa).

4.4.1 Some products contain hydratable materials (for example, dead-burned dolomite) or quick-setting bonds, or both, that tend to react during the course of pressing several specimens from a single wet-mixed batch. Because of this reaction, the physical properties of specimens pressed near the beginning of a batch may differ from those of specimens pressed near the end. Products of these types should be mixed in small batches to minimize this effect.

4.5 Test specimens prepared from mixes that do not contain dolomite should be air-dried for 4 h, and then dried for a minimum of 8 h at  $225 \pm 5^\circ\text{F}$  ( $107 \pm 2.5^\circ\text{C}$ ) in a circulating air dryer prior to testing. Testing should be carried out within 48 h.

4.6 Test specimens prepared from dolomitic mixes require special handling to prevent hydration. Place the test specimens in a furnace at  $1830^\circ\text{F}$  ( $1000^\circ\text{C}$ ) immediately after pressing

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee C-8 on Refractories and is the direct responsibility of Subcommittee C08.09 on Monolithics.

Current edition approved Aug. 28, 1987. Published September 1987. Originally published as C 973 – 82. Last previous edition C 973 – 82.

and soak for a minimum of 2 h. Then remove them from the furnace before it has cooled below 1100°F (593°C), cool in air for a maximum of 2 h, and store in a desiccator or nitrogen-purged box prior to testing. Testing must be performed within 48 h, taking precautions to prevent hydration.

## **5. Calculation and Report**

5.1 In the report on specimen preparation, include the percent water addition, drying time, and test specimen size.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*