

Methods of testing cement —

Part 6: Standard sand for mortar cubes

IMPORTANT NOTE. It is recommended that this Part be read in conjunction with the information in Part 0 "General Introduction" to BS 4550, which is issued separately

UDC 666.94.01:666.971.12



NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

Foreword

This British Standard has been prepared under the direction of the Cement, Gypsum, Aggregates and Quarry Products Standards Committee. It brings together and revises the specification for standard sand for mortar cubes described in the appendices of the following British Standards.

BS 12-2:1971, Portland cement (ordinary and rapid-hardening).

BS 915-2:1972, High alumina cement.

BS 4248:1974, Supersulphated cement.

Part 0 of BS 4550 is a general introduction; Part 1 lays down methods of sampling cement; Part 2 describes methods of chemical testing of cement; Part 3 describes methods of physical testing of cement; Part 4 specifies the standard coarse aggregate for concrete cubes and Part 5 specifies the standard sand for concrete cubes. Publication of BS 4550 enables the standards listed in the previous paragraph and BS 146-2:1973 "Portland-blastfurnace cement", BS 1370-2:1974 "Low heat Portland cement", BS 4027-2:1972 "Sulphate-resisting Portland cement" and BS 4246-2:1974 "Low heat Portland-blastfurnace cement", which cross refer to BS 12-2:1971, to be revised by deletion of the relevant appendices. This will avoid repetition in the expanding range of cement standards and ensure that, if changes are made in any of the test methods or specifications, the standards remain in step.

This Part of BS 4550 specifies the standard sand to be used in accordance with clause **2** "Compressive strength of mortar cubes", of Section **3.4** "Strength tests" of BS 4550 "*Methods of testing cement*" Part 3 "*Physical tests*".

It is anticipated that the mortar cube test will be deleted at the first revision of BS 4550 "*Methods of testing cement*" Part 3: Physical tests.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 and 2, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

This British Standard, having been prepared under the direction of the Cement, Gypsum, Aggregates and Quarry Products Standards Committee, was published under the authority of the Executive Board on 30 June 1978

© BSI 07-1999

The following BSI references relate to the work on this standard:

Committee reference CAB/1 Draft for comment 73/10751 DC

ISBN 0 580 10153 3

Amendments issued since publication

| Date of issue | Comments |
|---------------|---------------|
| | |
| | |
| | |
| | |
| | Date of issue |



Contents

| | | Page | |
|----------|--------------------------------|--------------------|--|
| Foreword | | Inside front cover | |
| 1 | Scope | 1 | |
| 2 | References | 1 | |
| 3 | Source | 1 | |
| 4 | Sampling | 1 | |
| 5 | Moisture content | 1 | |
| 6 | Grading | 1 | |
| 7 | Content of acid-soluble matter | 1 | |
| 8 | Marking | 1 | |
| Pul | nlications referred to | Inside back cover | |

© BSI 07-1999 i azmanco.com

1 Scope

This Part of this British Standard specifies the source, preparation and properties of a standard sand to be used for making mortar cubes.

2 References

The titles of the publications referred to in this Part are listed on the inside back cover.

3 Source

Natural (uncrushed) thoroughly washed and dried silica sand of the white variety shall be obtained from Leighton Buzzard, Bedfordshire.

4 Sampling

Using a suitable scoop or similar device, a main sample of about 8 kg shall be taken from a single bag selected at random from a delivery not exceeding 500 kg. For the purposes of either of the tests specified in clauses 5 and 6, the main sample shall be reduced to about 500 g by four passes through a sample divider. For the purpose of the test specified in clause 7, a sample of the specified size shall be taken from this reduced sample.

5 Moisture content

The moisture content of the sample obtained as in clause 4 shall not exceed 0.1 % by dry mass when tested by the standard (oven drying) method in BS 812-2.

6 Grading

The sample of the sand, obtained as specified in clause 4, shall pass an $850~\mu m$ test sieve and the proportion by mass passing a $600~\mu m$ test sieve shall not exceed 10~% when determined by the normal test procedure for sieve analysis given in BS 812-1. The test sieves shall be as specified in BS 410.

7 Content of acid-soluble matter

The sand shall show a loss of mass not exceeding 0.25 % on extraction with hot hydrochloric acid when determined by the following method.

Dry a sample of a little over 2 g of the sand at a temperature of 105 ± 5 °C for a period of 1 h. Weigh a quantity of approximately 2g of the dried sand to ± 0.001 g into a porcelain dish and add 20 ml of hydrochloric acid and 20 ml of distilled water. Heat the dish on a water bath for 1 h, filter the contents, and wash well with hot water. Dry the sand, ignite it in a covered crucible, cool it and weigh it again. The loss in mass shall be expressed as a percentage of the original mass of the sample.

8 Marking

The sand, processed in accordance with the requirements of this Part of this standard, shall be supplied in a suitable container marked with the following particulars:

- a) the name, trade mark or other means of identification of the processor;
- b) the number of this British Standard, i.e. BS 4550-6.

azmanco.com

Publications referred to

BS 410, Specification for test sieves.

BS 812, Methods for sampling and testing of mineral aggregates, sands and fillers.

 $BS\ 812\text{-}1, Sampling, size, shape\ and\ classification.$

 ${\it BS~812-2}, Physical\ properties.$

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.

389 Chiswick High Road London W4 4AL